

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.593E+00	2.700E-01	-1.663E-01	3.932E+00	1.373E+00	1.432E+00
4.429E+00	2.800E-01	6.251E-01	3.726E+00	1.484E+00	1.256E+00
4.276E+00	2.900E-01	9.657E-01	3.533E+00	1.521E+00	1.161E+00
4.133E+00	3.000E-01	1.779E+00	2.903E+00	1.610E+00	9.015E-01
4.000E+00	3.100E-01	1.645E+00	1.376E+00	1.377E+00	4.998E-01
3.875E+00	3.200E-01	5.819E-01	5.302E-01	8.274E-01	3.204E-01
3.758E+00	3.300E-01	-3.729E-01	3.142E-01	2.395E-01	6.559E-01
3.647E+00	3.400E-01	-1.113E+00	2.714E-01	1.277E-01	1.063E+00
3.543E+00	3.500E-01	-1.739E+00	2.690E-01	1.017E-01	1.323E+00
3.444E+00	3.600E-01	-2.307E+00	2.780E-01	9.135E-02	1.522E+00
3.351E+00	3.699E-01	-2.841E+00	2.904E-01	8.605E-02	1.688E+00
3.263E+00	3.799E-01	-3.357E+00	3.038E-01	8.282E-02	1.834E+00
3.180E+00	3.899E-01	-3.864E+00	3.174E-01	8.067E-02	1.967E+00
3.100E+00	3.999E-01	-4.367E+00	3.311E-01	7.917E-02	2.091E+00
3.024E+00	4.099E-01	-4.868E+00	3.448E-01	7.809E-02	2.208E+00
2.952E+00	4.199E-01	-5.372E+00	3.586E-01	7.732E-02	2.319E+00
2.884E+00	4.299E-01	-5.879E+00	3.725E-01	7.678E-02	2.426E+00
2.818E+00	4.399E-01	-6.391E+00	3.865E-01	7.642E-02	2.529E+00
2.756E+00	4.499E-01	-6.908E+00	4.008E-01	7.621E-02	2.629E+00
2.696E+00	4.599E-01	-7.432E+00	4.153E-01	7.613E-02	2.727E+00
2.638E+00	4.699E-01	-7.964E+00	4.300E-01	7.616E-02	2.823E+00
2.583E+00	4.799E-01	-8.503E+00	4.451E-01	7.629E-02	2.917E+00
2.531E+00	4.899E-01	-9.050E+00	4.604E-01	7.650E-02	3.009E+00
2.480E+00	4.999E-01	-9.606E+00	4.762E-01	7.680E-02	3.100E+00
2.431E+00	5.099E-01	-1.017E+01	4.924E-01	7.717E-02	3.190E+00
2.385E+00	5.199E-01	-1.074E+01	5.090E-01	7.761E-02	3.279E+00
2.340E+00	5.299E-01	-1.133E+01	5.260E-01	7.813E-02	3.367E+00
2.296E+00	5.399E-01	-1.192E+01	5.436E-01	7.870E-02	3.453E+00
2.255E+00	5.499E-01	-1.252E+01	5.616E-01	7.934E-02	3.540E+00
2.214E+00	5.599E-01	-1.313E+01	5.802E-01	8.004E-02	3.625E+00
2.175E+00	5.699E-01	-1.376E+01	5.994E-01	8.079E-02	3.710E+00
2.138E+00	5.799E-01	-1.439E+01	6.192E-01	8.160E-02	3.794E+00
2.102E+00	5.899E-01	-1.503E+01	6.396E-01	8.247E-02	3.878E+00
2.067E+00	5.999E-01	-1.568E+01	6.606E-01	8.339E-02	3.961E+00
2.033E+00	6.099E-01	-1.634E+01	6.823E-01	8.437E-02	4.043E+00
2.000E+00	6.199E-01	-1.701E+01	7.046E-01	8.539E-02	4.126E+00
1.968E+00	6.299E-01	-1.770E+01	7.276E-01	8.647E-02	4.208E+00
1.938E+00	6.399E-01	-1.839E+01	7.514E-01	8.760E-02	4.289E+00
1.908E+00	6.499E-01	-1.909E+01	7.759E-01	8.877E-02	4.370E+00
1.879E+00	6.599E-01	-1.981E+01	8.012E-01	8.999E-02	4.451E+00
1.851E+00	6.699E-01	-2.053E+01	8.272E-01	9.126E-02	4.532E+00
1.824E+00	6.799E-01	-2.126E+01	8.540E-01	9.258E-02	4.612E+00
1.797E+00	6.899E-01	-2.201E+01	8.816E-01	9.394E-02	4.692E+00
1.771E+00	6.999E-01	-2.276E+01	9.100E-01	9.535E-02	4.772E+00
1.747E+00	7.099E-01	-2.353E+01	9.393E-01	9.680E-02	4.852E+00
1.722E+00	7.199E-01	-2.431E+01	9.694E-01	9.829E-02	4.931E+00
1.699E+00	7.299E-01	-2.509E+01	1.000E+00	9.983E-02	5.010E+00
1.676E+00	7.399E-01	-2.589E+01	1.032E+00	1.014E-01	5.089E+00
1.653E+00	7.499E-01	-2.670E+01	1.065E+00	1.030E-01	5.168E+00
1.632E+00	7.599E-01	-2.752E+01	1.099E+00	1.047E-01	5.247E+00

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.610E+00	7.699E-01	-2.835E+01	1.133E+00	1.064E-01	5.325E+00
1.590E+00	7.799E-01	-2.919E+01	1.169E+00	1.082E-01	5.403E+00
1.570E+00	7.899E-01	-3.004E+01	1.205E+00	1.099E-01	5.482E+00
1.550E+00	7.999E-01	-3.090E+01	1.243E+00	1.118E-01	5.560E+00
1.531E+00	8.099E-01	-3.177E+01	1.281E+00	1.136E-01	5.638E+00
1.512E+00	8.199E-01	-3.265E+01	1.320E+00	1.155E-01	5.715E+00
1.494E+00	8.299E-01	-3.355E+01	1.361E+00	1.175E-01	5.793E+00
1.476E+00	8.399E-01	-3.445E+01	1.402E+00	1.194E-01	5.871E+00
1.459E+00	8.499E-01	-3.536E+01	1.445E+00	1.215E-01	5.948E+00
1.442E+00	8.599E-01	-3.629E+01	1.488E+00	1.235E-01	6.025E+00
1.425E+00	8.699E-01	-3.722E+01	1.533E+00	1.256E-01	6.103E+00
1.409E+00	8.799E-01	-3.817E+01	1.579E+00	1.277E-01	6.180E+00
1.393E+00	8.899E-01	-3.913E+01	1.625E+00	1.299E-01	6.257E+00
1.378E+00	8.999E-01	-4.010E+01	1.673E+00	1.321E-01	6.334E+00
1.363E+00	9.099E-01	-4.107E+01	1.722E+00	1.343E-01	6.410E+00
1.348E+00	9.199E-01	-4.206E+01	1.772E+00	1.366E-01	6.487E+00
1.333E+00	9.299E-01	-4.306E+01	1.823E+00	1.389E-01	6.564E+00
1.319E+00	9.399E-01	-4.407E+01	1.876E+00	1.412E-01	6.640E+00
1.305E+00	9.499E-01	-4.510E+01	1.929E+00	1.436E-01	6.717E+00
1.292E+00	9.599E-01	-4.613E+01	1.984E+00	1.460E-01	6.793E+00
1.278E+00	9.698E-01	-4.717E+01	2.040E+00	1.485E-01	6.870E+00
1.265E+00	9.799E-01	-4.822E+01	2.097E+00	1.509E-01	6.946E+00
1.253E+00	9.899E-01	-4.929E+01	2.155E+00	1.535E-01	7.022E+00
1.240E+00	9.999E-01	-5.036E+01	2.215E+00	1.560E-01	7.098E+00
1.228E+00	1.010E+00	-5.145E+01	2.275E+00	1.586E-01	7.175E+00
1.216E+00	1.020E+00	-5.255E+01	2.337E+00	1.612E-01	7.251E+00
1.204E+00	1.030E+00	-5.365E+01	2.401E+00	1.638E-01	7.327E+00
1.192E+00	1.040E+00	-5.477E+01	2.465E+00	1.665E-01	7.403E+00
1.181E+00	1.050E+00	-5.590E+01	2.531E+00	1.692E-01	7.478E+00
1.170E+00	1.060E+00	-5.704E+01	2.598E+00	1.720E-01	7.554E+00
1.159E+00	1.070E+00	-5.819E+01	2.667E+00	1.747E-01	7.630E+00
1.148E+00	1.080E+00	-5.935E+01	2.736E+00	1.775E-01	7.706E+00
1.138E+00	1.090E+00	-6.052E+01	2.807E+00	1.804E-01	7.782E+00
1.127E+00	1.100E+00	-6.170E+01	2.880E+00	1.833E-01	7.857E+00
1.117E+00	1.110E+00	-6.289E+01	2.953E+00	1.862E-01	7.933E+00
1.107E+00	1.120E+00	-6.410E+01	3.029E+00	1.891E-01	8.008E+00
1.097E+00	1.130E+00	-6.531E+01	3.105E+00	1.921E-01	8.084E+00
1.088E+00	1.140E+00	-6.653E+01	3.183E+00	1.951E-01	8.159E+00
1.078E+00	1.150E+00	-6.777E+01	3.262E+00	1.981E-01	8.235E+00
1.069E+00	1.160E+00	-6.902E+01	3.343E+00	2.011E-01	8.310E+00
1.060E+00	1.170E+00	-7.027E+01	3.425E+00	2.042E-01	8.385E+00
1.051E+00	1.180E+00	-7.154E+01	3.509E+00	2.074E-01	8.461E+00
1.042E+00	1.190E+00	-7.282E+01	3.594E+00	2.105E-01	8.536E+00
1.033E+00	1.200E+00	-7.411E+01	3.680E+00	2.137E-01	8.611E+00
1.025E+00	1.210E+00	-7.541E+01	3.768E+00	2.169E-01	8.686E+00
1.016E+00	1.220E+00	-7.672E+01	3.858E+00	2.202E-01	8.762E+00
1.008E+00	1.230E+00	-7.804E+01	3.949E+00	2.234E-01	8.837E+00
1.000E+00	1.240E+00	-7.937E+01	4.041E+00	2.267E-01	8.912E+00
9.920E-01	1.250E+00	-8.071E+01	4.135E+00	2.301E-01	8.987E+00

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.841E-01	1.260E+00	-8.206E+01	4.231E+00	2.334E-01	9.062E+00
9.777E-01	1.268E+00	-8.320E+01	4.311E+00	2.363E-01	9.124E+00
9.764E-01	1.270E+00	-8.343E+01	4.328E+00	2.368E-01	9.137E+00
9.700E-01	1.278E+00	-8.457E+01	4.410E+00	2.397E-01	9.199E+00
9.688E-01	1.280E+00	-8.480E+01	4.426E+00	2.403E-01	9.212E+00
9.624E-01	1.288E+00	-8.598E+01	4.511E+00	2.432E-01	9.276E+00
9.612E-01	1.290E+00	-8.619E+01	4.527E+00	2.437E-01	9.287E+00
9.547E-01	1.299E+00	-8.742E+01	4.616E+00	2.468E-01	9.353E+00
9.539E-01	1.300E+00	-8.758E+01	4.628E+00	2.472E-01	9.362E+00
9.471E-01	1.309E+00	-8.889E+01	4.725E+00	2.505E-01	9.432E+00
9.466E-01	1.310E+00	-8.899E+01	4.732E+00	2.507E-01	9.437E+00
9.394E-01	1.320E+00	-9.040E+01	4.837E+00	2.543E-01	9.511E+00
9.394E-01	1.320E+00	-9.040E+01	4.837E+00	2.543E-01	9.512E+00
9.337E-01	1.328E+00	-9.156E+01	4.923E+00	2.572E-01	9.572E+00
9.323E-01	1.330E+00	-9.183E+01	4.943E+00	2.578E-01	9.586E+00
9.260E-01	1.339E+00	-9.314E+01	5.042E+00	2.611E-01	9.654E+00
9.254E-01	1.340E+00	-9.327E+01	5.052E+00	2.614E-01	9.661E+00
9.203E-01	1.347E+00	-9.434E+01	5.133E+00	2.641E-01	9.717E+00
9.185E-01	1.350E+00	-9.472E+01	5.162E+00	2.651E-01	9.736E+00
9.126E-01	1.359E+00	-9.599E+01	5.259E+00	2.683E-01	9.801E+00
9.069E-01	1.367E+00	-9.725E+01	5.356E+00	2.715E-01	9.866E+00
8.992E-01	1.379E+00	-9.897E+01	5.489E+00	2.758E-01	9.952E+00
8.935E-01	1.388E+00	-1.003E+02	5.593E+00	2.791E-01	1.002E+01
8.858E-01	1.400E+00	-1.021E+02	5.734E+00	2.836E-01	1.011E+01
8.801E-01	1.409E+00	-1.035E+02	5.843E+00	2.871E-01	1.018E+01
8.744E-01	1.418E+00	-1.049E+02	5.955E+00	2.907E-01	1.025E+01
8.686E-01	1.427E+00	-1.063E+02	6.071E+00	2.943E-01	1.032E+01
8.671E-01	1.430E+00	-1.067E+02	6.101E+00	2.952E-01	1.033E+01
8.629E-01	1.437E+00	-1.078E+02	6.189E+00	2.980E-01	1.039E+01
8.611E-01	1.440E+00	-1.082E+02	6.226E+00	2.991E-01	1.041E+01
8.552E-01	1.450E+00	-1.098E+02	6.353E+00	3.030E-01	1.048E+01
8.552E-01	1.450E+00	-1.098E+02	6.353E+00	3.031E-01	1.048E+01
8.495E-01	1.460E+00	-1.113E+02	6.479E+00	3.069E-01	1.056E+01
8.493E-01	1.460E+00	-1.114E+02	6.482E+00	3.070E-01	1.056E+01
8.437E-01	1.469E+00	-1.129E+02	6.608E+00	3.109E-01	1.063E+01
8.435E-01	1.470E+00	-1.129E+02	6.613E+00	3.110E-01	1.063E+01
8.380E-01	1.480E+00	-1.145E+02	6.741E+00	3.149E-01	1.070E+01
8.378E-01	1.480E+00	-1.145E+02	6.745E+00	3.150E-01	1.071E+01
8.323E-01	1.490E+00	-1.161E+02	6.878E+00	3.190E-01	1.078E+01
8.322E-01	1.490E+00	-1.161E+02	6.879E+00	3.191E-01	1.078E+01
8.284E-01	1.497E+00	-1.172E+02	6.971E+00	3.218E-01	1.083E+01
8.267E-01	1.500E+00	-1.177E+02	7.015E+00	3.231E-01	1.086E+01
8.227E-01	1.507E+00	-1.189E+02	7.115E+00	3.261E-01	1.091E+01
8.212E-01	1.510E+00	-1.193E+02	7.153E+00	3.272E-01	1.093E+01
8.170E-01	1.518E+00	-1.206E+02	7.262E+00	3.305E-01	1.099E+01
8.158E-01	1.520E+00	-1.210E+02	7.293E+00	3.314E-01	1.100E+01
8.112E-01	1.528E+00	-1.224E+02	7.414E+00	3.349E-01	1.107E+01
8.105E-01	1.530E+00	-1.226E+02	7.434E+00	3.355E-01	1.108E+01
8.055E-01	1.539E+00	-1.242E+02	7.570E+00	3.395E-01	1.115E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
8.052E-01	1.540E+00	-1.243E+02	7.578E+00	3.397E-01	1.115E+01
8.017E-01	1.547E+00	-1.254E+02	7.676E+00	3.426E-01	1.120E+01
8.000E-01	1.550E+00	-1.259E+02	7.723E+00	3.439E-01	1.123E+01
7.959E-01	1.558E+00	-1.273E+02	7.839E+00	3.473E-01	1.129E+01
7.949E-01	1.560E+00	-1.276E+02	7.870E+00	3.482E-01	1.130E+01
7.902E-01	1.569E+00	-1.292E+02	8.008E+00	3.522E-01	1.137E+01
7.898E-01	1.570E+00	-1.293E+02	8.019E+00	3.525E-01	1.138E+01
7.863E-01	1.577E+00	-1.304E+02	8.123E+00	3.554E-01	1.143E+01
7.848E-01	1.580E+00	-1.310E+02	8.170E+00	3.568E-01	1.145E+01
7.806E-01	1.588E+00	-1.324E+02	8.300E+00	3.605E-01	1.151E+01
7.799E-01	1.590E+00	-1.327E+02	8.322E+00	3.611E-01	1.152E+01
7.768E-01	1.596E+00	-1.338E+02	8.420E+00	3.639E-01	1.157E+01
7.750E-01	1.600E+00	-1.344E+02	8.477E+00	3.655E-01	1.160E+01
7.710E-01	1.608E+00	-1.358E+02	8.606E+00	3.691E-01	1.166E+01
7.702E-01	1.610E+00	-1.361E+02	8.634E+00	3.698E-01	1.167E+01
7.672E-01	1.616E+00	-1.372E+02	8.733E+00	3.726E-01	1.172E+01
7.654E-01	1.620E+00	-1.379E+02	8.793E+00	3.743E-01	1.175E+01
7.615E-01	1.628E+00	-1.393E+02	8.928E+00	3.780E-01	1.181E+01
7.607E-01	1.630E+00	-1.396E+02	8.953E+00	3.787E-01	1.182E+01
7.576E-01	1.636E+00	-1.408E+02	9.062E+00	3.817E-01	1.187E+01
7.561E-01	1.640E+00	-1.413E+02	9.116E+00	3.832E-01	1.190E+01
7.519E-01	1.649E+00	-1.430E+02	9.267E+00	3.873E-01	1.196E+01
7.515E-01	1.650E+00	-1.431E+02	9.281E+00	3.877E-01	1.197E+01
7.481E-01	1.657E+00	-1.445E+02	9.407E+00	3.911E-01	1.203E+01
7.470E-01	1.660E+00	-1.449E+02	9.448E+00	3.922E-01	1.204E+01
7.443E-01	1.666E+00	-1.460E+02	9.550E+00	3.950E-01	1.209E+01
7.425E-01	1.670E+00	-1.467E+02	9.616E+00	3.968E-01	1.212E+01
7.385E-01	1.679E+00	-1.483E+02	9.771E+00	4.009E-01	1.219E+01
7.381E-01	1.680E+00	-1.485E+02	9.787E+00	4.014E-01	1.219E+01
7.347E-01	1.688E+00	-1.499E+02	9.922E+00	4.050E-01	1.225E+01
7.337E-01	1.690E+00	-1.503E+02	9.960E+00	4.060E-01	1.227E+01
7.309E-01	1.696E+00	-1.515E+02	1.008E+01	4.091E-01	1.232E+01
7.294E-01	1.700E+00	-1.521E+02	1.013E+01	4.106E-01	1.234E+01
7.270E-01	1.705E+00	-1.531E+02	1.023E+01	4.132E-01	1.238E+01
7.252E-01	1.710E+00	-1.539E+02	1.031E+01	4.153E-01	1.241E+01
7.213E-01	1.719E+00	-1.556E+02	1.047E+01	4.196E-01	1.248E+01
7.209E-01	1.720E+00	-1.558E+02	1.049E+01	4.200E-01	1.249E+01
7.175E-01	1.728E+00	-1.573E+02	1.064E+01	4.239E-01	1.255E+01
7.168E-01	1.730E+00	-1.576E+02	1.067E+01	4.247E-01	1.256E+01
7.136E-01	1.737E+00	-1.591E+02	1.081E+01	4.283E-01	1.262E+01
7.126E-01	1.740E+00	-1.595E+02	1.085E+01	4.295E-01	1.264E+01
7.098E-01	1.747E+00	-1.608E+02	1.098E+01	4.328E-01	1.269E+01
7.086E-01	1.750E+00	-1.614E+02	1.104E+01	4.343E-01	1.271E+01
7.060E-01	1.756E+00	-1.626E+02	1.116E+01	4.374E-01	1.276E+01
7.046E-01	1.760E+00	-1.633E+02	1.123E+01	4.391E-01	1.279E+01
7.022E-01	1.766E+00	-1.644E+02	1.134E+01	4.420E-01	1.283E+01
7.006E-01	1.770E+00	-1.652E+02	1.142E+01	4.439E-01	1.286E+01
6.983E-01	1.775E+00	-1.662E+02	1.153E+01	4.467E-01	1.290E+01
6.966E-01	1.780E+00	-1.671E+02	1.161E+01	4.488E-01	1.293E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.945E-01	1.785E+00	-1.681E+02	1.171E+01	4.515E-01	1.297E+01
6.927E-01	1.790E+00	-1.690E+02	1.180E+01	4.537E-01	1.301E+01
6.907E-01	1.795E+00	-1.700E+02	1.191E+01	4.563E-01	1.305E+01
6.889E-01	1.800E+00	-1.709E+02	1.200E+01	4.586E-01	1.308E+01
6.869E-01	1.805E+00	-1.719E+02	1.210E+01	4.613E-01	1.312E+01
6.851E-01	1.810E+00	-1.728E+02	1.220E+01	4.636E-01	1.316E+01
6.830E-01	1.815E+00	-1.739E+02	1.231E+01	4.663E-01	1.320E+01
6.813E-01	1.820E+00	-1.748E+02	1.240E+01	4.686E-01	1.323E+01
6.792E-01	1.825E+00	-1.759E+02	1.251E+01	4.714E-01	1.327E+01
6.776E-01	1.830E+00	-1.767E+02	1.260E+01	4.736E-01	1.330E+01
6.754E-01	1.836E+00	-1.779E+02	1.272E+01	4.766E-01	1.335E+01
6.739E-01	1.840E+00	-1.787E+02	1.280E+01	4.786E-01	1.338E+01
6.716E-01	1.846E+00	-1.800E+02	1.294E+01	4.819E-01	1.342E+01
6.703E-01	1.850E+00	-1.807E+02	1.301E+01	4.837E-01	1.345E+01
6.677E-01	1.857E+00	-1.821E+02	1.316E+01	4.873E-01	1.350E+01
6.667E-01	1.860E+00	-1.827E+02	1.322E+01	4.888E-01	1.352E+01
6.639E-01	1.868E+00	-1.842E+02	1.339E+01	4.928E-01	1.358E+01
6.631E-01	1.870E+00	-1.847E+02	1.343E+01	4.939E-01	1.360E+01
6.601E-01	1.878E+00	-1.864E+02	1.362E+01	4.983E-01	1.366E+01
6.596E-01	1.880E+00	-1.867E+02	1.365E+01	4.991E-01	1.367E+01
6.562E-01	1.889E+00	-1.886E+02	1.385E+01	5.040E-01	1.374E+01
6.561E-01	1.890E+00	-1.887E+02	1.386E+01	5.042E-01	1.375E+01
6.543E-01	1.895E+00	-1.897E+02	1.397E+01	5.069E-01	1.378E+01
6.526E-01	1.900E+00	-1.907E+02	1.408E+01	5.095E-01	1.382E+01
6.505E-01	1.906E+00	-1.920E+02	1.422E+01	5.127E-01	1.387E+01
6.492E-01	1.910E+00	-1.928E+02	1.430E+01	5.147E-01	1.389E+01
6.467E-01	1.917E+00	-1.943E+02	1.447E+01	5.186E-01	1.395E+01
6.458E-01	1.920E+00	-1.948E+02	1.452E+01	5.200E-01	1.397E+01
6.429E-01	1.929E+00	-1.966E+02	1.473E+01	5.247E-01	1.403E+01
6.425E-01	1.930E+00	-1.969E+02	1.475E+01	5.252E-01	1.404E+01
6.409E-01	1.934E+00	-1.979E+02	1.486E+01	5.277E-01	1.408E+01
6.392E-01	1.940E+00	-1.990E+02	1.498E+01	5.306E-01	1.412E+01
6.371E-01	1.946E+00	-2.002E+02	1.512E+01	5.339E-01	1.416E+01
6.359E-01	1.950E+00	-2.010E+02	1.521E+01	5.359E-01	1.419E+01
6.333E-01	1.958E+00	-2.027E+02	1.539E+01	5.402E-01	1.425E+01
6.327E-01	1.960E+00	-2.031E+02	1.544E+01	5.413E-01	1.426E+01
6.295E-01	1.970E+00	-2.052E+02	1.567E+01	5.467E-01	1.434E+01
6.294E-01	1.970E+00	-2.052E+02	1.567E+01	5.467E-01	1.434E+01
6.275E-01	1.976E+00	-2.065E+02	1.582E+01	5.499E-01	1.438E+01
6.263E-01	1.980E+00	-2.073E+02	1.591E+01	5.521E-01	1.441E+01
6.237E-01	1.988E+00	-2.091E+02	1.611E+01	5.565E-01	1.447E+01
6.231E-01	1.990E+00	-2.095E+02	1.615E+01	5.576E-01	1.448E+01
6.218E-01	1.994E+00	-2.104E+02	1.625E+01	5.599E-01	1.452E+01
6.200E-01	2.000E+00	-2.116E+02	1.639E+01	5.631E-01	1.456E+01
6.180E-01	2.006E+00	-2.130E+02	1.655E+01	5.667E-01	1.461E+01
6.142E-01	2.019E+00	-2.157E+02	1.686E+01	5.736E-01	1.470E+01
6.122E-01	2.025E+00	-2.171E+02	1.702E+01	5.771E-01	1.475E+01
6.084E-01	2.038E+00	-2.198E+02	1.734E+01	5.842E-01	1.484E+01
6.065E-01	2.044E+00	-2.212E+02	1.750E+01	5.878E-01	1.489E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.027E-01	2.057E+00	-2.241E+02	1.783E+01	5.951E-01	1.498E+01
6.008E-01	2.064E+00	-2.255E+02	1.800E+01	5.988E-01	1.503E+01
5.969E-01	2.077E+00	-2.285E+02	1.835E+01	6.064E-01	1.513E+01
5.950E-01	2.084E+00	-2.299E+02	1.852E+01	6.102E-01	1.518E+01
5.912E-01	2.097E+00	-2.330E+02	1.888E+01	6.180E-01	1.528E+01
5.893E-01	2.104E+00	-2.345E+02	1.906E+01	6.219E-01	1.533E+01
5.855E-01	2.118E+00	-2.376E+02	1.943E+01	6.299E-01	1.543E+01
5.835E-01	2.125E+00	-2.392E+02	1.962E+01	6.339E-01	1.548E+01
5.797E-01	2.139E+00	-2.424E+02	2.001E+01	6.422E-01	1.558E+01
5.778E-01	2.146E+00	-2.440E+02	2.021E+01	6.463E-01	1.563E+01
5.759E-01	2.153E+00	-2.456E+02	2.041E+01	6.505E-01	1.569E+01
5.721E-01	2.167E+00	-2.490E+02	2.082E+01	6.591E-01	1.579E+01
5.702E-01	2.175E+00	-2.506E+02	2.102E+01	6.634E-01	1.585E+01
5.663E-01	2.189E+00	-2.540E+02	2.145E+01	6.723E-01	1.595E+01
5.644E-01	2.197E+00	-2.558E+02	2.167E+01	6.767E-01	1.601E+01
5.625E-01	2.204E+00	-2.576E+02	2.189E+01	6.813E-01	1.606E+01
5.587E-01	2.219E+00	-2.611E+02	2.233E+01	6.905E-01	1.617E+01
5.568E-01	2.227E+00	-2.629E+02	2.256E+01	6.951E-01	1.623E+01
5.548E-01	2.235E+00	-2.647E+02	2.279E+01	6.998E-01	1.629E+01
5.529E-01	2.242E+00	-2.666E+02	2.303E+01	7.046E-01	1.634E+01
5.491E-01	2.258E+00	-2.704E+02	2.351E+01	7.143E-01	1.646E+01
5.472E-01	2.266E+00	-2.723E+02	2.376E+01	7.192E-01	1.652E+01
5.453E-01	2.274E+00	-2.742E+02	2.400E+01	7.241E-01	1.658E+01
5.434E-01	2.282E+00	-2.761E+02	2.426E+01	7.292E-01	1.663E+01
5.395E-01	2.298E+00	-2.801E+02	2.477E+01	7.393E-01	1.675E+01
5.376E-01	2.306E+00	-2.821E+02	2.503E+01	7.445E-01	1.681E+01
5.357E-01	2.314E+00	-2.841E+02	2.530E+01	7.498E-01	1.687E+01
5.338E-01	2.323E+00	-2.862E+02	2.557E+01	7.550E-01	1.693E+01
5.300E-01	2.339E+00	-2.904E+02	2.612E+01	7.658E-01	1.706E+01
5.281E-01	2.348E+00	-2.925E+02	2.641E+01	7.713E-01	1.712E+01
5.261E-01	2.356E+00	-2.946E+02	2.669E+01	7.768E-01	1.718E+01
5.242E-01	2.365E+00	-2.968E+02	2.698E+01	7.824E-01	1.725E+01
5.223E-01	2.374E+00	-2.989E+02	2.728E+01	7.880E-01	1.731E+01
5.204E-01	2.382E+00	-3.012E+02	2.758E+01	7.937E-01	1.737E+01
5.185E-01	2.391E+00	-3.034E+02	2.788E+01	7.995E-01	1.744E+01
5.147E-01	2.409E+00	-3.079E+02	2.850E+01	8.112E-01	1.757E+01
5.128E-01	2.418E+00	-3.103E+02	2.882E+01	8.172E-01	1.763E+01
5.108E-01	2.427E+00	-3.126E+02	2.914E+01	8.232E-01	1.770E+01
5.089E-01	2.436E+00	-3.149E+02	2.947E+01	8.293E-01	1.777E+01
5.070E-01	2.445E+00	-3.174E+02	2.980E+01	8.355E-01	1.783E+01
5.051E-01	2.455E+00	-3.198E+02	3.014E+01	8.417E-01	1.790E+01
5.032E-01	2.464E+00	-3.222E+02	3.048E+01	8.480E-01	1.797E+01
5.013E-01	2.473E+00	-3.247E+02	3.083E+01	8.544E-01	1.804E+01
4.994E-01	2.483E+00	-3.272E+02	3.118E+01	8.609E-01	1.811E+01
4.974E-01	2.492E+00	-3.297E+02	3.154E+01	8.674E-01	1.818E+01
4.955E-01	2.502E+00	-3.323E+02	3.190E+01	8.740E-01	1.825E+01
4.936E-01	2.512E+00	-3.348E+02	3.227E+01	8.807E-01	1.832E+01
4.917E-01	2.522E+00	-3.374E+02	3.264E+01	8.875E-01	1.839E+01
4.898E-01	2.531E+00	-3.401E+02	3.302E+01	8.943E-01	1.846E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.879E-01	2.541E+00	-3.428E+02	3.341E+01	9.012E-01	1.854E+01
4.860E-01	2.551E+00	-3.455E+02	3.380E+01	9.082E-01	1.861E+01
4.841E-01	2.561E+00	-3.482E+02	3.420E+01	9.153E-01	1.868E+01
4.821E-01	2.572E+00	-3.510E+02	3.461E+01	9.225E-01	1.876E+01
4.802E-01	2.582E+00	-3.538E+02	3.502E+01	9.297E-01	1.883E+01
4.783E-01	2.592E+00	-3.566E+02	3.544E+01	9.370E-01	1.891E+01
4.764E-01	2.603E+00	-3.595E+02	3.586E+01	9.445E-01	1.898E+01
4.745E-01	2.613E+00	-3.624E+02	3.629E+01	9.520E-01	1.906E+01
4.726E-01	2.624E+00	-3.653E+02	3.673E+01	9.596E-01	1.914E+01
4.707E-01	2.634E+00	-3.683E+02	3.718E+01	9.673E-01	1.922E+01
4.687E-01	2.645E+00	-3.713E+02	3.763E+01	9.751E-01	1.930E+01
4.668E-01	2.656E+00	-3.744E+02	3.809E+01	9.830E-01	1.937E+01
4.649E-01	2.667E+00	-3.775E+02	3.856E+01	9.910E-01	1.945E+01
4.630E-01	2.678E+00	-3.806E+02	3.903E+01	9.991E-01	1.954E+01
4.611E-01	2.689E+00	-3.838E+02	3.951E+01	1.007E+00	1.962E+01
4.592E-01	2.700E+00	-3.870E+02	4.001E+01	1.016E+00	1.970E+01
4.573E-01	2.711E+00	-3.902E+02	4.051E+01	1.024E+00	1.978E+01
4.554E-01	2.723E+00	-3.935E+02	4.102E+01	1.032E+00	1.986E+01
4.534E-01	2.734E+00	-3.968E+02	4.153E+01	1.041E+00	1.995E+01
4.515E-01	2.746E+00	-4.002E+02	4.206E+01	1.050E+00	2.003E+01
4.496E-01	2.758E+00	-4.036E+02	4.259E+01	1.059E+00	2.012E+01
4.477E-01	2.769E+00	-4.071E+02	4.314E+01	1.068E+00	2.020E+01
4.458E-01	2.781E+00	-4.105E+02	4.368E+01	1.077E+00	2.029E+01
4.439E-01	2.793E+00	-4.141E+02	4.425E+01	1.086E+00	2.038E+01
4.420E-01	2.805E+00	-4.177E+02	4.482E+01	1.095E+00	2.047E+01
4.401E-01	2.817E+00	-4.213E+02	4.540E+01	1.104E+00	2.056E+01
4.381E-01	2.830E+00	-4.250E+02	4.599E+01	1.114E+00	2.065E+01
4.362E-01	2.842E+00	-4.287E+02	4.660E+01	1.124E+00	2.074E+01
4.343E-01	2.855E+00	-4.325E+02	4.721E+01	1.133E+00	2.083E+01
4.324E-01	2.867E+00	-4.363E+02	4.783E+01	1.143E+00	2.092E+01
4.305E-01	2.880E+00	-4.402E+02	4.847E+01	1.153E+00	2.101E+01
4.286E-01	2.893E+00	-4.441E+02	4.911E+01	1.164E+00	2.111E+01
4.267E-01	2.906E+00	-4.481E+02	4.977E+01	1.174E+00	2.120E+01
4.247E-01	2.919E+00	-4.521E+02	5.044E+01	1.184E+00	2.130E+01
4.228E-01	2.932E+00	-4.562E+02	5.112E+01	1.195E+00	2.139E+01
4.209E-01	2.946E+00	-4.603E+02	5.181E+01	1.206E+00	2.149E+01
4.190E-01	2.959E+00	-4.645E+02	5.252E+01	1.216E+00	2.159E+01
4.171E-01	2.973E+00	-4.688E+02	5.324E+01	1.228E+00	2.169E+01
4.152E-01	2.986E+00	-4.731E+02	5.397E+01	1.239E+00	2.179E+01
4.133E-01	3.000E+00	-4.774E+02	5.472E+01	1.250E+00	2.189E+01
4.114E-01	3.014E+00	-4.819E+02	5.548E+01	1.262E+00	2.199E+01
4.094E-01	3.028E+00	-4.863E+02	5.625E+01	1.273E+00	2.209E+01
4.075E-01	3.042E+00	-4.909E+02	5.703E+01	1.285E+00	2.219E+01
4.056E-01	3.057E+00	-4.955E+02	5.784E+01	1.297E+00	2.230E+01
4.037E-01	3.071E+00	-5.002E+02	5.866E+01	1.309E+00	2.240E+01
4.018E-01	3.086E+00	-5.050E+02	5.949E+01	1.321E+00	2.251E+01
3.999E-01	3.101E+00	-5.097E+02	6.034E+01	1.334E+00	2.262E+01
3.980E-01	3.116E+00	-5.147E+02	6.121E+01	1.347E+00	2.273E+01
3.960E-01	3.131E+00	-5.196E+02	6.208E+01	1.359E+00	2.284E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.941E-01	3.146E+00	-5.246E+02	6.298E+01	1.372E+00	2.295E+01
3.922E-01	3.161E+00	-5.297E+02	6.390E+01	1.386E+00	2.306E+01
3.903E-01	3.177E+00	-5.349E+02	6.483E+01	1.399E+00	2.317E+01
3.884E-01	3.192E+00	-5.401E+02	6.578E+01	1.413E+00	2.328E+01
3.865E-01	3.208E+00	-5.454E+02	6.675E+01	1.427E+00	2.340E+01
3.846E-01	3.224E+00	-5.508E+02	6.775E+01	1.441E+00	2.351E+01
3.827E-01	3.240E+00	-5.563E+02	6.876E+01	1.455E+00	2.363E+01
3.807E-01	3.256E+00	-5.619E+02	6.979E+01	1.469E+00	2.375E+01
3.788E-01	3.273E+00	-5.675E+02	7.084E+01	1.484E+00	2.387E+01
3.769E-01	3.289E+00	-5.732E+02	7.191E+01	1.499E+00	2.399E+01
3.750E-01	3.306E+00	-5.790E+02	7.300E+01	1.514E+00	2.411E+01
3.731E-01	3.323E+00	-5.849E+02	7.412E+01	1.529E+00	2.423E+01
3.712E-01	3.340E+00	-5.909E+02	7.526E+01	1.545E+00	2.436E+01
3.693E-01	3.358E+00	-5.970E+02	7.642E+01	1.561E+00	2.448E+01
3.673E-01	3.375E+00	-6.032E+02	7.761E+01	1.577E+00	2.461E+01
3.654E-01	3.393E+00	-6.094E+02	7.882E+01	1.593E+00	2.474E+01
3.635E-01	3.411E+00	-6.158E+02	8.006E+01	1.610E+00	2.487E+01
3.616E-01	3.429E+00	-6.223E+02	8.131E+01	1.626E+00	2.500E+01
3.597E-01	3.447E+00	-6.288E+02	8.260E+01	1.644E+00	2.513E+01
3.578E-01	3.465E+00	-6.355E+02	8.392E+01	1.661E+00	2.526E+01
3.559E-01	3.484E+00	-6.423E+02	8.526E+01	1.679E+00	2.540E+01
3.540E-01	3.503E+00	-6.492E+02	8.664E+01	1.697E+00	2.554E+01
3.520E-01	3.522E+00	-6.562E+02	8.804E+01	1.715E+00	2.567E+01
3.501E-01	3.541E+00	-6.633E+02	8.947E+01	1.733E+00	2.581E+01
3.482E-01	3.561E+00	-6.705E+02	9.094E+01	1.752E+00	2.595E+01
3.463E-01	3.580E+00	-6.778E+02	9.243E+01	1.771E+00	2.610E+01
3.444E-01	3.600E+00	-6.853E+02	9.396E+01	1.791E+00	2.624E+01
3.425E-01	3.620E+00	-6.928E+02	9.553E+01	1.810E+00	2.638E+01
3.406E-01	3.641E+00	-7.005E+02	9.712E+01	1.830E+00	2.653E+01
3.386E-01	3.661E+00	-7.083E+02	9.875E+01	1.851E+00	2.668E+01
3.367E-01	3.682E+00	-7.163E+02	1.004E+02	1.872E+00	2.683E+01
3.348E-01	3.703E+00	-7.244E+02	1.021E+02	1.893E+00	2.698E+01
3.329E-01	3.724E+00	-7.326E+02	1.039E+02	1.914E+00	2.714E+01
3.310E-01	3.746E+00	-7.410E+02	1.057E+02	1.936E+00	2.729E+01
3.291E-01	3.768E+00	-7.495E+02	1.075E+02	1.958E+00	2.745E+01
3.272E-01	3.790E+00	-7.582E+02	1.094E+02	1.981E+00	2.761E+01
3.253E-01	3.812E+00	-7.670E+02	1.113E+02	2.004E+00	2.777E+01
3.233E-01	3.834E+00	-7.760E+02	1.132E+02	2.027E+00	2.793E+01
3.214E-01	3.857E+00	-7.851E+02	1.152E+02	2.051E+00	2.809E+01
3.195E-01	3.880E+00	-7.943E+02	1.173E+02	2.075E+00	2.826E+01
3.176E-01	3.904E+00	-8.038E+02	1.194E+02	2.100E+00	2.843E+01
3.157E-01	3.927E+00	-8.134E+02	1.215E+02	2.125E+00	2.860E+01
3.138E-01	3.951E+00	-8.231E+02	1.237E+02	2.151E+00	2.877E+01
3.119E-01	3.976E+00	-8.331E+02	1.260E+02	2.177E+00	2.895E+01
3.100E-01	4.000E+00	-8.432E+02	1.283E+02	2.203E+00	2.912E+01
3.080E-01	4.025E+00	-8.536E+02	1.307E+02	2.230E+00	2.930E+01
3.061E-01	4.050E+00	-8.640E+02	1.331E+02	2.258E+00	2.948E+01
3.042E-01	4.076E+00	-8.747E+02	1.356E+02	2.286E+00	2.966E+01
3.023E-01	4.101E+00	-8.857E+02	1.382E+02	2.314E+00	2.985E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.004E-01	4.128E+00	-8.967E+02	1.408E+02	2.343E+00	3.004E+01
2.985E-01	4.154E+00	-9.080E+02	1.434E+02	2.373E+00	3.023E+01
2.966E-01	4.181E+00	-9.195E+02	1.462E+02	2.403E+00	3.042E+01
2.946E-01	4.208E+00	-9.313E+02	1.490E+02	2.434E+00	3.061E+01
2.927E-01	4.235E+00	-9.432E+02	1.519E+02	2.465E+00	3.081E+01
2.908E-01	4.263E+00	-9.554E+02	1.549E+02	2.497E+00	3.101E+01
2.889E-01	4.292E+00	-9.679E+02	1.579E+02	2.530E+00	3.121E+01
2.870E-01	4.320E+00	-9.805E+02	1.610E+02	2.563E+00	3.142E+01
2.851E-01	4.349E+00	-9.934E+02	1.642E+02	2.597E+00	3.163E+01
2.832E-01	4.379E+00	-1.007E+03	1.675E+02	2.631E+00	3.184E+01
2.813E-01	4.408E+00	-1.020E+03	1.709E+02	2.666E+00	3.205E+01
2.793E-01	4.439E+00	-1.034E+03	1.744E+02	2.702E+00	3.226E+01
2.774E-01	4.469E+00	-1.048E+03	1.779E+02	2.739E+00	3.248E+01
2.755E-01	4.500E+00	-1.062E+03	1.816E+02	2.776E+00	3.270E+01
2.736E-01	4.532E+00	-1.076E+03	1.854E+02	2.815E+00	3.293E+01
2.717E-01	4.564E+00	-1.091E+03	1.892E+02	2.854E+00	3.316E+01
2.698E-01	4.596E+00	-1.106E+03	1.932E+02	2.893E+00	3.339E+01
2.679E-01	4.629E+00	-1.122E+03	1.973E+02	2.934E+00	3.362E+01
2.659E-01	4.662E+00	-1.138E+03	2.015E+02	2.975E+00	3.386E+01
2.640E-01	4.696E+00	-1.154E+03	2.058E+02	3.018E+00	3.410E+01
2.621E-01	4.730E+00	-1.170E+03	2.102E+02	3.061E+00	3.434E+01
2.602E-01	4.765E+00	-1.187E+03	2.148E+02	3.105E+00	3.459E+01
2.583E-01	4.800E+00	-1.204E+03	2.195E+02	3.150E+00	3.484E+01
2.564E-01	4.836E+00	-1.221E+03	2.244E+02	3.197E+00	3.510E+01
2.545E-01	4.872E+00	-1.239E+03	2.293E+02	3.244E+00	3.535E+01
2.526E-01	4.909E+00	-1.258E+03	2.345E+02	3.292E+00	3.562E+01
2.506E-01	4.947E+00	-1.276E+03	2.398E+02	3.341E+00	3.588E+01
2.487E-01	4.985E+00	-1.295E+03	2.452E+02	3.392E+00	3.615E+01
2.468E-01	5.023E+00	-1.315E+03	2.508E+02	3.443E+00	3.643E+01
2.449E-01	5.063E+00	-1.335E+03	2.566E+02	3.496E+00	3.670E+01
2.430E-01	5.103E+00	-1.355E+03	2.626E+02	3.550E+00	3.698E+01
2.411E-01	5.143E+00	-1.376E+03	2.687E+02	3.605E+00	3.727E+01
2.392E-01	5.184E+00	-1.397E+03	2.751E+02	3.662E+00	3.756E+01
2.372E-01	5.226E+00	-1.419E+03	2.816E+02	3.719E+00	3.786E+01
2.353E-01	5.269E+00	-1.442E+03	2.883E+02	3.779E+00	3.816E+01
2.334E-01	5.312E+00	-1.465E+03	2.953E+02	3.839E+00	3.846E+01
2.315E-01	5.356E+00	-1.488E+03	3.025E+02	3.901E+00	3.877E+01
2.296E-01	5.400E+00	-1.512E+03	3.099E+02	3.965E+00	3.908E+01
2.277E-01	5.446E+00	-1.536E+03	3.176E+02	4.030E+00	3.940E+01
2.258E-01	5.492E+00	-1.562E+03	3.255E+02	4.097E+00	3.973E+01
2.239E-01	5.539E+00	-1.587E+03	3.337E+02	4.165E+00	4.006E+01
2.219E-01	5.586E+00	-1.614E+03	3.421E+02	4.235E+00	4.039E+01
2.200E-01	5.635E+00	-1.641E+03	3.509E+02	4.307E+00	4.073E+01
2.181E-01	5.684E+00	-1.668E+03	3.599E+02	4.381E+00	4.108E+01
2.162E-01	5.735E+00	-1.697E+03	3.693E+02	4.456E+00	4.143E+01
2.143E-01	5.786E+00	-1.726E+03	3.789E+02	4.534E+00	4.179E+01
2.124E-01	5.838E+00	-1.756E+03	3.889E+02	4.613E+00	4.215E+01
2.105E-01	5.891E+00	-1.786E+03	3.993E+02	4.695E+00	4.252E+01
2.085E-01	5.945E+00	-1.818E+03	4.100E+02	4.779E+00	4.290E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.066E-01	6.000E+00	-1.850E+03	4.211E+02	4.865E+00	4.329E+01
2.047E-01	6.056E+00	-1.883E+03	4.327E+02	4.953E+00	4.368E+01
2.028E-01	6.114E+00	-1.917E+03	4.446E+02	5.044E+00	4.407E+01
2.009E-01	6.172E+00	-1.952E+03	4.570E+02	5.137E+00	4.448E+01
1.990E-01	6.231E+00	-1.988E+03	4.698E+02	5.233E+00	4.489E+01
1.971E-01	6.292E+00	-2.024E+03	4.831E+02	5.332E+00	4.531E+01
1.952E-01	6.353E+00	-2.062E+03	4.970E+02	5.433E+00	4.573E+01
1.932E-01	6.416E+00	-2.101E+03	5.113E+02	5.537E+00	4.617E+01
1.913E-01	6.480E+00	-2.141E+03	5.262E+02	5.645E+00	4.661E+01
1.894E-01	6.546E+00	-2.182E+03	5.417E+02	5.755E+00	4.706E+01
1.875E-01	6.612E+00	-2.224E+03	5.578E+02	5.869E+00	4.752E+01
1.856E-01	6.681E+00	-2.267E+03	5.745E+02	5.985E+00	4.799E+01
1.837E-01	6.750E+00	-2.312E+03	5.919E+02	6.106E+00	4.847E+01
1.818E-01	6.821E+00	-2.358E+03	6.100E+02	6.230E+00	4.896E+01
1.798E-01	6.894E+00	-2.405E+03	6.288E+02	6.358E+00	4.945E+01
1.779E-01	6.968E+00	-2.454E+03	6.484E+02	6.490E+00	4.996E+01
1.760E-01	7.044E+00	-2.504E+03	6.689E+02	6.625E+00	5.048E+01
1.741E-01	7.121E+00	-2.556E+03	6.901E+02	6.765E+00	5.101E+01
1.722E-01	7.200E+00	-2.609E+03	7.123E+02	6.910E+00	5.154E+01
1.703E-01	7.281E+00	-2.664E+03	7.354E+02	7.059E+00	5.209E+01
1.684E-01	7.364E+00	-2.720E+03	7.596E+02	7.213E+00	5.265E+01
1.665E-01	7.449E+00	-2.779E+03	7.848E+02	7.372E+00	5.323E+01
1.645E-01	7.535E+00	-2.839E+03	8.111E+02	7.536E+00	5.381E+01
1.626E-01	7.624E+00	-2.901E+03	8.385E+02	7.706E+00	5.441E+01
1.607E-01	7.715E+00	-2.965E+03	8.672E+02	7.881E+00	5.502E+01
1.588E-01	7.808E+00	-3.031E+03	8.973E+02	8.062E+00	5.565E+01
1.569E-01	7.903E+00	-3.100E+03	9.286E+02	8.250E+00	5.628E+01
1.550E-01	8.001E+00	-3.170E+03	9.615E+02	8.444E+00	5.694E+01
1.531E-01	8.100E+00	-3.243E+03	9.959E+02	8.645E+00	5.760E+01
1.512E-01	8.203E+00	-3.319E+03	1.032E+03	8.853E+00	5.829E+01
1.492E-01	8.308E+00	-3.397E+03	1.070E+03	9.068E+00	5.898E+01
1.473E-01	8.416E+00	-3.478E+03	1.109E+03	9.291E+00	5.970E+01
1.454E-01	8.527E+00	-3.561E+03	1.151E+03	9.523E+00	6.043E+01
1.435E-01	8.641E+00	-3.647E+03	1.194E+03	9.762E+00	6.118E+01
1.416E-01	8.757E+00	-3.737E+03	1.240E+03	1.001E+01	6.195E+01
1.397E-01	8.877E+00	-3.830E+03	1.288E+03	1.027E+01	6.273E+01
1.378E-01	9.001E+00	-3.926E+03	1.339E+03	1.054E+01	6.354E+01
1.358E-01	9.127E+00	-4.025E+03	1.392E+03	1.082E+01	6.436E+01
1.339E-01	9.257E+00	-4.129E+03	1.449E+03	1.111E+01	6.521E+01
1.320E-01	9.392E+00	-4.236E+03	1.508E+03	1.141E+01	6.607E+01
1.301E-01	9.530E+00	-4.347E+03	1.570E+03	1.172E+01	6.696E+01
1.282E-01	9.672E+00	-4.462E+03	1.635E+03	1.205E+01	6.788E+01
1.263E-01	9.819E+00	-4.582E+03	1.705E+03	1.239E+01	6.881E+01
1.244E-01	9.970E+00	-4.706E+03	1.778E+03	1.274E+01	6.978E+01
1.225E-01	1.013E+01	-4.836E+03	1.855E+03	1.311E+01	7.077E+01
1.205E-01	1.029E+01	-4.970E+03	1.937E+03	1.349E+01	7.178E+01
1.186E-01	1.045E+01	-5.110E+03	2.024E+03	1.390E+01	7.282E+01
1.167E-01	1.062E+01	-5.256E+03	2.115E+03	1.431E+01	7.390E+01
1.148E-01	1.080E+01	-5.407E+03	2.213E+03	1.475E+01	7.500E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.129E-01	1.098E+01	-5.565E+03	2.316E+03	1.521E+01	7.613E+01
1.110E-01	1.117E+01	-5.729E+03	2.425E+03	1.569E+01	7.730E+01
1.091E-01	1.137E+01	-5.900E+03	2.541E+03	1.619E+01	7.850E+01
1.071E-01	1.157E+01	-6.079E+03	2.665E+03	1.671E+01	7.974E+01
1.052E-01	1.178E+01	-6.265E+03	2.796E+03	1.726E+01	8.101E+01
1.033E-01	1.200E+01	-6.459E+03	2.936E+03	1.784E+01	8.232E+01
1.014E-01	1.223E+01	-6.662E+03	3.086E+03	1.844E+01	8.368E+01
9.949E-02	1.246E+01	-6.873E+03	3.245E+03	1.907E+01	8.507E+01
9.758E-02	1.271E+01	-7.095E+03	3.415E+03	1.974E+01	8.651E+01
9.566E-02	1.296E+01	-7.326E+03	3.597E+03	2.044E+01	8.800E+01
9.375E-02	1.323E+01	-7.567E+03	3.791E+03	2.117E+01	8.953E+01
9.184E-02	1.350E+01	-7.820E+03	3.999E+03	2.195E+01	9.111E+01
8.992E-02	1.379E+01	-8.084E+03	4.222E+03	2.276E+01	9.275E+01
8.801E-02	1.409E+01	-8.361E+03	4.462E+03	2.362E+01	9.444E+01
8.610E-02	1.440E+01	-8.651E+03	4.719E+03	2.453E+01	9.619E+01
8.418E-02	1.473E+01	-8.954E+03	4.995E+03	2.549E+01	9.800E+01
8.227E-02	1.507E+01	-9.272E+03	5.293E+03	2.650E+01	9.987E+01
8.036E-02	1.543E+01	-9.605E+03	5.614E+03	2.757E+01	1.018E+02
7.844E-02	1.581E+01	-9.955E+03	5.960E+03	2.870E+01	1.038E+02
7.653E-02	1.620E+01	-1.032E+04	6.333E+03	2.990E+01	1.059E+02
7.462E-02	1.662E+01	-1.071E+04	6.737E+03	3.117E+01	1.081E+02
7.270E-02	1.705E+01	-1.111E+04	7.175E+03	3.253E+01	1.103E+02
7.079E-02	1.751E+01	-1.153E+04	7.650E+03	3.396E+01	1.126E+02
6.888E-02	1.800E+01	-1.198E+04	8.164E+03	3.548E+01	1.150E+02
6.696E-02	1.852E+01	-1.244E+04	8.724E+03	3.711E+01	1.176E+02
6.505E-02	1.906E+01	-1.293E+04	9.333E+03	3.884E+01	1.202E+02
6.314E-02	1.964E+01	-1.344E+04	9.997E+03	4.068E+01	1.229E+02
6.122E-02	2.025E+01	-1.398E+04	1.072E+04	4.265E+01	1.257E+02
5.931E-02	2.090E+01	-1.454E+04	1.151E+04	4.475E+01	1.286E+02
5.740E-02	2.160E+01	-1.513E+04	1.238E+04	4.701E+01	1.317E+02
5.548E-02	2.235E+01	-1.575E+04	1.333E+04	4.942E+01	1.349E+02
5.357E-02	2.314E+01	-1.640E+04	1.437E+04	5.200E+01	1.382E+02
5.166E-02	2.400E+01	-1.708E+04	1.552E+04	5.478E+01	1.417E+02
4.974E-02	2.492E+01	-1.778E+04	1.679E+04	5.776E+01	1.453E+02