

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.592E+00	2.700E-01	2.309E-01	3.846E+00	1.429E+00	1.346E+00
4.428E+00	2.800E-01	5.747E-01	3.795E+00	1.485E+00	1.277E+00
4.275E+00	2.900E-01	1.060E+00	3.654E+00	1.560E+00	1.171E+00
4.133E+00	3.000E-01	1.763E+00	2.945E+00	1.612E+00	9.136E-01
3.999E+00	3.100E-01	1.667E+00	1.419E+00	1.389E+00	5.111E-01
3.875E+00	3.200E-01	5.778E-01	5.695E-01	8.334E-01	3.417E-01
3.757E+00	3.300E-01	-3.997E-01	3.070E-01	2.283E-01	6.722E-01
3.647E+00	3.400E-01	-1.134E+00	3.351E-01	1.557E-01	1.076E+00
3.542E+00	3.500E-01	-1.701E+00	3.233E-01	1.234E-01	1.310E+00
3.444E+00	3.600E-01	-2.260E+00	2.993E-01	9.932E-02	1.507E+00
3.351E+00	3.700E-01	-2.800E+00	2.943E-01	8.781E-02	1.676E+00
3.263E+00	3.800E-01	-3.317E+00	2.933E-01	8.045E-02	1.823E+00
3.179E+00	3.900E-01	-3.835E+00	2.935E-01	7.488E-02	1.960E+00
3.100E+00	4.000E-01	-4.330E+00	3.001E-01	7.207E-02	2.082E+00
3.024E+00	4.100E-01	-4.853E+00	3.047E-01	6.911E-02	2.204E+00
2.952E+00	4.200E-01	-5.352E+00	3.142E-01	6.788E-02	2.314E+00
2.883E+00	4.300E-01	-5.861E+00	3.269E-01	6.749E-02	2.422E+00
2.818E+00	4.400E-01	-6.380E+00	3.331E-01	6.591E-02	2.527E+00
2.755E+00	4.500E-01	-6.894E+00	3.461E-01	6.589E-02	2.626E+00
2.695E+00	4.600E-01	-7.425E+00	3.561E-01	6.533E-02	2.726E+00
2.638E+00	4.700E-01	-7.955E+00	3.698E-01	6.553E-02	2.821E+00
2.583E+00	4.800E-01	-8.508E+00	3.818E-01	6.543E-02	2.918E+00
2.530E+00	4.900E-01	-9.047E+00	3.989E-01	6.629E-02	3.009E+00
2.480E+00	5.000E-01	-9.606E+00	4.149E-01	6.691E-02	3.100E+00
2.431E+00	5.100E-01	-1.017E+01	4.328E-01	6.786E-02	3.189E+00
2.384E+00	5.200E-01	-1.077E+01	4.475E-01	6.816E-02	3.282E+00
2.339E+00	5.300E-01	-1.135E+01	4.674E-01	6.937E-02	3.369E+00
2.296E+00	5.400E-01	-1.193E+01	4.850E-01	7.021E-02	3.454E+00
2.254E+00	5.500E-01	-1.255E+01	5.025E-01	7.091E-02	3.543E+00
2.214E+00	5.600E-01	-1.317E+01	5.228E-01	7.202E-02	3.630E+00
2.175E+00	5.700E-01	-1.380E+01	5.436E-01	7.315E-02	3.716E+00
2.138E+00	5.800E-01	-1.443E+01	5.667E-01	7.458E-02	3.799E+00
2.101E+00	5.900E-01	-1.506E+01	5.904E-01	7.605E-02	3.882E+00
2.066E+00	6.000E-01	-1.573E+01	6.099E-01	7.688E-02	3.966E+00
2.033E+00	6.100E-01	-1.638E+01	6.388E-01	7.890E-02	4.048E+00
2.000E+00	6.200E-01	-1.707E+01	6.514E-01	7.883E-02	4.132E+00
1.968E+00	6.300E-01	-1.775E+01	6.777E-01	8.040E-02	4.214E+00
1.937E+00	6.400E-01	-1.845E+01	7.023E-01	8.174E-02	4.296E+00
1.907E+00	6.500E-01	-1.915E+01	7.264E-01	8.298E-02	4.377E+00
1.879E+00	6.600E-01	-1.986E+01	7.538E-01	8.457E-02	4.457E+00
1.851E+00	6.700E-01	-2.060E+01	7.755E-01	8.541E-02	4.540E+00
1.823E+00	6.800E-01	-2.133E+01	8.016E-01	8.676E-02	4.620E+00
1.797E+00	6.900E-01	-2.208E+01	8.264E-01	8.792E-02	4.700E+00
1.771E+00	7.000E-01	-2.286E+01	8.501E-01	8.888E-02	4.782E+00
1.746E+00	7.100E-01	-2.360E+01	8.779E-01	9.034E-02	4.859E+00
1.722E+00	7.200E-01	-2.436E+01	9.104E-01	9.221E-02	4.936E+00
1.698E+00	7.300E-01	-2.517E+01	9.345E-01	9.312E-02	5.018E+00
1.675E+00	7.400E-01	-2.596E+01	9.585E-01	9.405E-02	5.096E+00
1.653E+00	7.500E-01	-2.677E+01	9.924E-01	9.588E-02	5.175E+00
1.631E+00	7.600E-01	-2.763E+01	1.018E+00	9.680E-02	5.258E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.610E+00	7.700E-01	-2.848E+01	1.040E+00	9.741E-02	5.337E+00
1.590E+00	7.800E-01	-2.924E+01	1.094E+00	1.012E-01	5.409E+00
1.569E+00	7.900E-01	-3.013E+01	1.119E+00	1.019E-01	5.490E+00
1.550E+00	8.000E-01	-3.097E+01	1.148E+00	1.032E-01	5.566E+00
1.531E+00	8.100E-01	-3.189E+01	1.163E+00	1.030E-01	5.648E+00
1.512E+00	8.200E-01	-3.285E+01	1.221E+00	1.065E-01	5.733E+00
1.494E+00	8.300E-01	-3.363E+01	1.253E+00	1.080E-01	5.800E+00
1.476E+00	8.400E-01	-3.457E+01	1.286E+00	1.094E-01	5.880E+00
1.459E+00	8.500E-01	-3.573E+01	1.355E+00	1.133E-01	5.979E+00
1.442E+00	8.600E-01	-3.670E+01	1.382E+00	1.140E-01	6.059E+00
1.425E+00	8.700E-01	-3.767E+01	1.427E+00	1.162E-01	6.139E+00
1.409E+00	8.800E-01	-3.853E+01	1.456E+00	1.173E-01	6.209E+00
1.393E+00	8.900E-01	-3.965E+01	1.508E+00	1.197E-01	6.298E+00
1.378E+00	9.000E-01	-4.066E+01	1.547E+00	1.213E-01	6.378E+00
1.362E+00	9.100E-01	-4.169E+01	1.600E+00	1.239E-01	6.458E+00
1.348E+00	9.200E-01	-4.235E+01	1.620E+00	1.245E-01	6.509E+00
1.333E+00	9.300E-01	-4.352E+01	1.679E+00	1.272E-01	6.598E+00
1.319E+00	9.400E-01	-4.449E+01	1.722E+00	1.290E-01	6.671E+00
1.305E+00	9.500E-01	-4.549E+01	1.771E+00	1.313E-01	6.746E+00
1.292E+00	9.600E-01	-4.658E+01	1.830E+00	1.340E-01	6.826E+00
1.278E+00	9.700E-01	-4.769E+01	1.883E+00	1.363E-01	6.907E+00
1.265E+00	9.800E-01	-4.846E+01	1.921E+00	1.380E-01	6.963E+00
1.252E+00	9.900E-01	-4.975E+01	1.992E+00	1.412E-01	7.055E+00
1.240E+00	1.000E+00	-5.082E+01	2.039E+00	1.430E-01	7.130E+00
1.228E+00	1.010E+00	-5.197E+01	2.102E+00	1.458E-01	7.210E+00
1.216E+00	1.020E+00	-5.296E+01	2.153E+00	1.479E-01	7.279E+00
1.204E+00	1.030E+00	-5.416E+01	2.210E+00	1.501E-01	7.361E+00
1.192E+00	1.040E+00	-5.525E+01	2.268E+00	1.525E-01	7.435E+00
1.181E+00	1.050E+00	-5.637E+01	2.339E+00	1.557E-01	7.510E+00
1.170E+00	1.060E+00	-5.755E+01	2.398E+00	1.580E-01	7.588E+00
1.159E+00	1.070E+00	-5.877E+01	2.451E+00	1.599E-01	7.668E+00
1.148E+00	1.080E+00	-5.994E+01	2.518E+00	1.626E-01	7.744E+00
1.137E+00	1.090E+00	-6.090E+01	2.591E+00	1.660E-01	7.806E+00
1.127E+00	1.100E+00	-6.228E+01	2.656E+00	1.683E-01	7.894E+00
1.117E+00	1.110E+00	-6.345E+01	2.720E+00	1.707E-01	7.967E+00
1.107E+00	1.120E+00	-6.457E+01	2.788E+00	1.735E-01	8.037E+00
1.097E+00	1.130E+00	-6.588E+01	2.875E+00	1.771E-01	8.119E+00
1.088E+00	1.140E+00	-6.714E+01	2.943E+00	1.796E-01	8.196E+00
1.078E+00	1.150E+00	-6.844E+01	3.021E+00	1.826E-01	8.275E+00
1.069E+00	1.160E+00	-6.966E+01	3.086E+00	1.848E-01	8.348E+00
1.060E+00	1.170E+00	-7.106E+01	3.185E+00	1.889E-01	8.432E+00
1.051E+00	1.180E+00	-7.209E+01	3.249E+00	1.913E-01	8.493E+00
1.042E+00	1.190E+00	-7.337E+01	3.310E+00	1.932E-01	8.568E+00
1.033E+00	1.200E+00	-7.473E+01	3.360E+00	1.943E-01	8.647E+00
1.025E+00	1.210E+00	-7.597E+01	3.448E+00	1.978E-01	8.718E+00
1.016E+00	1.220E+00	-7.743E+01	3.546E+00	2.014E-01	8.802E+00
1.008E+00	1.230E+00	-7.864E+01	3.639E+00	2.051E-01	8.871E+00
9.999E-01	1.240E+00	-8.005E+01	3.724E+00	2.081E-01	8.950E+00
9.919E-01	1.250E+00	-8.138E+01	3.808E+00	2.110E-01	9.024E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.840E-01	1.260E+00	-8.299E+01	3.889E+00	2.134E-01	9.113E+00
9.763E-01	1.270E+00	-8.395E+01	3.978E+00	2.170E-01	9.165E+00
9.686E-01	1.280E+00	-8.548E+01	4.100E+00	2.217E-01	9.248E+00
9.611E-01	1.290E+00	-8.691E+01	4.149E+00	2.225E-01	9.325E+00
9.537E-01	1.300E+00	-8.834E+01	4.225E+00	2.247E-01	9.402E+00
9.464E-01	1.310E+00	-8.986E+01	4.403E+00	2.322E-01	9.482E+00
9.393E-01	1.320E+00	-9.127E+01	4.472E+00	2.340E-01	9.557E+00
9.322E-01	1.330E+00	-9.269E+01	4.517E+00	2.345E-01	9.631E+00
9.253E-01	1.340E+00	-9.417E+01	4.612E+00	2.376E-01	9.707E+00
9.184E-01	1.350E+00	-9.548E+01	4.762E+00	2.436E-01	9.774E+00
8.670E-01	1.430E+00	-1.076E+02	5.550E+00	2.674E-01	1.038E+01
8.610E-01	1.440E+00	-1.094E+02	5.700E+00	2.724E-01	1.046E+01
8.551E-01	1.450E+00	-1.108E+02	5.796E+00	2.752E-01	1.053E+01
8.492E-01	1.460E+00	-1.123E+02	5.922E+00	2.793E-01	1.060E+01
8.434E-01	1.470E+00	-1.142E+02	6.072E+00	2.840E-01	1.069E+01
8.377E-01	1.480E+00	-1.154E+02	6.144E+00	2.859E-01	1.075E+01
8.321E-01	1.490E+00	-1.169E+02	6.400E+00	2.958E-01	1.082E+01
8.266E-01	1.500E+00	-1.186E+02	6.411E+00	2.942E-01	1.090E+01
8.211E-01	1.510E+00	-1.204E+02	6.640E+00	3.024E-01	1.098E+01
8.157E-01	1.520E+00	-1.221E+02	6.669E+00	3.017E-01	1.105E+01
8.104E-01	1.530E+00	-1.237E+02	6.888E+00	3.095E-01	1.113E+01
8.051E-01	1.540E+00	-1.255E+02	6.935E+00	3.094E-01	1.121E+01
7.999E-01	1.550E+00	-1.271E+02	7.324E+00	3.248E-01	1.128E+01
7.948E-01	1.560E+00	-1.287E+02	7.527E+00	3.316E-01	1.135E+01
7.897E-01	1.570E+00	-1.303E+02	7.604E+00	3.329E-01	1.142E+01
7.847E-01	1.580E+00	-1.321E+02	7.626E+00	3.316E-01	1.150E+01
7.798E-01	1.590E+00	-1.337E+02	7.740E+00	3.346E-01	1.157E+01
7.749E-01	1.600E+00	-1.356E+02	7.881E+00	3.383E-01	1.165E+01
7.701E-01	1.610E+00	-1.373E+02	8.081E+00	3.447E-01	1.172E+01
7.653E-01	1.620E+00	-1.391E+02	8.149E+00	3.453E-01	1.180E+01
7.606E-01	1.630E+00	-1.407E+02	8.447E+00	3.559E-01	1.187E+01
7.560E-01	1.640E+00	-1.427E+02	8.511E+00	3.560E-01	1.195E+01
7.514E-01	1.650E+00	-1.443E+02	8.608E+00	3.581E-01	1.202E+01
7.469E-01	1.660E+00	-1.462E+02	8.694E+00	3.594E-01	1.210E+01
7.424E-01	1.670E+00	-1.481E+02	9.087E+00	3.732E-01	1.218E+01
7.380E-01	1.680E+00	-1.497E+02	9.286E+00	3.794E-01	1.224E+01
7.336E-01	1.690E+00	-1.516E+02	9.305E+00	3.777E-01	1.232E+01
7.293E-01	1.700E+00	-1.537E+02	9.411E+00	3.794E-01	1.240E+01
7.251E-01	1.710E+00	-1.556E+02	9.393E+00	3.763E-01	1.248E+01
7.208E-01	1.720E+00	-1.572E+02	9.562E+00	3.811E-01	1.255E+01
7.167E-01	1.730E+00	-1.592E+02	1.008E+01	3.992E-01	1.262E+01
7.126E-01	1.740E+00	-1.608E+02	1.007E+01	3.968E-01	1.269E+01
7.085E-01	1.750E+00	-1.629E+02	1.037E+01	4.062E-01	1.277E+01
7.045E-01	1.760E+00	-1.646E+02	1.041E+01	4.053E-01	1.284E+01
7.005E-01	1.770E+00	-1.662E+02	1.047E+01	4.060E-01	1.290E+01
6.965E-01	1.780E+00	-1.682E+02	1.070E+01	4.123E-01	1.298E+01
6.926E-01	1.790E+00	-1.699E+02	1.078E+01	4.132E-01	1.304E+01
6.888E-01	1.800E+00	-1.727E+02	1.123E+01	4.269E-01	1.315E+01
6.850E-01	1.810E+00	-1.749E+02	1.123E+01	4.244E-01	1.323E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.812E-01	1.820E+00	-1.763E+02	1.158E+01	4.357E-01	1.329E+01
6.775E-01	1.830E+00	-1.785E+02	1.187E+01	4.440E-01	1.337E+01
6.738E-01	1.840E+00	-1.803E+02	1.160E+01	4.317E-01	1.343E+01
6.702E-01	1.850E+00	-1.822E+02	1.189E+01	4.404E-01	1.351E+01
6.666E-01	1.860E+00	-1.841E+02	1.212E+01	4.466E-01	1.357E+01
6.630E-01	1.870E+00	-1.880E+02	1.161E+01	4.231E-01	1.372E+01
6.595E-01	1.880E+00	-1.890E+02	1.268E+01	4.609E-01	1.376E+01
6.560E-01	1.890E+00	-1.904E+02	1.282E+01	4.642E-01	1.381E+01
6.525E-01	1.900E+00	-1.929E+02	1.322E+01	4.757E-01	1.390E+01
6.491E-01	1.910E+00	-1.947E+02	1.297E+01	4.646E-01	1.396E+01
6.458E-01	1.920E+00	-1.963E+02	1.307E+01	4.660E-01	1.402E+01
6.424E-01	1.930E+00	-1.995E+02	1.326E+01	4.693E-01	1.413E+01
6.391E-01	1.940E+00	-2.013E+02	1.330E+01	4.686E-01	1.420E+01
6.358E-01	1.950E+00	-2.025E+02	1.397E+01	4.905E-01	1.424E+01
6.326E-01	1.960E+00	-2.062E+02	1.418E+01	4.935E-01	1.437E+01
6.294E-01	1.970E+00	-2.078E+02	1.440E+01	4.993E-01	1.443E+01
6.262E-01	1.980E+00	-2.101E+02	1.477E+01	5.090E-01	1.451E+01
6.230E-01	1.990E+00	-2.113E+02	1.470E+01	5.053E-01	1.455E+01
6.199E-01	2.000E+00	-2.141E+02	1.448E+01	4.946E-01	1.464E+01
-	-	-	-	-	-
7.269E-01	1.706E+00	-1.405E+02	6.972E+00	2.940E-01	1.186E+01
7.212E-01	1.719E+00	-1.430E+02	6.948E+00	2.904E-01	1.196E+01
7.174E-01	1.728E+00	-1.447E+02	6.630E+00	2.755E-01	1.203E+01
7.135E-01	1.738E+00	-1.458E+02	6.324E+00	2.618E-01	1.208E+01
7.097E-01	1.747E+00	-1.474E+02	6.624E+00	2.728E-01	1.214E+01
7.059E-01	1.756E+00	-1.493E+02	7.237E+00	2.961E-01	1.222E+01
7.021E-01	1.766E+00	-1.511E+02	7.243E+00	2.946E-01	1.230E+01
6.982E-01	1.776E+00	-1.524E+02	6.856E+00	2.776E-01	1.235E+01
6.944E-01	1.785E+00	-1.539E+02	6.744E+00	2.717E-01	1.241E+01
6.906E-01	1.795E+00	-1.553E+02	7.033E+00	2.821E-01	1.247E+01
6.868E-01	1.805E+00	-1.569E+02	7.650E+00	3.052E-01	1.253E+01
6.830E-01	1.815E+00	-1.586E+02	8.151E+00	3.235E-01	1.260E+01
6.791E-01	1.826E+00	-1.609E+02	8.242E+00	3.248E-01	1.269E+01
6.753E-01	1.836E+00	-1.634E+02	8.086E+00	3.162E-01	1.279E+01
6.715E-01	1.847E+00	-1.650E+02	7.903E+00	3.075E-01	1.285E+01
6.676E-01	1.857E+00	-1.663E+02	7.926E+00	3.072E-01	1.290E+01
6.638E-01	1.868E+00	-1.680E+02	8.187E+00	3.157E-01	1.297E+01
6.600E-01	1.879E+00	-1.703E+02	8.549E+00	3.275E-01	1.305E+01
6.562E-01	1.890E+00	-1.725E+02	8.450E+00	3.216E-01	1.314E+01
6.524E-01	1.895E+00	-1.737E+02	8.331E+00	3.159E-01	1.318E+01
6.504E-01	1.906E+00	-1.765E+02	8.460E+00	3.183E-01	1.329E+01
6.466E-01	1.918E+00	-1.787E+02	9.036E+00	3.379E-01	1.337E+01
6.428E-01	1.929E+00	-1.801E+02	9.663E+00	3.599E-01	1.342E+01
6.408E-01	1.935E+00	-1.810E+02	9.879E+00	3.670E-01	1.346E+01
6.370E-01	1.946E+00	-1.838E+02	9.848E+00	3.631E-01	1.356E+01
6.332E-01	1.958E+00	-1.858E+02	9.671E+00	3.546E-01	1.364E+01
6.294E-01	1.970E+00	-1.879E+02	1.004E+01	3.662E-01	1.371E+01
6.274E-01	1.976E+00	-1.889E+02	1.018E+01	3.702E-01	1.375E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.236E-01	1.988E+00	-1.916E+02	1.025E+01	3.703E-01	1.385E+01
6.217E-01	1.994E+00	-1.928E+02	1.031E+01	3.713E-01	1.389E+01
6.179E-01	2.007E+00	-1.951E+02	1.040E+01	3.723E-01	1.397E+01
6.141E-01	2.019E+00	-1.977E+02	1.039E+01	3.695E-01	1.407E+01
6.121E-01	2.025E+00	-1.990E+02	1.036E+01	3.671E-01	1.411E+01
6.083E-01	2.038E+00	-2.012E+02	1.028E+01	3.622E-01	1.419E+01
6.064E-01	2.045E+00	-2.023E+02	1.054E+01	3.705E-01	1.423E+01
6.026E-01	2.058E+00	-2.052E+02	1.156E+01	4.034E-01	1.433E+01
6.007E-01	2.064E+00	-2.070E+02	1.177E+01	4.088E-01	1.439E+01
5.969E-01	2.077E+00	-2.096E+02	1.166E+01	4.027E-01	1.448E+01
5.949E-01	2.084E+00	-2.107E+02	1.176E+01	4.048E-01	1.452E+01
5.911E-01	2.098E+00	-2.137E+02	1.197E+01	4.094E-01	1.462E+01
5.892E-01	2.104E+00	-2.155E+02	1.212E+01	4.127E-01	1.469E+01
5.854E-01	2.118E+00	-2.182E+02	1.253E+01	4.241E-01	1.478E+01
5.835E-01	2.125E+00	-2.195E+02	1.254E+01	4.230E-01	1.482E+01
5.796E-01	2.139E+00	-2.226E+02	1.232E+01	4.126E-01	1.493E+01
5.777E-01	2.146E+00	-2.239E+02	1.226E+01	4.096E-01	1.497E+01
5.758E-01	2.153E+00	-2.253E+02	1.233E+01	4.107E-01	1.501E+01
5.720E-01	2.168E+00	-2.279E+02	1.294E+01	4.283E-01	1.510E+01
5.701E-01	2.175E+00	-2.295E+02	1.334E+01	4.400E-01	1.516E+01
5.662E-01	2.190E+00	-2.327E+02	1.388E+01	4.549E-01	1.526E+01
5.643E-01	2.197E+00	-2.348E+02	1.406E+01	4.585E-01	1.533E+01
5.624E-01	2.205E+00	-2.367E+02	1.410E+01	4.582E-01	1.539E+01
5.586E-01	2.220E+00	-2.398E+02	1.427E+01	4.604E-01	1.549E+01
5.567E-01	2.227E+00	-2.415E+02	1.459E+01	4.691E-01	1.555E+01
5.548E-01	2.235E+00	-2.431E+02	1.493E+01	4.784E-01	1.560E+01
5.529E-01	2.243E+00	-2.448E+02	1.522E+01	4.860E-01	1.566E+01
5.490E-01	2.258E+00	-2.474E+02	1.539E+01	4.889E-01	1.574E+01
5.471E-01	2.266E+00	-2.491E+02	1.537E+01	4.868E-01	1.579E+01
5.452E-01	2.274E+00	-2.512E+02	1.548E+01	4.883E-01	1.586E+01
5.433E-01	2.282E+00	-2.531E+02	1.571E+01	4.934E-01	1.592E+01
5.395E-01	2.298E+00	-2.573E+02	1.636E+01	5.098E-01	1.605E+01
5.375E-01	2.307E+00	-2.592E+02	1.663E+01	5.161E-01	1.611E+01
5.356E-01	2.315E+00	-2.610E+02	1.681E+01	5.201E-01	1.617E+01
5.337E-01	2.323E+00	-2.631E+02	1.703E+01	5.247E-01	1.623E+01
5.299E-01	2.340E+00	-2.670E+02	1.717E+01	5.253E-01	1.635E+01
5.280E-01	2.348E+00	-2.691E+02	1.717E+01	5.231E-01	1.641E+01
5.261E-01	2.357E+00	-2.712E+02	1.725E+01	5.235E-01	1.648E+01
5.242E-01	2.365E+00	-2.729E+02	1.730E+01	5.233E-01	1.653E+01
5.223E-01	2.374E+00	-2.747E+02	1.727E+01	5.206E-01	1.658E+01
5.203E-01	2.383E+00	-2.769E+02	1.731E+01	5.198E-01	1.665E+01
5.184E-01	2.392E+00	-2.792E+02	1.747E+01	5.225E-01	1.672E+01
5.146E-01	2.409E+00	-2.838E+02	1.792E+01	5.315E-01	1.685E+01
5.127E-01	2.418E+00	-2.863E+02	1.825E+01	5.389E-01	1.693E+01
5.108E-01	2.427E+00	-2.885E+02	1.859E+01	5.471E-01	1.699E+01
5.089E-01	2.437E+00	-2.906E+02	1.889E+01	5.537E-01	1.706E+01
5.069E-01	2.446E+00	-2.926E+02	1.915E+01	5.596E-01	1.712E+01
5.050E-01	2.455E+00	-2.946E+02	1.944E+01	5.661E-01	1.717E+01
5.031E-01	2.464E+00	-2.970E+02	1.981E+01	5.745E-01	1.724E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
5.012E-01	2.474E+00	-2.998E+02	2.028E+01	5.853E-01	1.733E+01
4.993E-01	2.483E+00	-3.026E+02	2.081E+01	5.979E-01	1.741E+01
4.974E-01	2.493E+00	-3.048E+02	2.119E+01	6.064E-01	1.747E+01
4.955E-01	2.502E+00	-3.068E+02	2.118E+01	6.043E-01	1.753E+01
4.935E-01	2.512E+00	-3.089E+02	2.098E+01	5.965E-01	1.759E+01
4.916E-01	2.522E+00	-3.117E+02	2.107E+01	5.964E-01	1.767E+01
4.897E-01	2.532E+00	-3.146E+02	2.166E+01	6.102E-01	1.775E+01
4.878E-01	2.542E+00	-3.173E+02	2.242E+01	6.289E-01	1.782E+01
4.859E-01	2.552E+00	-3.201E+02	2.291E+01	6.399E-01	1.790E+01
4.840E-01	2.562E+00	-3.228E+02	2.303E+01	6.404E-01	1.798E+01
4.821E-01	2.572E+00	-3.252E+02	2.307E+01	6.391E-01	1.805E+01
4.802E-01	2.582E+00	-3.276E+02	2.332E+01	6.438E-01	1.811E+01
4.782E-01	2.593E+00	-3.305E+02	2.374E+01	6.525E-01	1.819E+01
4.763E-01	2.603E+00	-3.333E+02	2.407E+01	6.587E-01	1.827E+01
4.744E-01	2.613E+00	-3.361E+02	2.438E+01	6.645E-01	1.835E+01
4.725E-01	2.624E+00	-3.394E+02	2.492E+01	6.758E-01	1.843E+01
4.706E-01	2.635E+00	-3.423E+02	2.545E+01	6.873E-01	1.852E+01
4.687E-01	2.645E+00	-3.449E+02	2.570E+01	6.914E-01	1.859E+01
4.668E-01	2.656E+00	-3.476E+02	2.594E+01	6.952E-01	1.866E+01
4.649E-01	2.667E+00	-3.506E+02	2.641E+01	7.048E-01	1.874E+01
4.629E-01	2.678E+00	-3.535E+02	2.675E+01	7.109E-01	1.882E+01
4.610E-01	2.689E+00	-3.563E+02	2.688E+01	7.116E-01	1.889E+01
4.591E-01	2.701E+00	-3.596E+02	2.714E+01	7.152E-01	1.898E+01
4.572E-01	2.712E+00	-3.628E+02	2.763E+01	7.247E-01	1.906E+01
4.553E-01	2.723E+00	-3.658E+02	2.813E+01	7.349E-01	1.914E+01
4.534E-01	2.735E+00	-3.686E+02	2.847E+01	7.410E-01	1.921E+01
4.515E-01	2.746E+00	-3.715E+02	2.882E+01	7.471E-01	1.929E+01
4.496E-01	2.758E+00	-3.744E+02	2.925E+01	7.552E-01	1.936E+01
4.476E-01	2.770E+00	-3.775E+02	2.969E+01	7.634E-01	1.944E+01
4.457E-01	2.782E+00	-3.811E+02	3.013E+01	7.711E-01	1.954E+01
4.438E-01	2.794E+00	-3.849E+02	3.059E+01	7.789E-01	1.964E+01
4.419E-01	2.806E+00	-3.885E+02	3.100E+01	7.857E-01	1.973E+01
4.400E-01	2.818E+00	-3.920E+02	3.133E+01	7.906E-01	1.982E+01
4.381E-01	2.830E+00	-3.955E+02	3.165E+01	7.951E-01	1.990E+01
4.362E-01	2.843E+00	-3.989E+02	3.184E+01	7.966E-01	1.999E+01
4.343E-01	2.855E+00	-4.025E+02	3.196E+01	7.958E-01	2.008E+01
4.323E-01	2.868E+00	-4.060E+02	3.227E+01	8.002E-01	2.017E+01
4.304E-01	2.881E+00	-4.097E+02	3.287E+01	8.112E-01	2.026E+01
4.285E-01	2.893E+00	-4.133E+02	3.354E+01	8.243E-01	2.035E+01
4.266E-01	2.906E+00	-4.168E+02	3.429E+01	8.391E-01	2.043E+01
4.247E-01	2.919E+00	-4.202E+02	3.517E+01	8.571E-01	2.052E+01
4.228E-01	2.933E+00	-4.236E+02	3.605E+01	8.750E-01	2.060E+01
4.209E-01	2.946E+00	-4.274E+02	3.671E+01	8.870E-01	2.069E+01
4.189E-01	2.959E+00	-4.315E+02	3.692E+01	8.878E-01	2.079E+01
4.170E-01	2.973E+00	-4.357E+02	3.699E+01	8.853E-01	2.089E+01
4.151E-01	2.987E+00	-4.397E+02	3.740E+01	8.909E-01	2.099E+01
4.132E-01	3.001E+00	-4.438E+02	3.802E+01	9.016E-01	2.109E+01
4.113E-01	3.015E+00	-4.484E+02	3.856E+01	9.096E-01	2.120E+01
4.094E-01	3.029E+00	-4.529E+02	3.886E+01	9.123E-01	2.130E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.075E-01	3.043E+00	-4.570E+02	3.920E+01	9.159E-01	2.140E+01
4.056E-01	3.057E+00	-4.611E+02	3.985E+01	9.269E-01	2.149E+01
4.036E-01	3.072E+00	-4.652E+02	4.063E+01	9.410E-01	2.159E+01
4.017E-01	3.086E+00	-4.694E+02	4.154E+01	9.576E-01	2.169E+01
3.998E-01	3.101E+00	-4.740E+02	4.254E+01	9.760E-01	2.179E+01
3.979E-01	3.116E+00	-4.789E+02	4.316E+01	9.851E-01	2.191E+01
3.960E-01	3.131E+00	-4.840E+02	4.341E+01	9.856E-01	2.202E+01
3.941E-01	3.146E+00	-4.889E+02	4.367E+01	9.867E-01	2.213E+01
3.922E-01	3.162E+00	-4.938E+02	4.394E+01	9.878E-01	2.224E+01
3.903E-01	3.177E+00	-4.990E+02	4.447E+01	9.944E-01	2.236E+01
3.883E-01	3.193E+00	-5.041E+02	4.525E+01	1.007E+00	2.247E+01
3.864E-01	3.209E+00	-5.093E+02	4.590E+01	1.016E+00	2.259E+01
3.845E-01	3.224E+00	-5.148E+02	4.678E+01	1.030E+00	2.271E+01
3.826E-01	3.241E+00	-5.199E+02	4.801E+01	1.052E+00	2.283E+01
3.807E-01	3.257E+00	-5.248E+02	4.902E+01	1.069E+00	2.293E+01
3.788E-01	3.273E+00	-5.301E+02	4.978E+01	1.080E+00	2.305E+01
3.769E-01	3.290E+00	-5.355E+02	5.057E+01	1.091E+00	2.317E+01
3.749E-01	3.307E+00	-5.410E+02	5.104E+01	1.096E+00	2.329E+01
3.730E-01	3.324E+00	-5.467E+02	5.116E+01	1.093E+00	2.341E+01
3.711E-01	3.341E+00	-5.528E+02	5.179E+01	1.100E+00	2.354E+01
3.692E-01	3.358E+00	-5.588E+02	5.303E+01	1.121E+00	2.367E+01
3.673E-01	3.376E+00	-5.645E+02	5.411E+01	1.137E+00	2.379E+01
3.654E-01	3.393E+00	-5.701E+02	5.492E+01	1.149E+00	2.391E+01
3.635E-01	3.411E+00	-5.756E+02	5.594E+01	1.165E+00	2.402E+01
3.616E-01	3.429E+00	-5.812E+02	5.704E+01	1.182E+00	2.414E+01
3.596E-01	3.447E+00	-5.878E+02	5.800E+01	1.195E+00	2.427E+01
3.577E-01	3.466E+00	-5.944E+02	5.896E+01	1.208E+00	2.441E+01
3.558E-01	3.485E+00	-6.006E+02	5.981E+01	1.219E+00	2.454E+01
3.539E-01	3.503E+00	-6.071E+02	6.035E+01	1.223E+00	2.467E+01
3.520E-01	3.522E+00	-6.141E+02	6.105E+01	1.230E+00	2.481E+01
3.501E-01	3.542E+00	-6.212E+02	6.199E+01	1.242E+00	2.495E+01
3.482E-01	3.561E+00	-6.282E+02	6.286E+01	1.252E+00	2.510E+01
3.463E-01	3.581E+00	-6.352E+02	6.364E+01	1.261E+00	2.524E+01
3.443E-01	3.601E+00	-6.425E+02	6.465E+01	1.274E+00	2.538E+01
3.424E-01	3.621E+00	-6.501E+02	6.596E+01	1.292E+00	2.553E+01
3.405E-01	3.641E+00	-6.575E+02	6.692E+01	1.303E+00	2.567E+01
3.386E-01	3.662E+00	-6.648E+02	6.752E+01	1.308E+00	2.582E+01
3.367E-01	3.683E+00	-6.725E+02	6.843E+01	1.318E+00	2.597E+01
3.348E-01	3.704E+00	-6.806E+02	6.984E+01	1.337E+00	2.612E+01
3.329E-01	3.725E+00	-6.889E+02	7.094E+01	1.350E+00	2.628E+01
3.310E-01	3.746E+00	-6.970E+02	7.195E+01	1.361E+00	2.644E+01
3.290E-01	3.768E+00	-7.051E+02	7.322E+01	1.377E+00	2.659E+01
3.271E-01	3.790E+00	-7.135E+02	7.461E+01	1.395E+00	2.675E+01
3.252E-01	3.812E+00	-7.223E+02	7.642E+01	1.420E+00	2.691E+01
3.233E-01	3.835E+00	-7.310E+02	7.805E+01	1.441E+00	2.708E+01
3.214E-01	3.858E+00	-7.397E+02	7.910E+01	1.452E+00	2.724E+01
3.195E-01	3.881E+00	-7.487E+02	8.007E+01	1.461E+00	2.740E+01
3.176E-01	3.904E+00	-7.579E+02	8.170E+01	1.482E+00	2.757E+01
3.156E-01	3.928E+00	-7.672E+02	8.356E+01	1.506E+00	2.774E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.137E-01	3.952E+00	-7.765E+02	8.504E+01	1.524E+00	2.791E+01
3.118E-01	3.976E+00	-7.859E+02	8.692E+01	1.548E+00	2.808E+01
3.099E-01	4.001E+00	-7.959E+02	8.864E+01	1.569E+00	2.826E+01
3.080E-01	4.026E+00	-8.058E+02	8.980E+01	1.579E+00	2.843E+01
3.061E-01	4.051E+00	-8.158E+02	9.125E+01	1.595E+00	2.861E+01
3.042E-01	4.076E+00	-8.260E+02	9.351E+01	1.624E+00	2.879E+01
3.023E-01	4.102E+00	-8.365E+02	9.564E+01	1.651E+00	2.897E+01
3.003E-01	4.128E+00	-8.474E+02	9.701E+01	1.664E+00	2.916E+01
2.984E-01	4.155E+00	-8.588E+02	9.871E+01	1.681E+00	2.935E+01
2.965E-01	4.181E+00	-8.698E+02	1.012E+02	1.713E+00	2.954E+01
2.946E-01	4.209E+00	-8.810E+02	1.046E+02	1.758E+00	2.973E+01
2.927E-01	4.236E+00	-8.934E+02	1.075E+02	1.795E+00	2.994E+01
2.908E-01	4.264E+00	-9.057E+02	1.096E+02	1.817E+00	3.015E+01
2.889E-01	4.292E+00	-9.186E+02	1.113E+02	1.833E+00	3.036E+01
2.869E-01	4.321E+00	-9.317E+02	1.125E+02	1.839E+00	3.058E+01
2.850E-01	4.350E+00	-9.433E+02	1.137E+02	1.848E+00	3.077E+01
2.831E-01	4.379E+00	-9.554E+02	1.159E+02	1.871E+00	3.097E+01
2.812E-01	4.409E+00	-9.681E+02	1.181E+02	1.894E+00	3.117E+01
2.793E-01	4.439E+00	-9.814E+02	1.199E+02	1.911E+00	3.139E+01
2.774E-01	4.470E+00	-9.949E+02	1.222E+02	1.934E+00	3.160E+01
2.755E-01	4.501E+00	-1.008E+03	1.251E+02	1.967E+00	3.182E+01
2.736E-01	4.532E+00	-1.022E+03	1.279E+02	1.997E+00	3.204E+01
2.716E-01	4.564E+00	-1.037E+03	1.307E+02	2.025E+00	3.227E+01
2.697E-01	4.597E+00	-1.052E+03	1.336E+02	2.055E+00	3.250E+01
2.678E-01	4.629E+00	-1.065E+03	1.362E+02	2.083E+00	3.270E+01
2.659E-01	4.663E+00	-1.079E+03	1.386E+02	2.106E+00	3.291E+01
2.640E-01	4.697E+00	-1.095E+03	1.414E+02	2.132E+00	3.316E+01
2.621E-01	4.731E+00	-1.112E+03	1.445E+02	2.162E+00	3.342E+01
2.602E-01	4.766E+00	-1.129E+03	1.473E+02	2.188E+00	3.367E+01
2.583E-01	4.801E+00	-1.146E+03	1.507E+02	2.221E+00	3.392E+01
2.563E-01	4.837E+00	-1.163E+03	1.547E+02	2.263E+00	3.417E+01
2.544E-01	4.873E+00	-1.180E+03	1.576E+02	2.289E+00	3.443E+01
2.525E-01	4.910E+00	-1.198E+03	1.601E+02	2.308E+00	3.469E+01
2.506E-01	4.947E+00	-1.216E+03	1.641E+02	2.347E+00	3.495E+01
2.487E-01	4.986E+00	-1.234E+03	1.680E+02	2.385E+00	3.521E+01
2.468E-01	5.024E+00	-1.253E+03	1.717E+02	2.420E+00	3.548E+01
2.449E-01	5.063E+00	-1.272E+03	1.759E+02	2.460E+00	3.575E+01
2.429E-01	5.103E+00	-1.291E+03	1.795E+02	2.492E+00	3.601E+01
2.410E-01	5.144E+00	-1.311E+03	1.830E+02	2.521E+00	3.630E+01
2.391E-01	5.185E+00	-1.332E+03	1.873E+02	2.560E+00	3.659E+01
2.372E-01	5.227E+00	-1.353E+03	1.913E+02	2.594E+00	3.687E+01
2.353E-01	5.269E+00	-1.374E+03	1.951E+02	2.626E+00	3.716E+01
2.334E-01	5.312E+00	-1.396E+03	2.001E+02	2.671E+00	3.746E+01
2.315E-01	5.356E+00	-1.419E+03	2.054E+02	2.719E+00	3.777E+01
2.296E-01	5.401E+00	-1.443E+03	2.103E+02	2.761E+00	3.809E+01
2.276E-01	5.446E+00	-1.467E+03	2.152E+02	2.802E+00	3.840E+01
2.257E-01	5.493E+00	-1.491E+03	2.202E+02	2.843E+00	3.872E+01
2.238E-01	5.539E+00	-1.517E+03	2.263E+02	2.897E+00	3.905E+01
2.219E-01	5.587E+00	-1.542E+03	2.331E+02	2.960E+00	3.938E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.200E-01	5.636E+00	-1.567E+03	2.397E+02	3.018E+00	3.970E+01
2.181E-01	5.685E+00	-1.593E+03	2.467E+02	3.081E+00	4.003E+01
2.162E-01	5.736E+00	-1.620E+03	2.540E+02	3.146E+00	4.037E+01
2.143E-01	5.787E+00	-1.650E+03	2.606E+02	3.198E+00	4.074E+01
2.123E-01	5.839E+00	-1.679E+03	2.678E+02	3.259E+00	4.110E+01
2.104E-01	5.892E+00	-1.708E+03	2.754E+02	3.321E+00	4.146E+01
2.085E-01	5.946E+00	-1.739E+03	2.817E+02	3.366E+00	4.184E+01
2.066E-01	6.001E+00	-1.772E+03	2.880E+02	3.409E+00	4.224E+01
2.047E-01	6.057E+00	-1.809E+03	2.955E+02	3.463E+00	4.268E+01
2.028E-01	6.114E+00	-1.844E+03	3.045E+02	3.533E+00	4.309E+01
2.009E-01	6.173E+00	-1.875E+03	3.122E+02	3.593E+00	4.345E+01
1.990E-01	6.232E+00	-1.910E+03	3.187E+02	3.634E+00	4.386E+01
1.970E-01	6.292E+00	-1.948E+03	3.289E+02	3.712E+00	4.429E+01
1.951E-01	6.354E+00	-1.984E+03	3.428E+02	3.834E+00	4.471E+01
1.932E-01	6.417E+00	-2.021E+03	3.565E+02	3.949E+00	4.513E+01
1.913E-01	6.481E+00	-2.061E+03	3.682E+02	4.039E+00	4.558E+01
1.894E-01	6.547E+00	-2.101E+03	3.777E+02	4.103E+00	4.602E+01
1.875E-01	6.613E+00	-2.142E+03	3.865E+02	4.159E+00	4.647E+01
1.856E-01	6.682E+00	-2.187E+03	3.984E+02	4.243E+00	4.695E+01
1.836E-01	6.751E+00	-2.231E+03	4.124E+02	4.347E+00	4.744E+01
1.817E-01	6.822E+00	-2.277E+03	4.258E+02	4.442E+00	4.793E+01
1.798E-01	6.895E+00	-2.328E+03	4.409E+02	4.549E+00	4.846E+01
1.779E-01	6.969E+00	-2.373E+03	4.626E+02	4.726E+00	4.895E+01
1.760E-01	7.045E+00	-2.409E+03	4.907E+02	4.974E+00	4.933E+01
1.741E-01	7.122E+00	-2.452E+03	5.145E+02	5.167E+00	4.978E+01
1.722E-01	7.201E+00	-2.508E+03	5.199E+02	5.164E+00	5.035E+01
1.703E-01	7.282E+00	-2.567E+03	5.122E+02	5.030E+00	5.091E+01
1.683E-01	7.365E+00	-2.638E+03	5.250E+02	5.085E+00	5.162E+01
1.664E-01	7.450E+00	-2.693E+03	5.574E+02	5.342E+00	5.217E+01
1.645E-01	7.536E+00	-2.746E+03	5.711E+02	5.420E+00	5.268E+01
1.626E-01	7.625E+00	-2.809E+03	5.781E+02	5.426E+00	5.328E+01
1.607E-01	7.716E+00	-2.874E+03	6.006E+02	5.571E+00	5.390E+01
1.588E-01	7.809E+00	-2.941E+03	6.279E+02	5.757E+00	5.454E+01
1.569E-01	7.904E+00	-3.003E+03	6.505E+02	5.901E+00	5.512E+01
1.550E-01	8.001E+00	-3.073E+03	6.741E+02	6.044E+00	5.576E+01
1.530E-01	8.101E+00	-3.159E+03	6.983E+02	6.175E+00	5.654E+01
1.511E-01	8.204E+00	-3.244E+03	7.272E+02	6.345E+00	5.731E+01
1.492E-01	8.309E+00	-3.324E+03	7.677E+02	6.615E+00	5.803E+01
1.473E-01	8.417E+00	-3.403E+03	8.147E+02	6.934E+00	5.875E+01
1.454E-01	8.528E+00	-3.489E+03	8.478E+02	7.125E+00	5.950E+01
1.435E-01	8.642E+00	-3.578E+03	8.780E+02	7.285E+00	6.026E+01
1.416E-01	8.758E+00	-3.656E+03	9.261E+02	7.599E+00	6.094E+01
1.396E-01	8.878E+00	-3.732E+03	9.731E+02	7.899E+00	6.160E+01
1.377E-01	9.002E+00	-3.825E+03	9.984E+02	8.006E+00	6.236E+01
1.358E-01	9.128E+00	-3.939E+03	1.013E+03	8.005E+00	6.327E+01
1.339E-01	9.259E+00	-4.052E+03	1.052E+03	8.195E+00	6.418E+01
1.320E-01	9.393E+00	-4.166E+03	1.094E+03	8.404E+00	6.509E+01
1.301E-01	9.531E+00	-4.290E+03	1.128E+03	8.539E+00	6.605E+01
1.282E-01	9.673E+00	-4.413E+03	1.180E+03	8.807E+00	6.702E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample A
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.263E-01	9.820E+00	-4.545E+03	1.237E+03	9.095E+00	6.803E+01
1.243E-01	9.971E+00	-4.680E+03	1.273E+03	9.222E+00	6.903E+01
1.224E-01	1.013E+01	-4.807E+03	1.310E+03	9.359E+00	6.996E+01
1.205E-01	1.029E+01	-4.939E+03	1.379E+03	9.716E+00	7.095E+01
1.186E-01	1.045E+01	-5.073E+03	1.468E+03	1.020E+01	7.196E+01
1.167E-01	1.063E+01	-5.212E+03	1.544E+03	1.058E+01	7.297E+01
1.148E-01	1.080E+01	-5.374E+03	1.580E+03	1.066E+01	7.408E+01
1.129E-01	1.099E+01	-5.534E+03	1.623E+03	1.080E+01	7.517E+01
1.110E-01	1.117E+01	-5.693E+03	1.718E+03	1.126E+01	7.629E+01
1.090E-01	1.137E+01	-5.876E+03	1.818E+03	1.172E+01	7.754E+01
1.071E-01	1.157E+01	-6.076E+03	1.918E+03	1.216E+01	7.889E+01
1.052E-01	1.178E+01	-6.288E+03	2.019E+03	1.257E+01	8.029E+01
1.033E-01	1.200E+01	-6.500E+03	2.114E+03	1.294E+01	8.166E+01
1.014E-01	1.223E+01	-6.736E+03	2.241E+03	1.347E+01	8.317E+01
9.947E-02	1.246E+01	-7.026E+03	2.405E+03	1.415E+01	8.500E+01
9.756E-02	1.271E+01	-7.309E+03	2.537E+03	1.462E+01	8.674E+01
9.565E-02	1.296E+01	-7.588E+03	2.660E+03	1.505E+01	8.840E+01
9.374E-02	1.323E+01	-7.826E+03	2.812E+03	1.565E+01	8.984E+01
9.183E-02	1.350E+01	-8.048E+03	2.972E+03	1.630E+01	9.118E+01
8.991E-02	1.379E+01	-8.307E+03	3.100E+03	1.673E+01	9.266E+01
8.800E-02	1.409E+01	-8.557E+03	3.306E+03	1.756E+01	9.416E+01
8.608E-02	1.440E+01	-8.820E+03	3.571E+03	1.865E+01	9.575E+01
8.417E-02	1.473E+01	-9.173E+03	3.761E+03	1.925E+01	9.769E+01
8.226E-02	1.507E+01	-9.618E+03	3.940E+03	1.970E+01	1.000E+02
8.035E-02	1.543E+01	-1.004E+04	4.187E+03	2.047E+01	1.023E+02
7.843E-02	1.581E+01	-1.050E+04	4.338E+03	2.074E+01	1.046E+02
7.652E-02	1.620E+01	-1.099E+04	4.598E+03	2.149E+01	1.070E+02
7.461E-02	1.662E+01	-1.145E+04	4.987E+03	2.279E+01	1.094E+02
7.269E-02	1.706E+01	-1.197E+04	5.210E+03	2.329E+01	1.119E+02
7.078E-02	1.752E+01	-1.251E+04	5.408E+03	2.366E+01	1.143E+02
6.887E-02	1.800E+01	-1.314E+04	5.568E+03	2.378E+01	1.171E+02
6.696E-02	1.852E+01	-1.383E+04	5.723E+03	2.384E+01	1.200E+02
6.504E-02	1.906E+01	-1.460E+04	6.107E+03	2.476E+01	1.233E+02
6.313E-02	1.964E+01	-1.522E+04	6.594E+03	2.614E+01	1.261E+02
6.121E-02	2.025E+01	-1.550E+04	7.281E+03	2.850E+01	1.277E+02
5.930E-02	2.091E+01	-1.608E+04	8.247E+03	3.155E+01	1.307E+02
5.739E-02	2.160E+01	-1.712E+04	9.062E+03	3.354E+01	1.351E+02
5.548E-02	2.235E+01	-1.852E+04	9.509E+03	3.390E+01	1.403E+02
5.356E-02	2.315E+01	-1.946E+04	1.040E+04	3.611E+01	1.441E+02
5.165E-02	2.400E+01	-2.014E+04	1.163E+04	3.947E+01	1.473E+02
4.974E-02	2.493E+01	-2.132E+04	1.254E+04	4.133E+01	1.518E+02