

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.592E+00	2.700E-01	2.232E-01	3.775E+00	1.415E+00	1.334E+00
4.428E+00	2.800E-01	5.714E-01	3.785E+00	1.483E+00	1.276E+00
4.275E+00	2.900E-01	1.037E+00	3.608E+00	1.548E+00	1.166E+00
4.133E+00	3.000E-01	1.738E+00	2.936E+00	1.605E+00	9.150E-01
3.999E+00	3.100E-01	1.670E+00	1.438E+00	1.392E+00	5.165E-01
3.875E+00	3.200E-01	5.631E-01	5.454E-01	8.207E-01	3.323E-01
3.757E+00	3.300E-01	-3.949E-01	2.974E-01	2.230E-01	6.668E-01
3.647E+00	3.400E-01	-1.129E+00	2.973E-01	1.387E-01	1.072E+00
3.542E+00	3.500E-01	-1.737E+00	2.906E-01	1.099E-01	1.323E+00
3.444E+00	3.600E-01	-2.287E+00	2.897E-01	9.559E-02	1.515E+00
3.351E+00	3.700E-01	-2.826E+00	2.870E-01	8.527E-02	1.683E+00
3.263E+00	3.800E-01	-3.347E+00	2.994E-01	8.174E-02	1.831E+00
3.179E+00	3.900E-01	-3.854E+00	3.052E-01	7.769E-02	1.965E+00
3.100E+00	4.000E-01	-4.354E+00	3.143E-01	7.527E-02	2.088E+00
3.024E+00	4.100E-01	-4.858E+00	3.229E-01	7.321E-02	2.205E+00
2.952E+00	4.200E-01	-5.363E+00	3.376E-01	7.285E-02	2.317E+00
2.883E+00	4.300E-01	-5.866E+00	3.530E-01	7.284E-02	2.423E+00
2.818E+00	4.400E-01	-6.376E+00	3.624E-01	7.173E-02	2.526E+00
2.755E+00	4.500E-01	-6.894E+00	3.822E-01	7.275E-02	2.627E+00
2.695E+00	4.600E-01	-7.420E+00	3.984E-01	7.310E-02	2.725E+00
2.638E+00	4.700E-01	-7.955E+00	4.154E-01	7.362E-02	2.822E+00
2.583E+00	4.800E-01	-8.495E+00	4.355E-01	7.468E-02	2.916E+00
2.530E+00	4.900E-01	-9.053E+00	4.503E-01	7.480E-02	3.010E+00
2.480E+00	5.000E-01	-9.615E+00	4.671E-01	7.530E-02	3.102E+00
2.431E+00	5.100E-01	-1.018E+01	4.859E-01	7.612E-02	3.192E+00
2.384E+00	5.200E-01	-1.074E+01	5.133E-01	7.830E-02	3.278E+00
2.339E+00	5.300E-01	-1.132E+01	5.335E-01	7.926E-02	3.366E+00
2.296E+00	5.400E-01	-1.193E+01	5.515E-01	7.983E-02	3.454E+00
2.254E+00	5.500E-01	-1.253E+01	5.750E-01	8.121E-02	3.540E+00
2.214E+00	5.600E-01	-1.314E+01	6.003E-01	8.279E-02	3.625E+00
2.175E+00	5.700E-01	-1.377E+01	6.245E-01	8.414E-02	3.711E+00
2.138E+00	5.800E-01	-1.440E+01	6.490E-01	8.550E-02	3.795E+00
2.101E+00	5.900E-01	-1.503E+01	6.728E-01	8.674E-02	3.878E+00
2.066E+00	6.000E-01	-1.567E+01	6.981E-01	8.815E-02	3.960E+00
2.033E+00	6.100E-01	-1.634E+01	7.247E-01	8.962E-02	4.043E+00
2.000E+00	6.200E-01	-1.702E+01	7.527E-01	9.121E-02	4.126E+00
1.968E+00	6.300E-01	-1.771E+01	7.771E-01	9.230E-02	4.209E+00
1.937E+00	6.400E-01	-1.839E+01	8.076E-01	9.414E-02	4.290E+00
1.907E+00	6.500E-01	-1.909E+01	8.311E-01	9.509E-02	4.370E+00
1.879E+00	6.600E-01	-1.981E+01	8.487E-01	9.533E-02	4.451E+00
1.851E+00	6.700E-01	-2.054E+01	8.850E-01	9.762E-02	4.533E+00
1.823E+00	6.800E-01	-2.126E+01	9.144E-01	9.914E-02	4.612E+00
1.797E+00	6.900E-01	-2.200E+01	9.417E-01	1.004E-01	4.692E+00
1.771E+00	7.000E-01	-2.275E+01	9.656E-01	1.012E-01	4.771E+00
1.746E+00	7.100E-01	-2.353E+01	9.962E-01	1.027E-01	4.852E+00
1.722E+00	7.200E-01	-2.430E+01	1.026E+00	1.041E-01	4.931E+00
1.698E+00	7.300E-01	-2.511E+01	1.057E+00	1.054E-01	5.013E+00
1.675E+00	7.400E-01	-2.589E+01	1.094E+00	1.075E-01	5.089E+00
1.653E+00	7.500E-01	-2.668E+01	1.125E+00	1.088E-01	5.167E+00
1.631E+00	7.600E-01	-2.752E+01	1.154E+00	1.100E-01	5.247E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.610E+00	7.700E-01	-2.832E+01	1.191E+00	1.119E-01	5.323E+00
1.590E+00	7.800E-01	-2.917E+01	1.217E+00	1.126E-01	5.402E+00
1.569E+00	7.900E-01	-3.001E+01	1.255E+00	1.145E-01	5.479E+00
1.550E+00	8.000E-01	-3.088E+01	1.312E+00	1.181E-01	5.558E+00
1.531E+00	8.100E-01	-3.177E+01	1.343E+00	1.191E-01	5.638E+00
1.512E+00	8.200E-01	-3.273E+01	1.383E+00	1.208E-01	5.723E+00
1.494E+00	8.300E-01	-3.351E+01	1.415E+00	1.222E-01	5.790E+00
1.476E+00	8.400E-01	-3.444E+01	1.457E+00	1.241E-01	5.870E+00
1.459E+00	8.500E-01	-3.562E+01	1.517E+00	1.271E-01	5.969E+00
1.442E+00	8.600E-01	-3.661E+01	1.558E+00	1.287E-01	6.052E+00
1.425E+00	8.700E-01	-3.755E+01	1.608E+00	1.312E-01	6.129E+00
1.409E+00	8.800E-01	-3.841E+01	1.643E+00	1.325E-01	6.199E+00
1.393E+00	8.900E-01	-3.954E+01	1.702E+00	1.353E-01	6.289E+00
1.378E+00	9.000E-01	-4.054E+01	1.747E+00	1.371E-01	6.369E+00
1.362E+00	9.100E-01	-4.158E+01	1.803E+00	1.398E-01	6.450E+00
1.348E+00	9.200E-01	-4.220E+01	1.828E+00	1.406E-01	6.498E+00
1.333E+00	9.300E-01	-4.339E+01	1.890E+00	1.434E-01	6.589E+00
1.319E+00	9.400E-01	-4.435E+01	1.944E+00	1.459E-01	6.661E+00
1.305E+00	9.500E-01	-4.535E+01	1.991E+00	1.478E-01	6.736E+00
1.292E+00	9.600E-01	-4.643E+01	2.051E+00	1.505E-01	6.816E+00
1.278E+00	9.700E-01	-4.754E+01	2.113E+00	1.532E-01	6.897E+00
1.265E+00	9.800E-01	-4.833E+01	2.156E+00	1.550E-01	6.953E+00
1.252E+00	9.900E-01	-4.961E+01	2.233E+00	1.585E-01	7.045E+00
1.240E+00	1.000E+00	-5.064E+01	2.294E+00	1.611E-01	7.118E+00
1.228E+00	1.010E+00	-5.180E+01	2.350E+00	1.632E-01	7.199E+00
1.216E+00	1.020E+00	-5.281E+01	2.408E+00	1.657E-01	7.269E+00
1.204E+00	1.030E+00	-5.398E+01	2.477E+00	1.685E-01	7.349E+00
1.192E+00	1.040E+00	-5.509E+01	2.543E+00	1.713E-01	7.425E+00
1.181E+00	1.050E+00	-5.624E+01	2.603E+00	1.735E-01	7.501E+00
1.170E+00	1.060E+00	-5.733E+01	2.701E+00	1.783E-01	7.574E+00
1.159E+00	1.070E+00	-5.855E+01	2.756E+00	1.800E-01	7.654E+00
1.148E+00	1.080E+00	-5.977E+01	2.820E+00	1.824E-01	7.733E+00
1.137E+00	1.090E+00	-6.077E+01	2.899E+00	1.859E-01	7.798E+00
1.127E+00	1.100E+00	-6.212E+01	2.968E+00	1.882E-01	7.884E+00
1.117E+00	1.110E+00	-6.324E+01	3.065E+00	1.927E-01	7.955E+00
1.107E+00	1.120E+00	-6.438E+01	3.137E+00	1.955E-01	8.026E+00
1.097E+00	1.130E+00	-6.571E+01	3.231E+00	1.993E-01	8.109E+00
1.088E+00	1.140E+00	-6.694E+01	3.297E+00	2.014E-01	8.184E+00
1.078E+00	1.150E+00	-6.819E+01	3.381E+00	2.046E-01	8.261E+00
1.069E+00	1.160E+00	-6.946E+01	3.460E+00	2.075E-01	8.337E+00
1.060E+00	1.170E+00	-7.086E+01	3.556E+00	2.112E-01	8.421E+00
1.051E+00	1.180E+00	-7.185E+01	3.632E+00	2.142E-01	8.479E+00
1.042E+00	1.190E+00	-7.317E+01	3.715E+00	2.171E-01	8.557E+00
1.033E+00	1.200E+00	-7.454E+01	3.793E+00	2.196E-01	8.636E+00
1.025E+00	1.210E+00	-7.586E+01	3.875E+00	2.224E-01	8.713E+00
1.016E+00	1.220E+00	-7.711E+01	3.982E+00	2.267E-01	8.784E+00
1.008E+00	1.230E+00	-7.847E+01	4.046E+00	2.283E-01	8.862E+00
9.999E-01	1.240E+00	-7.974E+01	4.169E+00	2.334E-01	8.933E+00
9.919E-01	1.250E+00	-8.112E+01	4.220E+00	2.342E-01	9.010E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.840E-01	1.260E+00	-8.274E+01	4.351E+00	2.391E-01	9.099E+00
9.763E-01	1.270E+00	-8.372E+01	4.416E+00	2.412E-01	9.153E+00
9.686E-01	1.280E+00	-8.525E+01	4.505E+00	2.439E-01	9.236E+00
9.611E-01	1.290E+00	-8.672E+01	4.645E+00	2.493E-01	9.316E+00
9.537E-01	1.300E+00	-8.804E+01	4.804E+00	2.559E-01	9.386E+00
9.464E-01	1.310E+00	-8.948E+01	4.876E+00	2.577E-01	9.463E+00
9.393E-01	1.320E+00	-9.091E+01	4.942E+00	2.591E-01	9.538E+00
9.322E-01	1.330E+00	-9.232E+01	5.001E+00	2.601E-01	9.612E+00
9.253E-01	1.340E+00	-9.369E+01	5.169E+00	2.669E-01	9.683E+00
9.184E-01	1.350E+00	-9.530E+01	5.243E+00	2.684E-01	9.766E+00
8.670E-01	1.430E+00	-1.073E+02	6.086E+00	2.937E-01	1.036E+01
8.610E-01	1.440E+00	-1.089E+02	6.320E+00	3.027E-01	1.044E+01
8.551E-01	1.450E+00	-1.106E+02	6.458E+00	3.070E-01	1.052E+01
8.492E-01	1.460E+00	-1.119E+02	6.571E+00	3.104E-01	1.059E+01
8.434E-01	1.470E+00	-1.138E+02	6.755E+00	3.165E-01	1.067E+01
8.377E-01	1.480E+00	-1.150E+02	6.778E+00	3.158E-01	1.073E+01
8.321E-01	1.490E+00	-1.167E+02	6.919E+00	3.201E-01	1.081E+01
8.266E-01	1.500E+00	-1.184E+02	7.118E+00	3.270E-01	1.089E+01
8.211E-01	1.510E+00	-1.203E+02	7.236E+00	3.297E-01	1.097E+01
8.157E-01	1.520E+00	-1.216E+02	7.400E+00	3.354E-01	1.103E+01
8.104E-01	1.530E+00	-1.235E+02	7.543E+00	3.392E-01	1.112E+01
8.051E-01	1.540E+00	-1.252E+02	7.730E+00	3.453E-01	1.119E+01
7.999E-01	1.550E+00	-1.265E+02	8.172E+00	3.631E-01	1.125E+01
7.948E-01	1.560E+00	-1.284E+02	8.305E+00	3.663E-01	1.134E+01
7.897E-01	1.570E+00	-1.300E+02	8.386E+00	3.675E-01	1.141E+01
7.847E-01	1.580E+00	-1.317E+02	8.532E+00	3.715E-01	1.148E+01
7.798E-01	1.590E+00	-1.336E+02	8.676E+00	3.751E-01	1.156E+01
7.749E-01	1.600E+00	-1.352E+02	8.905E+00	3.827E-01	1.164E+01
7.701E-01	1.610E+00	-1.368E+02	9.000E+00	3.845E-01	1.170E+01
7.653E-01	1.620E+00	-1.387E+02	9.113E+00	3.867E-01	1.178E+01
7.606E-01	1.630E+00	-1.408E+02	9.194E+00	3.872E-01	1.187E+01
7.560E-01	1.640E+00	-1.421E+02	9.334E+00	3.914E-01	1.193E+01
7.514E-01	1.650E+00	-1.440E+02	9.767E+00	4.068E-01	1.201E+01
7.469E-01	1.660E+00	-1.458E+02	9.818E+00	4.063E-01	1.208E+01
7.424E-01	1.670E+00	-1.476E+02	1.003E+01	4.127E-01	1.216E+01
7.380E-01	1.680E+00	-1.492E+02	1.019E+01	4.167E-01	1.222E+01
7.336E-01	1.690E+00	-1.513E+02	1.029E+01	4.179E-01	1.231E+01
7.293E-01	1.700E+00	-1.528E+02	1.033E+01	4.174E-01	1.237E+01
7.251E-01	1.710E+00	-1.550E+02	1.076E+01	4.320E-01	1.246E+01
7.208E-01	1.720E+00	-1.565E+02	1.061E+01	4.236E-01	1.252E+01
7.167E-01	1.730E+00	-1.585E+02	1.090E+01	4.325E-01	1.260E+01
7.126E-01	1.740E+00	-1.603E+02	1.116E+01	4.406E-01	1.267E+01
7.085E-01	1.750E+00	-1.622E+02	1.151E+01	4.516E-01	1.274E+01
7.045E-01	1.760E+00	-1.639E+02	1.176E+01	4.588E-01	1.281E+01
7.005E-01	1.770E+00	-1.661E+02	1.153E+01	4.472E-01	1.290E+01
6.965E-01	1.780E+00	-1.678E+02	1.228E+01	4.737E-01	1.296E+01
6.926E-01	1.790E+00	-1.696E+02	1.182E+01	4.537E-01	1.303E+01
6.888E-01	1.800E+00	-1.717E+02	1.215E+01	4.635E-01	1.311E+01
6.850E-01	1.810E+00	-1.744E+02	1.230E+01	4.653E-01	1.321E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.812E-01	1.820E+00	-1.760E+02	1.279E+01	4.817E-01	1.328E+01
6.775E-01	1.830E+00	-1.785E+02	1.266E+01	4.736E-01	1.337E+01
6.738E-01	1.840E+00	-1.798E+02	1.304E+01	4.861E-01	1.342E+01
6.702E-01	1.850E+00	-1.820E+02	1.339E+01	4.959E-01	1.350E+01
6.666E-01	1.860E+00	-1.839E+02	1.366E+01	5.035E-01	1.357E+01
6.630E-01	1.870E+00	-1.863E+02	1.326E+01	4.854E-01	1.366E+01
6.595E-01	1.880E+00	-1.887E+02	1.405E+01	5.109E-01	1.375E+01
6.560E-01	1.890E+00	-1.901E+02	1.424E+01	5.160E-01	1.380E+01
6.525E-01	1.900E+00	-1.920E+02	1.395E+01	5.029E-01	1.387E+01
6.491E-01	1.910E+00	-1.952E+02	1.423E+01	5.088E-01	1.398E+01
6.458E-01	1.920E+00	-1.966E+02	1.473E+01	5.250E-01	1.403E+01
6.424E-01	1.930E+00	-1.987E+02	1.465E+01	5.194E-01	1.411E+01
6.391E-01	1.940E+00	-2.009E+02	1.557E+01	5.487E-01	1.418E+01
6.358E-01	1.950E+00	-2.033E+02	1.528E+01	5.353E-01	1.427E+01
6.326E-01	1.960E+00	-2.037E+02	1.546E+01	5.411E-01	1.428E+01
6.294E-01	1.970E+00	-2.068E+02	1.610E+01	5.593E-01	1.439E+01
6.262E-01	1.980E+00	-2.098E+02	1.636E+01	5.644E-01	1.449E+01
6.230E-01	1.990E+00	-2.110E+02	1.652E+01	5.680E-01	1.454E+01
6.199E-01	2.000E+00	-2.122E+02	1.663E+01	5.702E-01	1.458E+01
—	—	—	—	—	—
—	—	—	—	—	—
7.269E-01	1.706E+00	-1.406E+02	7.147E+00	3.013E-01	1.186E+01
7.212E-01	1.719E+00	-1.430E+02	7.193E+00	3.007E-01	1.196E+01
7.174E-01	1.728E+00	-1.445E+02	7.376E+00	3.067E-01	1.202E+01
7.135E-01	1.738E+00	-1.455E+02	7.467E+00	3.095E-01	1.207E+01
7.097E-01	1.747E+00	-1.470E+02	7.980E+00	3.290E-01	1.213E+01
7.059E-01	1.756E+00	-1.490E+02	8.584E+00	3.515E-01	1.221E+01
7.021E-01	1.766E+00	-1.509E+02	8.357E+00	3.401E-01	1.229E+01
6.982E-01	1.776E+00	-1.522E+02	7.910E+00	3.205E-01	1.234E+01
6.944E-01	1.785E+00	-1.538E+02	7.992E+00	3.222E-01	1.240E+01
6.906E-01	1.795E+00	-1.553E+02	8.258E+00	3.312E-01	1.247E+01
6.868E-01	1.805E+00	-1.570E+02	8.681E+00	3.463E-01	1.253E+01
6.830E-01	1.815E+00	-1.585E+02	8.934E+00	3.547E-01	1.260E+01
6.791E-01	1.826E+00	-1.608E+02	8.852E+00	3.489E-01	1.269E+01
6.753E-01	1.836E+00	-1.633E+02	8.753E+00	3.423E-01	1.279E+01
6.715E-01	1.847E+00	-1.648E+02	8.987E+00	3.499E-01	1.284E+01
6.676E-01	1.857E+00	-1.662E+02	9.675E+00	3.750E-01	1.290E+01
6.638E-01	1.868E+00	-1.682E+02	1.023E+01	3.943E-01	1.298E+01
6.600E-01	1.879E+00	-1.703E+02	1.012E+01	3.876E-01	1.306E+01
6.562E-01	1.890E+00	-1.723E+02	9.585E+00	3.650E-01	1.313E+01
6.542E-01	1.895E+00	-1.735E+02	9.562E+00	3.629E-01	1.318E+01
6.504E-01	1.906E+00	-1.761E+02	9.976E+00	3.757E-01	1.328E+01
6.466E-01	1.918E+00	-1.783E+02	1.021E+01	3.823E-01	1.336E+01
6.428E-01	1.929E+00	-1.798E+02	1.019E+01	3.799E-01	1.342E+01
6.408E-01	1.935E+00	-1.808E+02	1.031E+01	3.833E-01	1.345E+01
6.370E-01	1.946E+00	-1.835E+02	1.058E+01	3.905E-01	1.355E+01
6.332E-01	1.958E+00	-1.854E+02	1.061E+01	3.893E-01	1.362E+01
6.294E-01	1.970E+00	-1.876E+02	1.088E+01	3.972E-01	1.370E+01
6.274E-01	1.976E+00	-1.888E+02	1.106E+01	4.024E-01	1.375E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.236E-01	1.988E+00	-1.916E+02	1.130E+01	4.080E-01	1.385E+01
6.217E-01	1.994E+00	-1.927E+02	1.141E+01	4.107E-01	1.389E+01
6.179E-01	2.007E+00	-1.949E+02	1.166E+01	4.173E-01	1.397E+01
6.141E-01	2.019E+00	-1.975E+02	1.166E+01	4.147E-01	1.406E+01
6.121E-01	2.025E+00	-1.988E+02	1.153E+01	4.086E-01	1.410E+01
6.083E-01	2.038E+00	-2.009E+02	1.142E+01	4.028E-01	1.418E+01
6.064E-01	2.045E+00	-2.021E+02	1.168E+01	4.106E-01	1.422E+01
6.026E-01	2.058E+00	-2.050E+02	1.258E+01	4.393E-01	1.432E+01
6.007E-01	2.064E+00	-2.067E+02	1.286E+01	4.471E-01	1.438E+01
5.969E-01	2.077E+00	-2.093E+02	1.278E+01	4.415E-01	1.447E+01
5.949E-01	2.084E+00	-2.103E+02	1.277E+01	4.402E-01	1.451E+01
5.911E-01	2.098E+00	-2.131E+02	1.320E+01	4.519E-01	1.461E+01
5.892E-01	2.104E+00	-2.151E+02	1.349E+01	4.597E-01	1.467E+01
5.854E-01	2.118E+00	-2.182E+02	1.393E+01	4.714E-01	1.478E+01
5.835E-01	2.125E+00	-2.196E+02	1.403E+01	4.730E-01	1.483E+01
5.796E-01	2.139E+00	-2.225E+02	1.415E+01	4.739E-01	1.492E+01
5.777E-01	2.146E+00	-2.237E+02	1.422E+01	4.751E-01	1.496E+01
5.758E-01	2.153E+00	-2.251E+02	1.426E+01	4.749E-01	1.501E+01
5.720E-01	2.168E+00	-2.278E+02	1.449E+01	4.797E-01	1.510E+01
5.701E-01	2.175E+00	-2.292E+02	1.486E+01	4.904E-01	1.515E+01
5.662E-01	2.190E+00	-2.323E+02	1.569E+01	5.144E-01	1.525E+01
5.643E-01	2.197E+00	-2.343E+02	1.591E+01	5.195E-01	1.532E+01
5.624E-01	2.205E+00	-2.362E+02	1.589E+01	5.167E-01	1.538E+01
5.586E-01	2.220E+00	-2.394E+02	1.582E+01	5.108E-01	1.548E+01
5.567E-01	2.227E+00	-2.412E+02	1.606E+01	5.169E-01	1.554E+01
5.548E-01	2.235E+00	-2.429E+02	1.636E+01	5.246E-01	1.560E+01
5.529E-01	2.243E+00	-2.447E+02	1.668E+01	5.327E-01	1.565E+01
5.490E-01	2.258E+00	-2.472E+02	1.702E+01	5.410E-01	1.573E+01
5.471E-01	2.266E+00	-2.490E+02	1.716E+01	5.434E-01	1.579E+01
5.452E-01	2.274E+00	-2.512E+02	1.748E+01	5.512E-01	1.586E+01
5.433E-01	2.282E+00	-2.533E+02	1.785E+01	5.605E-01	1.593E+01
5.395E-01	2.298E+00	-2.573E+02	1.848E+01	5.758E-01	1.605E+01
5.375E-01	2.307E+00	-2.589E+02	1.864E+01	5.788E-01	1.610E+01
5.356E-01	2.315E+00	-2.605E+02	1.857E+01	5.748E-01	1.615E+01
5.337E-01	2.323E+00	-2.626E+02	1.852E+01	5.710E-01	1.622E+01
5.299E-01	2.340E+00	-2.668E+02	1.876E+01	5.739E-01	1.634E+01
5.280E-01	2.348E+00	-2.689E+02	1.904E+01	5.801E-01	1.641E+01
5.261E-01	2.357E+00	-2.708E+02	1.932E+01	5.865E-01	1.647E+01
5.242E-01	2.365E+00	-2.726E+02	1.939E+01	5.869E-01	1.652E+01
5.223E-01	2.374E+00	-2.745E+02	1.940E+01	5.851E-01	1.658E+01
5.203E-01	2.383E+00	-2.767E+02	1.956E+01	5.875E-01	1.665E+01
5.184E-01	2.392E+00	-2.791E+02	1.967E+01	5.882E-01	1.672E+01
5.146E-01	2.409E+00	-2.835E+02	1.969E+01	5.844E-01	1.685E+01
5.127E-01	2.418E+00	-2.859E+02	2.019E+01	5.968E-01	1.692E+01
5.108E-01	2.427E+00	-2.880E+02	2.069E+01	6.092E-01	1.698E+01
5.089E-01	2.437E+00	-2.903E+02	2.091E+01	6.133E-01	1.705E+01
5.069E-01	2.446E+00	-2.926E+02	2.121E+01	6.195E-01	1.712E+01
5.050E-01	2.455E+00	-2.945E+02	2.167E+01	6.308E-01	1.717E+01
5.031E-01	2.464E+00	-2.969E+02	2.205E+01	6.394E-01	1.724E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
5.012E-01	2.474E+00	-2.999E+02	2.245E+01	6.478E-01	1.733E+01
4.993E-01	2.483E+00	-3.026E+02	2.292E+01	6.584E-01	1.741E+01
4.974E-01	2.493E+00	-3.048E+02	2.314E+01	6.622E-01	1.747E+01
4.955E-01	2.502E+00	-3.066E+02	2.320E+01	6.620E-01	1.752E+01
4.935E-01	2.512E+00	-3.087E+02	2.355E+01	6.698E-01	1.758E+01
4.916E-01	2.522E+00	-3.114E+02	2.414E+01	6.835E-01	1.766E+01
4.897E-01	2.532E+00	-3.143E+02	2.454E+01	6.916E-01	1.774E+01
4.878E-01	2.542E+00	-3.169E+02	2.478E+01	6.955E-01	1.782E+01
4.859E-01	2.552E+00	-3.195E+02	2.507E+01	7.007E-01	1.789E+01
4.840E-01	2.562E+00	-3.224E+02	2.534E+01	7.052E-01	1.797E+01
4.821E-01	2.572E+00	-3.250E+02	2.560E+01	7.094E-01	1.804E+01
4.802E-01	2.582E+00	-3.275E+02	2.597E+01	7.171E-01	1.811E+01
4.782E-01	2.593E+00	-3.300E+02	2.643E+01	7.268E-01	1.818E+01
4.763E-01	2.603E+00	-3.326E+02	2.687E+01	7.361E-01	1.825E+01
4.744E-01	2.613E+00	-3.357E+02	2.737E+01	7.463E-01	1.834E+01
4.725E-01	2.624E+00	-3.391E+02	2.772E+01	7.520E-01	1.843E+01
4.706E-01	2.635E+00	-3.419E+02	2.783E+01	7.521E-01	1.851E+01
4.687E-01	2.645E+00	-3.443E+02	2.805E+01	7.551E-01	1.857E+01
4.668E-01	2.656E+00	-3.472E+02	2.857E+01	7.659E-01	1.865E+01
4.649E-01	2.667E+00	-3.505E+02	2.918E+01	7.788E-01	1.874E+01
4.629E-01	2.678E+00	-3.534E+02	2.951E+01	7.841E-01	1.882E+01
4.610E-01	2.689E+00	-3.559E+02	2.960E+01	7.838E-01	1.888E+01
4.591E-01	2.701E+00	-3.588E+02	2.992E+01	7.890E-01	1.896E+01
4.572E-01	2.712E+00	-3.621E+02	3.057E+01	8.026E-01	1.905E+01
4.553E-01	2.723E+00	-3.654E+02	3.121E+01	8.155E-01	1.913E+01
4.534E-01	2.735E+00	-3.683E+02	3.171E+01	8.255E-01	1.921E+01
4.515E-01	2.746E+00	-3.711E+02	3.226E+01	8.366E-01	1.928E+01
4.496E-01	2.758E+00	-3.739E+02	3.259E+01	8.419E-01	1.936E+01
4.476E-01	2.770E+00	-3.770E+02	3.280E+01	8.439E-01	1.944E+01
4.457E-01	2.782E+00	-3.808E+02	3.336E+01	8.540E-01	1.953E+01
4.438E-01	2.794E+00	-3.847E+02	3.412E+01	8.690E-01	1.963E+01
4.419E-01	2.806E+00	-3.883E+02	3.461E+01	8.774E-01	1.973E+01
4.400E-01	2.818E+00	-3.917E+02	3.469E+01	8.756E-01	1.981E+01
4.381E-01	2.830E+00	-3.949E+02	3.463E+01	8.704E-01	1.989E+01
4.362E-01	2.843E+00	-3.982E+02	3.465E+01	8.674E-01	1.997E+01
4.343E-01	2.855E+00	-4.016E+02	3.482E+01	8.679E-01	2.006E+01
4.323E-01	2.868E+00	-4.051E+02	3.543E+01	8.794E-01	2.015E+01
4.304E-01	2.881E+00	-4.087E+02	3.628E+01	8.965E-01	2.024E+01
4.285E-01	2.893E+00	-4.124E+02	3.684E+01	9.062E-01	2.033E+01
4.266E-01	2.906E+00	-4.160E+02	3.762E+01	9.213E-01	2.042E+01
4.247E-01	2.919E+00	-4.198E+02	3.892E+01	9.487E-01	2.051E+01
4.228E-01	2.933E+00	-4.239E+02	4.015E+01	9.739E-01	2.061E+01
4.209E-01	2.946E+00	-4.278E+02	4.094E+01	9.885E-01	2.071E+01
4.189E-01	2.959E+00	-4.315E+02	4.135E+01	9.942E-01	2.080E+01
4.170E-01	2.973E+00	-4.353E+02	4.143E+01	9.917E-01	2.089E+01
4.151E-01	2.987E+00	-4.392E+02	4.135E+01	9.854E-01	2.098E+01
4.132E-01	3.001E+00	-4.432E+02	4.154E+01	9.855E-01	2.108E+01
4.113E-01	3.015E+00	-4.473E+02	4.202E+01	9.924E-01	2.117E+01
4.094E-01	3.029E+00	-4.516E+02	4.244E+01	9.974E-01	2.128E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.075E-01	3.043E+00	-4.562E+02	4.293E+01	1.004E+00	2.138E+01
4.056E-01	3.057E+00	-4.606E+02	4.359E+01	1.014E+00	2.149E+01
4.036E-01	3.072E+00	-4.647E+02	4.437E+01	1.028E+00	2.158E+01
4.017E-01	3.086E+00	-4.687E+02	4.540E+01	1.047E+00	2.168E+01
3.998E-01	3.101E+00	-4.734E+02	4.641E+01	1.065E+00	2.178E+01
3.979E-01	3.116E+00	-4.783E+02	4.714E+01	1.076E+00	2.190E+01
3.960E-01	3.131E+00	-4.830E+02	4.779E+01	1.086E+00	2.201E+01
3.941E-01	3.146E+00	-4.878E+02	4.820E+01	1.090E+00	2.211E+01
3.922E-01	3.162E+00	-4.928E+02	4.851E+01	1.091E+00	2.223E+01
3.903E-01	3.177E+00	-4.980E+02	4.936E+01	1.105E+00	2.234E+01
3.883E-01	3.193E+00	-5.033E+02	5.042E+01	1.122E+00	2.246E+01
3.864E-01	3.209E+00	-5.085E+02	5.111E+01	1.132E+00	2.258E+01
3.845E-01	3.224E+00	-5.137E+02	5.194E+01	1.145E+00	2.269E+01
3.826E-01	3.241E+00	-5.185E+02	5.319E+01	1.166E+00	2.280E+01
3.807E-01	3.257E+00	-5.233E+02	5.448E+01	1.189E+00	2.291E+01
3.788E-01	3.273E+00	-5.282E+02	5.557E+01	1.207E+00	2.302E+01
3.769E-01	3.290E+00	-5.340E+02	5.623E+01	1.215E+00	2.314E+01
3.749E-01	3.307E+00	-5.400E+02	5.639E+01	1.212E+00	2.327E+01
3.730E-01	3.324E+00	-5.458E+02	5.672E+01	1.212E+00	2.339E+01
3.711E-01	3.341E+00	-5.517E+02	5.777E+01	1.228E+00	2.352E+01
3.692E-01	3.358E+00	-5.574E+02	5.909E+01	1.250E+00	2.364E+01
3.673E-01	3.376E+00	-5.630E+02	5.993E+01	1.261E+00	2.376E+01
3.654E-01	3.393E+00	-5.688E+02	6.062E+01	1.269E+00	2.388E+01
3.635E-01	3.411E+00	-5.746E+02	6.149E+01	1.281E+00	2.401E+01
3.616E-01	3.429E+00	-5.805E+02	6.219E+01	1.289E+00	2.413E+01
3.596E-01	3.447E+00	-5.869E+02	6.303E+01	1.299E+00	2.426E+01
3.577E-01	3.466E+00	-5.932E+02	6.398E+01	1.311E+00	2.439E+01
3.558E-01	3.485E+00	-5.994E+02	6.493E+01	1.324E+00	2.452E+01
3.539E-01	3.503E+00	-6.059E+02	6.612E+01	1.341E+00	2.465E+01
3.520E-01	3.522E+00	-6.128E+02	6.728E+01	1.357E+00	2.479E+01
3.501E-01	3.542E+00	-6.196E+02	6.805E+01	1.365E+00	2.493E+01
3.482E-01	3.561E+00	-6.268E+02	6.872E+01	1.370E+00	2.507E+01
3.463E-01	3.581E+00	-6.342E+02	6.973E+01	1.382E+00	2.522E+01
3.443E-01	3.601E+00	-6.415E+02	7.094E+01	1.398E+00	2.537E+01
3.424E-01	3.621E+00	-6.487E+02	7.188E+01	1.409E+00	2.551E+01
3.405E-01	3.641E+00	-6.560E+02	7.303E+01	1.424E+00	2.565E+01
3.386E-01	3.662E+00	-6.634E+02	7.437E+01	1.442E+00	2.580E+01
3.367E-01	3.683E+00	-6.709E+02	7.539E+01	1.453E+00	2.594E+01
3.348E-01	3.704E+00	-6.788E+02	7.676E+01	1.471E+00	2.610E+01
3.329E-01	3.725E+00	-6.873E+02	7.824E+01	1.490E+00	2.626E+01
3.310E-01	3.746E+00	-6.956E+02	7.952E+01	1.505E+00	2.642E+01
3.290E-01	3.768E+00	-7.033E+02	8.095E+01	1.524E+00	2.656E+01
3.271E-01	3.790E+00	-7.115E+02	8.248E+01	1.543E+00	2.672E+01
3.252E-01	3.812E+00	-7.203E+02	8.447E+01	1.571E+00	2.688E+01
3.233E-01	3.835E+00	-7.289E+02	8.645E+01	1.598E+00	2.705E+01
3.214E-01	3.858E+00	-7.376E+02	8.771E+01	1.612E+00	2.721E+01
3.195E-01	3.881E+00	-7.464E+02	8.864E+01	1.619E+00	2.737E+01
3.176E-01	3.904E+00	-7.554E+02	9.016E+01	1.637E+00	2.753E+01
3.156E-01	3.928E+00	-7.648E+02	9.208E+01	1.662E+00	2.771E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.137E-01	3.952E+00	-7.743E+02	9.382E+01	1.683E+00	2.788E+01
3.118E-01	3.976E+00	-7.838E+02	9.559E+01	1.704E+00	2.805E+01
3.099E-01	4.001E+00	-7.934E+02	9.721E+01	1.722E+00	2.822E+01
3.080E-01	4.026E+00	-8.030E+02	9.880E+01	1.740E+00	2.839E+01
3.061E-01	4.051E+00	-8.131E+02	1.005E+02	1.759E+00	2.857E+01
3.042E-01	4.076E+00	-8.238E+02	1.029E+02	1.789E+00	2.876E+01
3.023E-01	4.102E+00	-8.343E+02	1.054E+02	1.820E+00	2.894E+01
3.003E-01	4.128E+00	-8.451E+02	1.072E+02	1.840E+00	2.913E+01
2.984E-01	4.155E+00	-8.564E+02	1.090E+02	1.859E+00	2.932E+01
2.965E-01	4.181E+00	-8.670E+02	1.117E+02	1.894E+00	2.951E+01
2.946E-01	4.209E+00	-8.757E+02	1.170E+02	1.972E+00	2.966E+01
2.927E-01	4.236E+00	-8.859E+02	1.231E+02	2.063E+00	2.984E+01
2.908E-01	4.264E+00	-8.981E+02	1.259E+02	2.096E+00	3.004E+01
2.889E-01	4.292E+00	-9.118E+02	1.269E+02	2.096E+00	3.027E+01
2.869E-01	4.321E+00	-9.261E+02	1.261E+02	2.068E+00	3.050E+01
2.850E-01	4.350E+00	-9.391E+02	1.259E+02	2.049E+00	3.071E+01
2.831E-01	4.379E+00	-9.516E+02	1.274E+02	2.061E+00	3.092E+01
2.812E-01	4.409E+00	-9.641E+02	1.295E+02	2.081E+00	3.112E+01
2.793E-01	4.439E+00	-9.773E+02	1.317E+02	2.102E+00	3.133E+01
2.774E-01	4.470E+00	-9.912E+02	1.341E+02	2.125E+00	3.156E+01
2.755E-01	4.501E+00	-1.005E+03	1.368E+02	2.153E+00	3.178E+01
2.736E-01	4.532E+00	-1.019E+03	1.401E+02	2.190E+00	3.199E+01
2.716E-01	4.564E+00	-1.033E+03	1.434E+02	2.225E+00	3.222E+01
2.697E-01	4.597E+00	-1.048E+03	1.459E+02	2.249E+00	3.245E+01
2.678E-01	4.629E+00	-1.061E+03	1.489E+02	2.281E+00	3.265E+01
2.659E-01	4.663E+00	-1.075E+03	1.524E+02	2.319E+00	3.286E+01
2.640E-01	4.697E+00	-1.091E+03	1.549E+02	2.339E+00	3.311E+01
2.621E-01	4.731E+00	-1.108E+03	1.576E+02	2.362E+00	3.336E+01
2.602E-01	4.766E+00	-1.124E+03	1.614E+02	2.401E+00	3.361E+01
2.583E-01	4.801E+00	-1.141E+03	1.653E+02	2.440E+00	3.387E+01
2.563E-01	4.837E+00	-1.158E+03	1.693E+02	2.481E+00	3.412E+01
2.544E-01	4.873E+00	-1.175E+03	1.730E+02	2.517E+00	3.438E+01
2.525E-01	4.910E+00	-1.193E+03	1.758E+02	2.538E+00	3.463E+01
2.506E-01	4.947E+00	-1.211E+03	1.789E+02	2.563E+00	3.489E+01
2.487E-01	4.986E+00	-1.230E+03	1.830E+02	2.602E+00	3.516E+01
2.468E-01	5.024E+00	-1.248E+03	1.877E+02	2.649E+00	3.543E+01
2.449E-01	5.063E+00	-1.267E+03	1.919E+02	2.689E+00	3.570E+01
2.429E-01	5.103E+00	-1.286E+03	1.953E+02	2.715E+00	3.597E+01
2.410E-01	5.144E+00	-1.306E+03	1.994E+02	2.751E+00	3.625E+01
2.391E-01	5.185E+00	-1.326E+03	2.054E+02	2.812E+00	3.652E+01
2.372E-01	5.227E+00	-1.347E+03	2.110E+02	2.866E+00	3.681E+01
2.353E-01	5.269E+00	-1.368E+03	2.155E+02	2.903E+00	3.711E+01
2.334E-01	5.312E+00	-1.391E+03	2.201E+02	2.943E+00	3.741E+01
2.315E-01	5.356E+00	-1.413E+03	2.247E+02	2.979E+00	3.771E+01
2.296E-01	5.401E+00	-1.435E+03	2.299E+02	3.025E+00	3.801E+01
2.276E-01	5.446E+00	-1.459E+03	2.369E+02	3.092E+00	3.832E+01
2.257E-01	5.493E+00	-1.484E+03	2.442E+02	3.160E+00	3.865E+01
2.238E-01	5.539E+00	-1.509E+03	2.497E+02	3.204E+00	3.898E+01
2.219E-01	5.587E+00	-1.534E+03	2.551E+02	3.245E+00	3.930E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.200E-01	5.636E+00	-1.559E+03	2.625E+02	3.312E+00	3.963E+01
2.181E-01	5.685E+00	-1.585E+03	2.717E+02	3.400E+00	3.996E+01
2.162E-01	5.736E+00	-1.610E+03	2.809E+02	3.487E+00	4.028E+01
2.143E-01	5.787E+00	-1.638E+03	2.879E+02	3.544E+00	4.062E+01
2.123E-01	5.839E+00	-1.667E+03	2.943E+02	3.590E+00	4.098E+01
2.104E-01	5.892E+00	-1.695E+03	3.008E+02	3.639E+00	4.134E+01
2.085E-01	5.946E+00	-1.724E+03	3.059E+02	3.669E+00	4.169E+01
2.066E-01	6.001E+00	-1.755E+03	3.126E+02	3.716E+00	4.206E+01
2.047E-01	6.057E+00	-1.792E+03	3.227E+02	3.796E+00	4.250E+01
2.028E-01	6.114E+00	-1.829E+03	3.333E+02	3.880E+00	4.294E+01
2.009E-01	6.173E+00	-1.862E+03	3.413E+02	3.938E+00	4.333E+01
1.990E-01	6.232E+00	-1.897E+03	3.489E+02	3.988E+00	4.374E+01
1.970E-01	6.292E+00	-1.934E+03	3.589E+02	4.064E+00	4.416E+01
1.951E-01	6.354E+00	-1.968E+03	3.717E+02	4.171E+00	4.456E+01
1.932E-01	6.417E+00	-2.003E+03	3.870E+02	4.304E+00	4.496E+01
1.913E-01	6.481E+00	-2.041E+03	3.992E+02	4.397E+00	4.540E+01
1.894E-01	6.547E+00	-2.081E+03	4.088E+02	4.460E+00	4.584E+01
1.875E-01	6.613E+00	-2.120E+03	4.214E+02	4.554E+00	4.627E+01
1.856E-01	6.682E+00	-2.163E+03	4.343E+02	4.646E+00	4.674E+01
1.836E-01	6.751E+00	-2.206E+03	4.481E+02	4.746E+00	4.721E+01
1.817E-01	6.822E+00	-2.249E+03	4.645E+02	4.871E+00	4.767E+01
1.798E-01	6.895E+00	-2.299E+03	4.803E+02	4.982E+00	4.821E+01
1.779E-01	6.969E+00	-2.345E+03	4.950E+02	5.082E+00	4.870E+01
1.760E-01	7.045E+00	-2.382E+03	5.096E+02	5.192E+00	4.909E+01
1.741E-01	7.122E+00	-2.433E+03	5.261E+02	5.302E+00	4.961E+01
1.722E-01	7.201E+00	-2.498E+03	5.445E+02	5.416E+00	5.028E+01
1.703E-01	7.282E+00	-2.550E+03	5.658E+02	5.568E+00	5.081E+01
1.683E-01	7.365E+00	-2.613E+03	5.953E+02	5.786E+00	5.145E+01
1.664E-01	7.450E+00	-2.672E+03	6.082E+02	5.846E+00	5.202E+01
1.645E-01	7.536E+00	-2.727E+03	6.145E+02	5.848E+00	5.254E+01
1.626E-01	7.625E+00	-2.787E+03	6.297E+02	5.926E+00	5.313E+01
1.607E-01	7.716E+00	-2.853E+03	6.545E+02	6.087E+00	5.376E+01
1.588E-01	7.809E+00	-2.920E+03	6.818E+02	6.266E+00	5.440E+01
1.569E-01	7.904E+00	-2.977E+03	7.076E+02	6.440E+00	5.494E+01
1.550E-01	8.001E+00	-3.040E+03	7.339E+02	6.608E+00	5.553E+01
1.530E-01	8.101E+00	-3.119E+03	7.598E+02	6.752E+00	5.626E+01
1.511E-01	8.204E+00	-3.203E+03	7.877E+02	6.908E+00	5.701E+01
1.492E-01	8.309E+00	-3.285E+03	8.235E+02	7.129E+00	5.775E+01
1.473E-01	8.417E+00	-3.368E+03	8.746E+02	7.474E+00	5.851E+01
1.454E-01	8.528E+00	-3.451E+03	9.120E+02	7.696E+00	5.925E+01
1.435E-01	8.642E+00	-3.535E+03	9.427E+02	7.859E+00	5.998E+01
1.416E-01	8.758E+00	-3.618E+03	9.985E+02	8.224E+00	6.071E+01
1.396E-01	8.878E+00	-3.697E+03	1.050E+03	8.551E+00	6.140E+01
1.377E-01	9.002E+00	-3.783E+03	1.083E+03	8.717E+00	6.212E+01
1.358E-01	9.128E+00	-3.885E+03	1.105E+03	8.779E+00	6.294E+01
1.339E-01	9.259E+00	-3.985E+03	1.133E+03	8.887E+00	6.375E+01
1.320E-01	9.393E+00	-4.084E+03	1.179E+03	9.134E+00	6.455E+01
1.301E-01	9.531E+00	-4.196E+03	1.222E+03	9.339E+00	6.545E+01
1.282E-01	9.673E+00	-4.329E+03	1.265E+03	9.516E+00	6.648E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample B
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.263E-01	9.820E+00	-4.467E+03	1.314E+03	9.728E+00	6.754E+01
1.243E-01	9.971E+00	-4.598E+03	1.359E+03	9.916E+00	6.853E+01
1.224E-01	1.013E+01	-4.724E+03	1.406E+03	1.012E+01	6.947E+01
1.205E-01	1.029E+01	-4.856E+03	1.451E+03	1.030E+01	7.044E+01
1.186E-01	1.045E+01	-5.000E+03	1.524E+03	1.066E+01	7.151E+01
1.167E-01	1.063E+01	-5.144E+03	1.639E+03	1.129E+01	7.261E+01
1.148E-01	1.080E+01	-5.293E+03	1.710E+03	1.160E+01	7.367E+01
1.129E-01	1.099E+01	-5.451E+03	1.760E+03	1.177E+01	7.476E+01
1.110E-01	1.117E+01	-5.605E+03	1.860E+03	1.226E+01	7.586E+01
1.090E-01	1.137E+01	-5.764E+03	1.976E+03	1.283E+01	7.700E+01
1.071E-01	1.157E+01	-5.959E+03	2.057E+03	1.313E+01	7.830E+01
1.052E-01	1.178E+01	-6.161E+03	2.132E+03	1.339E+01	7.962E+01
1.033E-01	1.200E+01	-6.345E+03	2.262E+03	1.399E+01	8.087E+01
1.014E-01	1.223E+01	-6.574E+03	2.385E+03	1.448E+01	8.237E+01
9.947E-02	1.246E+01	-6.831E+03	2.489E+03	1.482E+01	8.397E+01
9.756E-02	1.271E+01	-7.062E+03	2.643E+03	1.547E+01	8.545E+01
9.565E-02	1.296E+01	-7.324E+03	2.813E+03	1.615E+01	8.709E+01
9.374E-02	1.323E+01	-7.572E+03	3.037E+03	1.712E+01	8.868E+01
9.183E-02	1.350E+01	-7.769E+03	3.218E+03	1.789E+01	8.994E+01
8.991E-02	1.379E+01	-7.954E+03	3.351E+03	1.840E+01	9.106E+01
8.800E-02	1.409E+01	-8.225E+03	3.566E+03	1.923E+01	9.271E+01
8.608E-02	1.440E+01	-8.591E+03	3.745E+03	1.976E+01	9.477E+01
8.417E-02	1.473E+01	-8.930E+03	3.952E+03	2.044E+01	9.668E+01
8.226E-02	1.507E+01	-9.266E+03	4.196E+03	2.128E+01	9.859E+01
8.035E-02	1.543E+01	-9.594E+03	4.330E+03	2.159E+01	1.003E+02
7.843E-02	1.581E+01	-1.003E+04	4.430E+03	2.162E+01	1.025E+02
7.652E-02	1.620E+01	-1.049E+04	4.795E+03	2.284E+01	1.050E+02
7.461E-02	1.662E+01	-1.092E+04	5.218E+03	2.432E+01	1.073E+02
7.269E-02	1.706E+01	-1.141E+04	5.424E+03	2.474E+01	1.096E+02
7.078E-02	1.752E+01	-1.188E+04	5.620E+03	2.512E+01	1.119E+02
6.887E-02	1.800E+01	-1.242E+04	5.843E+03	2.555E+01	1.143E+02
6.696E-02	1.852E+01	-1.310E+04	5.998E+03	2.558E+01	1.173E+02
6.504E-02	1.906E+01	-1.382E+04	6.391E+03	2.651E+01	1.205E+02
6.313E-02	1.964E+01	-1.435E+04	7.097E+03	2.880E+01	1.232E+02
6.121E-02	2.025E+01	-1.476E+04	7.785E+03	3.104E+01	1.254E+02
5.930E-02	2.091E+01	-1.544E+04	8.427E+03	3.279E+01	1.285E+02
5.739E-02	2.160E+01	-1.629E+04	9.110E+03	3.445E+01	1.322E+02
5.548E-02	2.235E+01	-1.744E+04	9.418E+03	3.450E+01	1.365E+02
5.356E-02	2.315E+01	-1.804E+04	1.028E+04	3.688E+01	1.393E+02
5.165E-02	2.400E+01	-1.839E+04	1.163E+04	4.103E+01	1.417E+02
4.974E-02	2.493E+01	-1.995E+04	1.225E+04	4.159E+01	1.472E+02