

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.592E+00	2.700E-01	1.645E-01	3.757E+00	1.401E+00	1.341E+00
4.428E+00	2.800E-01	5.137E-01	3.715E+00	1.460E+00	1.272E+00
4.275E+00	2.900E-01	9.853E-01	3.551E+00	1.528E+00	1.162E+00
4.133E+00	3.000E-01	1.696E+00	2.906E+00	1.591E+00	9.134E-01
3.999E+00	3.100E-01	1.622E+00	1.392E+00	1.371E+00	5.076E-01
3.875E+00	3.200E-01	5.611E-01	5.259E-01	8.155E-01	3.225E-01
3.757E+00	3.300E-01	-3.921E-01	2.714E-01	2.059E-01	6.592E-01
3.647E+00	3.400E-01	-1.126E+00	2.769E-01	1.296E-01	1.069E+00
3.542E+00	3.500E-01	-1.699E+00	2.742E-01	1.048E-01	1.308E+00
3.444E+00	3.600E-01	-2.248E+00	2.659E-01	8.852E-02	1.502E+00
3.351E+00	3.700E-01	-2.774E+00	2.594E-01	7.777E-02	1.667E+00
3.263E+00	3.800E-01	-3.283E+00	2.601E-01	7.172E-02	1.813E+00
3.179E+00	3.900E-01	-3.776E+00	2.624E-01	6.747E-02	1.944E+00
3.100E+00	4.000E-01	-4.272E+00	2.651E-01	6.409E-02	2.068E+00
3.024E+00	4.100E-01	-4.766E+00	2.695E-01	6.171E-02	2.184E+00
2.952E+00	4.200E-01	-5.264E+00	2.744E-01	5.978E-02	2.295E+00
2.883E+00	4.300E-01	-5.767E+00	2.778E-01	5.783E-02	2.402E+00
2.818E+00	4.400E-01	-6.273E+00	2.835E-01	5.657E-02	2.505E+00
2.755E+00	4.500E-01	-6.784E+00	2.957E-01	5.675E-02	2.605E+00
2.695E+00	4.600E-01	-7.310E+00	3.037E-01	5.615E-02	2.704E+00
2.638E+00	4.700E-01	-7.835E+00	3.154E-01	5.633E-02	2.800E+00
2.583E+00	4.800E-01	-8.375E+00	3.258E-01	5.629E-02	2.895E+00
2.530E+00	4.900E-01	-8.921E+00	3.394E-01	5.681E-02	2.987E+00
2.480E+00	5.000E-01	-9.471E+00	3.517E-01	5.712E-02	3.078E+00
2.431E+00	5.100E-01	-1.003E+01	3.676E-01	5.801E-02	3.168E+00
2.384E+00	5.200E-01	-1.060E+01	3.781E-01	5.807E-02	3.256E+00
2.339E+00	5.300E-01	-1.118E+01	3.984E-01	5.958E-02	3.344E+00
2.296E+00	5.400E-01	-1.176E+01	4.129E-01	6.019E-02	3.430E+00
2.254E+00	5.500E-01	-1.236E+01	4.292E-01	6.105E-02	3.516E+00
2.214E+00	5.600E-01	-1.297E+01	4.469E-01	6.203E-02	3.602E+00
2.175E+00	5.700E-01	-1.359E+01	4.624E-01	6.271E-02	3.687E+00
2.138E+00	5.800E-01	-1.421E+01	4.846E-01	6.427E-02	3.770E+00
2.101E+00	5.900E-01	-1.485E+01	5.070E-01	6.577E-02	3.854E+00
2.066E+00	6.000E-01	-1.549E+01	5.223E-01	6.636E-02	3.936E+00
2.033E+00	6.100E-01	-1.614E+01	5.450E-01	6.782E-02	4.018E+00
2.000E+00	6.200E-01	-1.680E+01	5.635E-01	6.872E-02	4.100E+00
1.968E+00	6.300E-01	-1.747E+01	5.845E-01	6.991E-02	4.181E+00
1.937E+00	6.400E-01	-1.815E+01	6.080E-01	7.134E-02	4.261E+00
1.907E+00	6.500E-01	-1.885E+01	6.328E-01	7.287E-02	4.342E+00
1.879E+00	6.600E-01	-1.955E+01	6.488E-01	7.336E-02	4.422E+00
1.851E+00	6.700E-01	-2.026E+01	6.739E-01	7.484E-02	4.502E+00
1.823E+00	6.800E-01	-2.100E+01	6.979E-01	7.613E-02	4.583E+00
1.797E+00	6.900E-01	-2.172E+01	7.172E-01	7.694E-02	4.661E+00
1.771E+00	7.000E-01	-2.247E+01	7.373E-01	7.777E-02	4.741E+00
1.746E+00	7.100E-01	-2.324E+01	7.732E-01	8.019E-02	4.821E+00
1.722E+00	7.200E-01	-2.398E+01	7.968E-01	8.134E-02	4.898E+00
1.698E+00	7.300E-01	-2.477E+01	8.137E-01	8.173E-02	4.978E+00
1.675E+00	7.400E-01	-2.555E+01	8.397E-01	8.305E-02	5.055E+00
1.653E+00	7.500E-01	-2.636E+01	8.659E-01	8.432E-02	5.135E+00
1.631E+00	7.600E-01	-2.717E+01	9.023E-01	8.655E-02	5.213E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.610E+00	7.700E-01	-2.798E+01	9.365E-01	8.851E-02	5.290E+00
1.590E+00	7.800E-01	-2.879E+01	9.714E-01	9.052E-02	5.366E+00
1.569E+00	7.900E-01	-2.962E+01	9.910E-01	9.102E-02	5.444E+00
1.550E+00	8.000E-01	-3.048E+01	1.026E+00	9.290E-02	5.522E+00
1.531E+00	8.100E-01	-3.135E+01	1.077E+00	9.619E-02	5.600E+00
1.512E+00	8.200E-01	-3.232E+01	1.055E+00	9.278E-02	5.686E+00
1.494E+00	8.300E-01	-3.309E+01	1.085E+00	9.426E-02	5.753E+00
1.476E+00	8.400E-01	-3.400E+01	1.133E+00	9.716E-02	5.832E+00
1.459E+00	8.500E-01	-3.519E+01	1.143E+00	9.630E-02	5.933E+00
1.442E+00	8.600E-01	-3.613E+01	1.181E+00	9.825E-02	6.012E+00
1.425E+00	8.700E-01	-3.709E+01	1.222E+00	1.003E-01	6.091E+00
1.409E+00	8.800E-01	-3.793E+01	1.244E+00	1.010E-01	6.160E+00
1.393E+00	8.900E-01	-3.906E+01	1.286E+00	1.029E-01	6.250E+00
1.378E+00	9.000E-01	-4.004E+01	1.320E+00	1.043E-01	6.328E+00
1.362E+00	9.100E-01	-4.109E+01	1.363E+00	1.063E-01	6.411E+00
1.348E+00	9.200E-01	-4.166E+01	1.386E+00	1.074E-01	6.456E+00
1.333E+00	9.300E-01	-4.283E+01	1.431E+00	1.093E-01	6.546E+00
1.319E+00	9.400E-01	-4.379E+01	1.468E+00	1.109E-01	6.618E+00
1.305E+00	9.500E-01	-4.477E+01	1.510E+00	1.129E-01	6.692E+00
1.292E+00	9.600E-01	-4.585E+01	1.560E+00	1.152E-01	6.772E+00
1.278E+00	9.700E-01	-4.694E+01	1.609E+00	1.174E-01	6.852E+00
1.265E+00	9.800E-01	-4.771E+01	1.643E+00	1.189E-01	6.908E+00
1.252E+00	9.900E-01	-4.898E+01	1.697E+00	1.212E-01	6.999E+00
1.240E+00	1.000E+00	-5.001E+01	1.741E+00	1.231E-01	7.073E+00
1.228E+00	1.010E+00	-5.115E+01	1.789E+00	1.251E-01	7.153E+00
1.216E+00	1.020E+00	-5.213E+01	1.841E+00	1.275E-01	7.221E+00
1.204E+00	1.030E+00	-5.330E+01	1.894E+00	1.297E-01	7.302E+00
1.192E+00	1.040E+00	-5.436E+01	1.937E+00	1.313E-01	7.374E+00
1.181E+00	1.050E+00	-5.551E+01	1.996E+00	1.339E-01	7.452E+00
1.170E+00	1.060E+00	-5.661E+01	2.053E+00	1.364E-01	7.525E+00
1.159E+00	1.070E+00	-5.779E+01	2.091E+00	1.375E-01	7.604E+00
1.148E+00	1.080E+00	-5.900E+01	2.158E+00	1.405E-01	7.683E+00
1.137E+00	1.090E+00	-5.996E+01	2.220E+00	1.433E-01	7.745E+00
1.127E+00	1.100E+00	-6.128E+01	2.296E+00	1.466E-01	7.829E+00
1.117E+00	1.110E+00	-6.245E+01	2.334E+00	1.477E-01	7.904E+00
1.107E+00	1.120E+00	-6.357E+01	2.393E+00	1.500E-01	7.975E+00
1.097E+00	1.130E+00	-6.485E+01	2.462E+00	1.528E-01	8.055E+00
1.088E+00	1.140E+00	-6.607E+01	2.535E+00	1.559E-01	8.130E+00
1.078E+00	1.150E+00	-6.728E+01	2.610E+00	1.590E-01	8.204E+00
1.069E+00	1.160E+00	-6.857E+01	2.675E+00	1.615E-01	8.282E+00
1.060E+00	1.170E+00	-6.998E+01	2.738E+00	1.636E-01	8.367E+00
1.051E+00	1.180E+00	-7.096E+01	2.777E+00	1.648E-01	8.425E+00
1.042E+00	1.190E+00	-7.224E+01	2.843E+00	1.672E-01	8.501E+00
1.033E+00	1.200E+00	-7.356E+01	2.919E+00	1.702E-01	8.578E+00
1.025E+00	1.210E+00	-7.484E+01	3.028E+00	1.750E-01	8.653E+00
1.016E+00	1.220E+00	-7.622E+01	3.071E+00	1.758E-01	8.732E+00
1.008E+00	1.230E+00	-7.741E+01	3.145E+00	1.787E-01	8.800E+00
9.999E-01	1.240E+00	-7.878E+01	3.218E+00	1.813E-01	8.878E+00
9.919E-01	1.250E+00	-8.012E+01	3.281E+00	1.833E-01	8.953E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.840E-01	1.260E+00	-8.172E+01	3.356E+00	1.856E-01	9.042E+00
9.763E-01	1.270E+00	-8.274E+01	3.404E+00	1.871E-01	9.098E+00
9.686E-01	1.280E+00	-8.414E+01	3.577E+00	1.949E-01	9.175E+00
9.611E-01	1.290E+00	-8.558E+01	3.643E+00	1.969E-01	9.253E+00
9.537E-01	1.300E+00	-8.704E+01	3.761E+00	2.015E-01	9.332E+00
9.464E-01	1.310E+00	-8.841E+01	3.781E+00	2.010E-01	9.405E+00
9.393E-01	1.320E+00	-8.985E+01	3.861E+00	2.036E-01	9.481E+00
9.322E-01	1.330E+00	-9.117E+01	3.930E+00	2.057E-01	9.551E+00
9.253E-01	1.340E+00	-9.272E+01	3.998E+00	2.076E-01	9.632E+00
9.184E-01	1.350E+00	-9.413E+01	4.201E+00	2.164E-01	9.705E+00
8.670E-01	1.430E+00	-1.060E+02	4.891E+00	2.375E-01	1.030E+01
8.610E-01	1.440E+00	-1.076E+02	5.038E+00	2.427E-01	1.038E+01
8.551E-01	1.450E+00	-1.091E+02	5.279E+00	2.526E-01	1.045E+01
8.492E-01	1.460E+00	-1.107E+02	5.300E+00	2.518E-01	1.052E+01
8.434E-01	1.470E+00	-1.126E+02	5.214E+00	2.456E-01	1.062E+01
8.377E-01	1.480E+00	-1.137E+02	5.283E+00	2.476E-01	1.067E+01
8.321E-01	1.490E+00	-1.154E+02	5.652E+00	2.630E-01	1.074E+01
8.266E-01	1.500E+00	-1.171E+02	5.900E+00	2.725E-01	1.083E+01
8.211E-01	1.510E+00	-1.188E+02	5.786E+00	2.653E-01	1.090E+01
8.157E-01	1.520E+00	-1.202E+02	6.052E+00	2.759E-01	1.097E+01
8.104E-01	1.530E+00	-1.219E+02	6.074E+00	2.750E-01	1.105E+01
8.051E-01	1.540E+00	-1.238E+02	6.068E+00	2.726E-01	1.113E+01
7.999E-01	1.550E+00	-1.251E+02	6.257E+00	2.796E-01	1.119E+01
7.948E-01	1.560E+00	-1.267E+02	6.468E+00	2.872E-01	1.126E+01
7.897E-01	1.570E+00	-1.287E+02	6.578E+00	2.898E-01	1.135E+01
7.847E-01	1.580E+00	-1.301E+02	6.705E+00	2.938E-01	1.141E+01
7.798E-01	1.590E+00	-1.318E+02	6.775E+00	2.950E-01	1.148E+01
7.749E-01	1.600E+00	-1.337E+02	6.900E+00	2.983E-01	1.157E+01
7.701E-01	1.610E+00	-1.352E+02	6.876E+00	2.955E-01	1.163E+01
7.653E-01	1.620E+00	-1.370E+02	7.070E+00	3.019E-01	1.171E+01
7.606E-01	1.630E+00	-1.386E+02	7.327E+00	3.110E-01	1.178E+01
7.560E-01	1.640E+00	-1.405E+02	7.432E+00	3.134E-01	1.186E+01
7.514E-01	1.650E+00	-1.421E+02	7.539E+00	3.161E-01	1.193E+01
7.469E-01	1.660E+00	-1.439E+02	7.632E+00	3.180E-01	1.200E+01
7.424E-01	1.670E+00	-1.460E+02	7.886E+00	3.262E-01	1.209E+01
7.380E-01	1.680E+00	-1.475E+02	7.802E+00	3.211E-01	1.215E+01
7.336E-01	1.690E+00	-1.494E+02	7.993E+00	3.269E-01	1.223E+01
7.293E-01	1.700E+00	-1.513E+02	8.194E+00	3.330E-01	1.230E+01
7.251E-01	1.710E+00	-1.533E+02	8.400E+00	3.390E-01	1.239E+01
7.208E-01	1.720E+00	-1.548E+02	8.690E+00	3.491E-01	1.245E+01
7.167E-01	1.730E+00	-1.568E+02	8.691E+00	3.469E-01	1.253E+01
7.126E-01	1.740E+00	-1.591E+02	8.957E+00	3.550E-01	1.262E+01
7.085E-01	1.750E+00	-1.603E+02	9.103E+00	3.593E-01	1.267E+01
7.045E-01	1.760E+00	-1.624E+02	8.959E+00	3.514E-01	1.275E+01
7.005E-01	1.770E+00	-1.643E+02	9.455E+00	3.687E-01	1.282E+01
6.965E-01	1.780E+00	-1.662E+02	9.768E+00	3.787E-01	1.290E+01
6.926E-01	1.790E+00	-1.682E+02	9.810E+00	3.781E-01	1.297E+01
6.888E-01	1.800E+00	-1.702E+02	1.033E+01	3.958E-01	1.305E+01
6.850E-01	1.810E+00	-1.723E+02	1.019E+01	3.879E-01	1.313E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.812E-01	1.820E+00	-1.746E+02	1.021E+01	3.861E-01	1.322E+01
6.775E-01	1.830E+00	-1.761E+02	1.054E+01	3.971E-01	1.328E+01
6.738E-01	1.840E+00	-1.785E+02	1.057E+01	3.955E-01	1.337E+01
6.702E-01	1.850E+00	-1.798E+02	1.107E+01	4.125E-01	1.342E+01
6.666E-01	1.860E+00	-1.823E+02	1.092E+01	4.042E-01	1.351E+01
6.630E-01	1.870E+00	-1.845E+02	1.152E+01	4.237E-01	1.359E+01
6.595E-01	1.880E+00	-1.865E+02	1.143E+01	4.181E-01	1.366E+01
6.560E-01	1.890E+00	-1.883E+02	1.156E+01	4.210E-01	1.373E+01
6.525E-01	1.900E+00	-1.900E+02	1.185E+01	4.295E-01	1.379E+01
6.491E-01	1.910E+00	-1.923E+02	1.207E+01	4.351E-01	1.387E+01
6.458E-01	1.920E+00	-1.946E+02	1.206E+01	4.319E-01	1.396E+01
6.424E-01	1.930E+00	-1.967E+02	1.231E+01	4.385E-01	1.403E+01
6.391E-01	1.940E+00	-1.976E+02	1.204E+01	4.282E-01	1.406E+01
6.358E-01	1.950E+00	-2.011E+02	1.291E+01	4.550E-01	1.419E+01
6.326E-01	1.960E+00	-2.033E+02	1.300E+01	4.558E-01	1.427E+01
6.294E-01	1.970E+00	-2.050E+02	1.353E+01	4.722E-01	1.433E+01
6.262E-01	1.980E+00	-2.082E+02	1.336E+01	4.627E-01	1.444E+01
6.230E-01	1.990E+00	-2.093E+02	1.355E+01	4.680E-01	1.448E+01
6.199E-01	2.000E+00	-2.113E+02	1.387E+01	4.768E-01	1.454E+01
-	-	-	-	-	-
-	-	-	-	-	-
7.269E-01	1.706E+00	-1.372E+02	6.844E+00	2.921E-01	1.172E+01
7.212E-01	1.719E+00	-1.398E+02	6.801E+00	2.875E-01	1.183E+01
7.174E-01	1.728E+00	-1.414E+02	6.833E+00	2.873E-01	1.189E+01
7.135E-01	1.738E+00	-1.427E+02	6.989E+00	2.925E-01	1.195E+01
7.097E-01	1.747E+00	-1.445E+02	7.433E+00	3.091E-01	1.203E+01
7.059E-01	1.756E+00	-1.464E+02	7.822E+00	3.231E-01	1.210E+01
7.021E-01	1.766E+00	-1.480E+02	7.814E+00	3.211E-01	1.217E+01
6.982E-01	1.776E+00	-1.491E+02	7.767E+00	3.179E-01	1.222E+01
6.944E-01	1.785E+00	-1.507E+02	7.826E+00	3.187E-01	1.228E+01
6.906E-01	1.795E+00	-1.522E+02	7.787E+00	3.155E-01	1.234E+01
6.868E-01	1.805E+00	-1.539E+02	8.084E+00	3.257E-01	1.241E+01
6.830E-01	1.815E+00	-1.557E+02	8.431E+00	3.377E-01	1.248E+01
6.791E-01	1.826E+00	-1.580E+02	8.314E+00	3.306E-01	1.258E+01
6.753E-01	1.836E+00	-1.605E+02	8.048E+00	3.175E-01	1.267E+01
6.715E-01	1.847E+00	-1.620E+02	7.952E+00	3.123E-01	1.273E+01
6.676E-01	1.857E+00	-1.632E+02	8.160E+00	3.192E-01	1.278E+01
6.638E-01	1.868E+00	-1.650E+02	8.678E+00	3.376E-01	1.285E+01
6.600E-01	1.879E+00	-1.672E+02	9.219E+00	3.563E-01	1.294E+01
6.562E-01	1.890E+00	-1.691E+02	9.248E+00	3.554E-01	1.301E+01
6.524E-01	1.895E+00	-1.702E+02	9.098E+00	3.486E-01	1.305E+01
6.504E-01	1.906E+00	-1.728E+02	9.051E+00	3.442E-01	1.315E+01
6.466E-01	1.918E+00	-1.751E+02	9.480E+00	3.581E-01	1.324E+01
6.428E-01	1.929E+00	-1.764E+02	9.815E+00	3.693E-01	1.329E+01
6.408E-01	1.935E+00	-1.774E+02	9.931E+00	3.727E-01	1.332E+01
6.370E-01	1.946E+00	-1.802E+02	9.965E+00	3.710E-01	1.343E+01
6.332E-01	1.958E+00	-1.823E+02	9.946E+00	3.682E-01	1.351E+01
6.294E-01	1.970E+00	-1.843E+02	1.050E+01	3.865E-01	1.358E+01
6.274E-01	1.976E+00	-1.852E+02	1.067E+01	3.918E-01	1.362E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.236E-01	1.988E+00	-1.878E+02	1.050E+01	3.828E-01	1.371E+01
6.217E-01	1.994E+00	-1.889E+02	1.040E+01	3.781E-01	1.375E+01
6.179E-01	2.007E+00	-1.912E+02	1.053E+01	3.807E-01	1.383E+01
6.141E-01	2.019E+00	-1.940E+02	1.056E+01	3.789E-01	1.393E+01
6.121E-01	2.025E+00	-1.954E+02	1.050E+01	3.756E-01	1.398E+01
6.083E-01	2.038E+00	-1.975E+02	1.060E+01	3.771E-01	1.406E+01
6.064E-01	2.045E+00	-1.985E+02	1.090E+01	3.866E-01	1.410E+01
6.026E-01	2.058E+00	-2.015E+02	1.167E+01	4.111E-01	1.420E+01
6.007E-01	2.064E+00	-2.031E+02	1.184E+01	4.152E-01	1.426E+01
5.969E-01	2.077E+00	-2.057E+02	1.173E+01	4.088E-01	1.435E+01
5.949E-01	2.084E+00	-2.066E+02	1.182E+01	4.109E-01	1.438E+01
5.911E-01	2.098E+00	-2.093E+02	1.253E+01	4.329E-01	1.448E+01
5.892E-01	2.104E+00	-2.112E+02	1.287E+01	4.425E-01	1.454E+01
5.854E-01	2.118E+00	-2.138E+02	1.295E+01	4.426E-01	1.463E+01
5.835E-01	2.125E+00	-2.151E+02	1.278E+01	4.356E-01	1.467E+01
5.796E-01	2.139E+00	-2.179E+02	1.268E+01	4.292E-01	1.477E+01
5.777E-01	2.146E+00	-2.192E+02	1.282E+01	4.328E-01	1.481E+01
5.758E-01	2.153E+00	-2.206E+02	1.302E+01	4.382E-01	1.486E+01
5.720E-01	2.168E+00	-2.232E+02	1.346E+01	4.504E-01	1.495E+01
5.701E-01	2.175E+00	-2.247E+02	1.368E+01	4.561E-01	1.500E+01
5.662E-01	2.190E+00	-2.281E+02	1.418E+01	4.693E-01	1.511E+01
5.643E-01	2.197E+00	-2.302E+02	1.449E+01	4.774E-01	1.518E+01
5.624E-01	2.205E+00	-2.321E+02	1.466E+01	4.808E-01	1.524E+01
5.586E-01	2.220E+00	-2.352E+02	1.466E+01	4.777E-01	1.534E+01
5.567E-01	2.227E+00	-2.368E+02	1.487E+01	4.828E-01	1.540E+01
5.548E-01	2.235E+00	-2.384E+02	1.511E+01	4.890E-01	1.545E+01
5.529E-01	2.243E+00	-2.401E+02	1.532E+01	4.942E-01	1.550E+01
5.490E-01	2.258E+00	-2.425E+02	1.559E+01	5.002E-01	1.558E+01
5.471E-01	2.266E+00	-2.442E+02	1.583E+01	5.064E-01	1.563E+01
5.452E-01	2.274E+00	-2.463E+02	1.626E+01	5.178E-01	1.570E+01
5.433E-01	2.282E+00	-2.483E+02	1.672E+01	5.303E-01	1.577E+01
5.395E-01	2.298E+00	-2.525E+02	1.753E+01	5.513E-01	1.590E+01
5.375E-01	2.307E+00	-2.543E+02	1.768E+01	5.541E-01	1.596E+01
5.356E-01	2.315E+00	-2.560E+02	1.764E+01	5.509E-01	1.601E+01
5.337E-01	2.323E+00	-2.579E+02	1.774E+01	5.518E-01	1.607E+01
5.299E-01	2.340E+00	-2.614E+02	1.808E+01	5.587E-01	1.618E+01
5.280E-01	2.348E+00	-2.634E+02	1.813E+01	5.582E-01	1.624E+01
5.261E-01	2.357E+00	-2.655E+02	1.837E+01	5.635E-01	1.630E+01
5.242E-01	2.365E+00	-2.674E+02	1.862E+01	5.691E-01	1.636E+01
5.223E-01	2.374E+00	-2.693E+02	1.863E+01	5.674E-01	1.642E+01
5.203E-01	2.383E+00	-2.715E+02	1.849E+01	5.607E-01	1.649E+01
5.184E-01	2.392E+00	-2.738E+02	1.836E+01	5.546E-01	1.656E+01
5.146E-01	2.409E+00	-2.781E+02	1.867E+01	5.595E-01	1.669E+01
5.127E-01	2.418E+00	-2.806E+02	1.911E+01	5.700E-01	1.676E+01
5.108E-01	2.427E+00	-2.827E+02	1.931E+01	5.739E-01	1.682E+01
5.089E-01	2.437E+00	-2.850E+02	1.926E+01	5.703E-01	1.689E+01
5.069E-01	2.446E+00	-2.873E+02	1.943E+01	5.729E-01	1.696E+01
5.050E-01	2.455E+00	-2.892E+02	1.983E+01	5.826E-01	1.702E+01
5.031E-01	2.464E+00	-2.914E+02	2.026E+01	5.931E-01	1.708E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
5.012E-01	2.474E+00	-2.941E+02	2.088E+01	6.083E-01	1.716E+01
4.993E-01	2.483E+00	-2.967E+02	2.157E+01	6.257E-01	1.724E+01
4.974E-01	2.493E+00	-2.988E+02	2.192E+01	6.337E-01	1.730E+01
4.955E-01	2.502E+00	-3.007E+02	2.193E+01	6.318E-01	1.735E+01
4.935E-01	2.512E+00	-3.029E+02	2.189E+01	6.283E-01	1.742E+01
4.916E-01	2.522E+00	-3.058E+02	2.201E+01	6.290E-01	1.750E+01
4.897E-01	2.532E+00	-3.088E+02	2.232E+01	6.348E-01	1.758E+01
4.878E-01	2.542E+00	-3.112E+02	2.269E+01	6.426E-01	1.765E+01
4.859E-01	2.552E+00	-3.137E+02	2.311E+01	6.520E-01	1.772E+01
4.840E-01	2.562E+00	-3.164E+02	2.358E+01	6.623E-01	1.780E+01
4.821E-01	2.572E+00	-3.190E+02	2.399E+01	6.711E-01	1.787E+01
4.802E-01	2.582E+00	-3.216E+02	2.439E+01	6.794E-01	1.795E+01
4.782E-01	2.593E+00	-3.244E+02	2.481E+01	6.882E-01	1.802E+01
4.763E-01	2.603E+00	-3.269E+02	2.512E+01	6.941E-01	1.809E+01
4.744E-01	2.613E+00	-3.297E+02	2.541E+01	6.991E-01	1.817E+01
4.725E-01	2.624E+00	-3.330E+02	2.578E+01	7.057E-01	1.826E+01
4.706E-01	2.635E+00	-3.359E+02	2.613E+01	7.123E-01	1.834E+01
4.687E-01	2.645E+00	-3.382E+02	2.643E+01	7.181E-01	1.840E+01
4.668E-01	2.656E+00	-3.406E+02	2.687E+01	7.273E-01	1.847E+01
4.649E-01	2.667E+00	-3.439E+02	2.745E+01	7.395E-01	1.856E+01
4.629E-01	2.678E+00	-3.470E+02	2.785E+01	7.468E-01	1.864E+01
4.610E-01	2.689E+00	-3.498E+02	2.802E+01	7.486E-01	1.872E+01
4.591E-01	2.701E+00	-3.527E+02	2.823E+01	7.510E-01	1.880E+01
4.572E-01	2.712E+00	-3.557E+02	2.859E+01	7.574E-01	1.888E+01
4.553E-01	2.723E+00	-3.587E+02	2.907E+01	7.667E-01	1.896E+01
4.534E-01	2.735E+00	-3.616E+02	2.953E+01	7.757E-01	1.903E+01
4.515E-01	2.746E+00	-3.643E+02	2.982E+01	7.806E-01	1.910E+01
4.496E-01	2.758E+00	-3.671E+02	2.999E+01	7.821E-01	1.918E+01
4.476E-01	2.770E+00	-3.703E+02	3.022E+01	7.845E-01	1.926E+01
4.457E-01	2.782E+00	-3.739E+02	3.066E+01	7.922E-01	1.935E+01
4.438E-01	2.794E+00	-3.776E+02	3.121E+01	8.025E-01	1.945E+01
4.419E-01	2.806E+00	-3.812E+02	3.170E+01	8.111E-01	1.954E+01
4.400E-01	2.818E+00	-3.845E+02	3.220E+01	8.203E-01	1.963E+01
4.381E-01	2.830E+00	-3.876E+02	3.257E+01	8.263E-01	1.971E+01
4.362E-01	2.843E+00	-3.908E+02	3.262E+01	8.242E-01	1.979E+01
4.343E-01	2.855E+00	-3.945E+02	3.251E+01	8.176E-01	1.988E+01
4.323E-01	2.868E+00	-3.981E+02	3.286E+01	8.226E-01	1.997E+01
4.304E-01	2.881E+00	-4.017E+02	3.383E+01	8.432E-01	2.006E+01
4.285E-01	2.893E+00	-4.052E+02	3.474E+01	8.620E-01	2.015E+01
4.266E-01	2.906E+00	-4.088E+02	3.540E+01	8.746E-01	2.024E+01
4.247E-01	2.919E+00	-4.122E+02	3.617E+01	8.899E-01	2.032E+01
4.228E-01	2.933E+00	-4.159E+02	3.703E+01	9.071E-01	2.041E+01
4.209E-01	2.946E+00	-4.198E+02	3.758E+01	9.160E-01	2.051E+01
4.189E-01	2.959E+00	-4.239E+02	3.788E+01	9.189E-01	2.061E+01
4.170E-01	2.973E+00	-4.278E+02	3.816E+01	9.216E-01	2.070E+01
4.151E-01	2.987E+00	-4.313E+02	3.834E+01	9.221E-01	2.079E+01
4.132E-01	3.001E+00	-4.352E+02	3.871E+01	9.267E-01	2.088E+01
4.113E-01	3.015E+00	-4.395E+02	3.917E+01	9.332E-01	2.098E+01
4.094E-01	3.029E+00	-4.437E+02	3.933E+01	9.328E-01	2.108E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.075E-01	3.043E+00	-4.478E+02	3.975E+01	9.384E-01	2.118E+01
4.056E-01	3.057E+00	-4.522E+02	4.063E+01	9.545E-01	2.129E+01
4.036E-01	3.072E+00	-4.565E+02	4.153E+01	9.709E-01	2.139E+01
4.017E-01	3.086E+00	-4.608E+02	4.240E+01	9.865E-01	2.149E+01
3.998E-01	3.101E+00	-4.654E+02	4.319E+01	1.000E+00	2.160E+01
3.979E-01	3.116E+00	-4.703E+02	4.364E+01	1.005E+00	2.171E+01
3.960E-01	3.131E+00	-4.752E+02	4.360E+01	9.990E-01	2.182E+01
3.941E-01	3.146E+00	-4.799E+02	4.361E+01	9.943E-01	2.193E+01
3.922E-01	3.162E+00	-4.844E+02	4.425E+01	1.004E+00	2.203E+01
3.903E-01	3.177E+00	-4.894E+02	4.537E+01	1.024E+00	2.215E+01
3.883E-01	3.193E+00	-4.948E+02	4.643E+01	1.043E+00	2.227E+01
3.864E-01	3.209E+00	-5.002E+02	4.713E+01	1.053E+00	2.239E+01
3.845E-01	3.224E+00	-5.056E+02	4.804E+01	1.067E+00	2.251E+01
3.826E-01	3.241E+00	-5.107E+02	4.929E+01	1.089E+00	2.262E+01
3.807E-01	3.257E+00	-5.155E+02	4.997E+01	1.099E+00	2.273E+01
3.788E-01	3.273E+00	-5.204E+02	5.040E+01	1.103E+00	2.284E+01
3.769E-01	3.290E+00	-5.256E+02	5.138E+01	1.119E+00	2.295E+01
3.749E-01	3.307E+00	-5.311E+02	5.222E+01	1.132E+00	2.307E+01
3.730E-01	3.324E+00	-5.366E+02	5.259E+01	1.134E+00	2.319E+01
3.711E-01	3.341E+00	-5.424E+02	5.317E+01	1.140E+00	2.332E+01
3.692E-01	3.358E+00	-5.484E+02	5.411E+01	1.154E+00	2.345E+01
3.673E-01	3.376E+00	-5.542E+02	5.518E+01	1.171E+00	2.357E+01
3.654E-01	3.393E+00	-5.600E+02	5.632E+01	1.188E+00	2.369E+01
3.635E-01	3.411E+00	-5.651E+02	5.749E+01	1.208E+00	2.380E+01
3.616E-01	3.429E+00	-5.704E+02	5.849E+01	1.223E+00	2.392E+01
3.596E-01	3.447E+00	-5.767E+02	5.919E+01	1.231E+00	2.405E+01
3.577E-01	3.466E+00	-5.832E+02	5.975E+01	1.235E+00	2.418E+01
3.558E-01	3.485E+00	-5.895E+02	6.040E+01	1.242E+00	2.431E+01
3.539E-01	3.503E+00	-5.958E+02	6.158E+01	1.260E+00	2.444E+01
3.520E-01	3.522E+00	-6.023E+02	6.272E+01	1.276E+00	2.457E+01
3.501E-01	3.542E+00	-6.088E+02	6.332E+01	1.281E+00	2.471E+01
3.482E-01	3.561E+00	-6.157E+02	6.404E+01	1.289E+00	2.485E+01
3.463E-01	3.581E+00	-6.230E+02	6.491E+01	1.299E+00	2.499E+01
3.443E-01	3.601E+00	-6.301E+02	6.602E+01	1.313E+00	2.514E+01
3.424E-01	3.621E+00	-6.374E+02	6.700E+01	1.325E+00	2.528E+01
3.405E-01	3.641E+00	-6.449E+02	6.748E+01	1.327E+00	2.543E+01
3.386E-01	3.662E+00	-6.521E+02	6.842E+01	1.338E+00	2.557E+01
3.367E-01	3.683E+00	-6.593E+02	6.978E+01	1.357E+00	2.571E+01
3.348E-01	3.704E+00	-6.673E+02	7.102E+01	1.373E+00	2.587E+01
3.329E-01	3.725E+00	-6.754E+02	7.190E+01	1.381E+00	2.603E+01
3.310E-01	3.746E+00	-6.834E+02	7.282E+01	1.391E+00	2.618E+01
3.290E-01	3.768E+00	-6.916E+02	7.410E+01	1.407E+00	2.634E+01
3.271E-01	3.790E+00	-7.000E+02	7.557E+01	1.426E+00	2.650E+01
3.252E-01	3.812E+00	-7.083E+02	7.736E+01	1.451E+00	2.665E+01
3.233E-01	3.835E+00	-7.167E+02	7.885E+01	1.471E+00	2.681E+01
3.214E-01	3.858E+00	-7.252E+02	8.004E+01	1.484E+00	2.697E+01
3.195E-01	3.881E+00	-7.340E+02	8.134E+01	1.499E+00	2.713E+01
3.176E-01	3.904E+00	-7.430E+02	8.279E+01	1.516E+00	2.730E+01
3.156E-01	3.928E+00	-7.522E+02	8.428E+01	1.534E+00	2.747E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.137E-01	3.952E+00	-7.616E+02	8.578E+01	1.552E+00	2.764E+01
3.118E-01	3.976E+00	-7.709E+02	8.763E+01	1.576E+00	2.781E+01
3.099E-01	4.001E+00	-7.804E+02	8.923E+01	1.595E+00	2.798E+01
3.080E-01	4.026E+00	-7.901E+02	9.058E+01	1.609E+00	2.816E+01
3.061E-01	4.051E+00	-8.000E+02	9.234E+01	1.630E+00	2.833E+01
3.042E-01	4.076E+00	-8.101E+02	9.454E+01	1.658E+00	2.851E+01
3.023E-01	4.102E+00	-8.206E+02	9.671E+01	1.685E+00	2.870E+01
3.003E-01	4.128E+00	-8.314E+02	9.845E+01	1.704E+00	2.889E+01
2.984E-01	4.155E+00	-8.426E+02	1.003E+02	1.724E+00	2.908E+01
2.965E-01	4.181E+00	-8.535E+02	1.029E+02	1.757E+00	2.927E+01
2.946E-01	4.209E+00	-8.654E+02	1.067E+02	1.810E+00	2.947E+01
2.927E-01	4.236E+00	-8.784E+02	1.106E+02	1.863E+00	2.970E+01
2.908E-01	4.264E+00	-8.904E+02	1.127E+02	1.884E+00	2.990E+01
2.889E-01	4.292E+00	-9.026E+02	1.142E+02	1.897E+00	3.010E+01
2.869E-01	4.321E+00	-9.142E+02	1.154E+02	1.905E+00	3.030E+01
2.850E-01	4.350E+00	-9.252E+02	1.159E+02	1.902E+00	3.048E+01
2.831E-01	4.379E+00	-9.371E+02	1.174E+02	1.914E+00	3.067E+01
2.812E-01	4.409E+00	-9.497E+02	1.195E+02	1.936E+00	3.088E+01
2.793E-01	4.439E+00	-9.626E+02	1.216E+02	1.957E+00	3.109E+01
2.774E-01	4.470E+00	-9.757E+02	1.242E+02	1.984E+00	3.130E+01
2.755E-01	4.501E+00	-9.893E+02	1.268E+02	2.012E+00	3.152E+01
2.736E-01	4.532E+00	-1.003E+03	1.299E+02	2.046E+00	3.174E+01
2.716E-01	4.564E+00	-1.017E+03	1.327E+02	2.076E+00	3.196E+01
2.697E-01	4.597E+00	-1.032E+03	1.348E+02	2.094E+00	3.219E+01
2.678E-01	4.629E+00	-1.045E+03	1.375E+02	2.122E+00	3.239E+01
2.659E-01	4.663E+00	-1.059E+03	1.409E+02	2.160E+00	3.262E+01
2.640E-01	4.697E+00	-1.075E+03	1.437E+02	2.187E+00	3.286E+01
2.621E-01	4.731E+00	-1.091E+03	1.462E+02	2.208E+00	3.311E+01
2.602E-01	4.766E+00	-1.108E+03	1.495E+02	2.241E+00	3.336E+01
2.583E-01	4.801E+00	-1.124E+03	1.536E+02	2.286E+00	3.360E+01
2.563E-01	4.837E+00	-1.141E+03	1.576E+02	2.328E+00	3.385E+01
2.544E-01	4.873E+00	-1.158E+03	1.609E+02	2.359E+00	3.411E+01
2.525E-01	4.910E+00	-1.175E+03	1.637E+02	2.382E+00	3.436E+01
2.506E-01	4.947E+00	-1.193E+03	1.667E+02	2.408E+00	3.462E+01
2.487E-01	4.986E+00	-1.210E+03	1.711E+02	2.453E+00	3.487E+01
2.468E-01	5.024E+00	-1.228E+03	1.760E+02	2.505E+00	3.513E+01
2.449E-01	5.063E+00	-1.247E+03	1.798E+02	2.539E+00	3.541E+01
2.429E-01	5.103E+00	-1.267E+03	1.827E+02	2.560E+00	3.568E+01
2.410E-01	5.144E+00	-1.286E+03	1.863E+02	2.592E+00	3.595E+01
2.391E-01	5.185E+00	-1.305E+03	1.910E+02	2.637E+00	3.622E+01
2.372E-01	5.227E+00	-1.325E+03	1.956E+02	2.680E+00	3.650E+01
2.353E-01	5.269E+00	-1.347E+03	1.995E+02	2.711E+00	3.680E+01
2.334E-01	5.312E+00	-1.369E+03	2.033E+02	2.740E+00	3.710E+01
2.315E-01	5.356E+00	-1.391E+03	2.079E+02	2.779E+00	3.740E+01
2.296E-01	5.401E+00	-1.414E+03	2.132E+02	2.827E+00	3.771E+01
2.276E-01	5.446E+00	-1.438E+03	2.185E+02	2.873E+00	3.803E+01
2.257E-01	5.493E+00	-1.463E+03	2.243E+02	2.924E+00	3.836E+01
2.238E-01	5.539E+00	-1.487E+03	2.310E+02	2.986E+00	3.868E+01
2.219E-01	5.587E+00	-1.512E+03	2.384E+02	3.056E+00	3.901E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.200E-01	5.636E+00	-1.538E+03	2.456E+02	3.122E+00	3.934E+01
2.181E-01	5.685E+00	-1.564E+03	2.522E+02	3.178E+00	3.968E+01
2.162E-01	5.736E+00	-1.591E+03	2.597E+02	3.245E+00	4.001E+01
2.143E-01	5.787E+00	-1.618E+03	2.683E+02	3.324E+00	4.036E+01
2.123E-01	5.839E+00	-1.645E+03	2.756E+02	3.386E+00	4.070E+01
2.104E-01	5.892E+00	-1.674E+03	2.805E+02	3.416E+00	4.106E+01
2.085E-01	5.946E+00	-1.705E+03	2.858E+02	3.449E+00	4.144E+01
2.066E-01	6.001E+00	-1.737E+03	2.936E+02	3.509E+00	4.183E+01
2.047E-01	6.057E+00	-1.774E+03	3.028E+02	3.581E+00	4.227E+01
2.028E-01	6.114E+00	-1.809E+03	3.111E+02	3.644E+00	4.269E+01
2.009E-01	6.173E+00	-1.840E+03	3.185E+02	3.699E+00	4.305E+01
1.990E-01	6.232E+00	-1.874E+03	3.260E+02	3.751E+00	4.345E+01
1.970E-01	6.292E+00	-1.910E+03	3.347E+02	3.814E+00	4.387E+01
1.951E-01	6.354E+00	-1.946E+03	3.467E+02	3.914E+00	4.428E+01
1.932E-01	6.417E+00	-1.983E+03	3.621E+02	4.048E+00	4.472E+01
1.913E-01	6.481E+00	-2.026E+03	3.776E+02	4.177E+00	4.520E+01
1.894E-01	6.547E+00	-2.066E+03	3.903E+02	4.274E+00	4.566E+01
1.875E-01	6.613E+00	-2.105E+03	4.008E+02	4.348E+00	4.609E+01
1.856E-01	6.682E+00	-2.148E+03	4.105E+02	4.409E+00	4.655E+01
1.836E-01	6.751E+00	-2.189E+03	4.216E+02	4.486E+00	4.700E+01
1.817E-01	6.822E+00	-2.234E+03	4.365E+02	4.596E+00	4.748E+01
1.798E-01	6.895E+00	-2.285E+03	4.523E+02	4.709E+00	4.803E+01
1.779E-01	6.969E+00	-2.329E+03	4.675E+02	4.820E+00	4.850E+01
1.760E-01	7.045E+00	-2.364E+03	4.826E+02	4.937E+00	4.887E+01
1.741E-01	7.122E+00	-2.405E+03	5.031E+02	5.102E+00	4.930E+01
1.722E-01	7.201E+00	-2.457E+03	5.258E+02	5.275E+00	4.984E+01
1.703E-01	7.282E+00	-2.509E+03	5.331E+02	5.292E+00	5.037E+01
1.683E-01	7.365E+00	-2.582E+03	5.492E+02	5.374E+00	5.110E+01
1.664E-01	7.450E+00	-2.650E+03	5.744E+02	5.547E+00	5.178E+01
1.645E-01	7.536E+00	-2.700E+03	5.860E+02	5.606E+00	5.226E+01
1.626E-01	7.625E+00	-2.756E+03	5.956E+02	5.641E+00	5.280E+01
1.607E-01	7.716E+00	-2.819E+03	6.134E+02	5.743E+00	5.341E+01
1.588E-01	7.809E+00	-2.883E+03	6.392E+02	5.917E+00	5.402E+01
1.569E-01	7.904E+00	-2.939E+03	6.676E+02	6.118E+00	5.456E+01
1.550E-01	8.001E+00	-3.002E+03	6.926E+02	6.280E+00	5.515E+01
1.530E-01	8.101E+00	-3.080E+03	7.104E+02	6.358E+00	5.586E+01
1.511E-01	8.204E+00	-3.161E+03	7.267E+02	6.421E+00	5.659E+01
1.492E-01	8.309E+00	-3.241E+03	7.572E+02	6.606E+00	5.732E+01
1.473E-01	8.417E+00	-3.329E+03	8.027E+02	6.907E+00	5.811E+01
1.454E-01	8.528E+00	-3.413E+03	8.443E+02	7.172E+00	5.886E+01
1.435E-01	8.642E+00	-3.497E+03	8.845E+02	7.420E+00	5.960E+01
1.416E-01	8.758E+00	-3.583E+03	9.365E+02	7.757E+00	6.036E+01
1.396E-01	8.878E+00	-3.660E+03	9.838E+02	8.060E+00	6.103E+01
1.377E-01	9.002E+00	-3.739E+03	1.013E+03	8.207E+00	6.169E+01
1.358E-01	9.128E+00	-3.844E+03	1.036E+03	8.285E+00	6.255E+01
1.339E-01	9.259E+00	-3.953E+03	1.065E+03	8.393E+00	6.343E+01
1.320E-01	9.393E+00	-4.059E+03	1.092E+03	8.496E+00	6.427E+01
1.301E-01	9.531E+00	-4.175E+03	1.118E+03	8.573E+00	6.518E+01
1.282E-01	9.673E+00	-4.294E+03	1.150E+03	8.697E+00	6.611E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.263E-01	9.820E+00	-4.422E+03	1.201E+03	8.953E+00	6.710E+01
1.243E-01	9.971E+00	-4.565E+03	1.251E+03	9.172E+00	6.818E+01
1.224E-01	1.013E+01	-4.703E+03	1.284E+03	9.277E+00	6.920E+01
1.205E-01	1.029E+01	-4.828E+03	1.334E+03	9.512E+00	7.013E+01
1.186E-01	1.045E+01	-4.960E+03	1.417E+03	9.963E+00	7.113E+01
1.167E-01	1.063E+01	-5.113E+03	1.513E+03	1.047E+01	7.226E+01
1.148E-01	1.080E+01	-5.282E+03	1.575E+03	1.072E+01	7.346E+01
1.129E-01	1.099E+01	-5.449E+03	1.628E+03	1.091E+01	7.462E+01
1.110E-01	1.117E+01	-5.626E+03	1.696E+03	1.118E+01	7.584E+01
1.090E-01	1.137E+01	-5.808E+03	1.776E+03	1.152E+01	7.708E+01
1.071E-01	1.157E+01	-6.004E+03	1.884E+03	1.202E+01	7.841E+01
1.052E-01	1.178E+01	-6.220E+03	1.984E+03	1.243E+01	7.984E+01
1.033E-01	1.200E+01	-6.432E+03	2.090E+03	1.287E+01	8.122E+01
1.014E-01	1.223E+01	-6.680E+03	2.215E+03	1.337E+01	8.282E+01
9.947E-02	1.246E+01	-6.951E+03	2.346E+03	1.388E+01	8.452E+01
9.756E-02	1.271E+01	-7.175E+03	2.503E+03	1.456E+01	8.595E+01
9.565E-02	1.296E+01	-7.431E+03	2.668E+03	1.524E+01	8.754E+01
9.374E-02	1.323E+01	-7.689E+03	2.891E+03	1.621E+01	8.917E+01
9.183E-02	1.350E+01	-7.908E+03	3.115E+03	1.720E+01	9.058E+01
8.991E-02	1.379E+01	-8.149E+03	3.281E+03	1.783E+01	9.201E+01
8.800E-02	1.409E+01	-8.426E+03	3.459E+03	1.847E+01	9.363E+01
8.608E-02	1.440E+01	-8.739E+03	3.618E+03	1.896E+01	9.539E+01
8.417E-02	1.473E+01	-9.134E+03	3.814E+03	1.955E+01	9.755E+01
8.226E-02	1.507E+01	-9.532E+03	4.028E+03	2.020E+01	9.970E+01
8.035E-02	1.543E+01	-9.820E+03	4.134E+03	2.043E+01	1.012E+02
7.843E-02	1.581E+01	-1.025E+04	4.251E+03	2.058E+01	1.033E+02
7.652E-02	1.620E+01	-1.079E+04	4.633E+03	2.183E+01	1.061E+02
7.461E-02	1.662E+01	-1.124E+04	5.027E+03	2.316E+01	1.085E+02
7.269E-02	1.706E+01	-1.170E+04	5.255E+03	2.373E+01	1.107E+02
7.078E-02	1.752E+01	-1.212E+04	5.553E+03	2.462E+01	1.128E+02
6.887E-02	1.800E+01	-1.253E+04	5.841E+03	2.544E+01	1.148E+02
6.696E-02	1.852E+01	-1.328E+04	6.035E+03	2.557E+01	1.180E+02
6.504E-02	1.906E+01	-1.413E+04	6.364E+03	2.614E+01	1.217E+02
6.313E-02	1.964E+01	-1.454E+04	6.834E+03	2.762E+01	1.237E+02
6.121E-02	2.025E+01	-1.487E+04	7.268E+03	2.900E+01	1.253E+02
5.930E-02	2.091E+01	-1.558E+04	7.908E+03	3.076E+01	1.286E+02
5.739E-02	2.160E+01	-1.646E+04	8.713E+03	3.289E+01	1.325E+02
5.548E-02	2.235E+01	-1.768E+04	9.084E+03	3.315E+01	1.370E+02
5.356E-02	2.315E+01	-1.883E+04	9.440E+03	3.342E+01	1.412E+02
5.165E-02	2.400E+01	-1.954E+04	1.073E+04	3.710E+01	1.446E+02
4.974E-02	2.493E+01	-2.052E+04	1.225E+04	4.112E+01	1.490E+02