

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.593E+00	2.700E-01	1.255E-01	3.595E+00	1.364E+00	1.318E+00
4.429E+00	2.800E-01	6.453E-01	3.663E+00	1.477E+00	1.240E+00
4.276E+00	2.900E-01	9.800E-01	3.577E+00	1.531E+00	1.168E+00
4.133E+00	3.000E-01	1.757E+00	2.937E+00	1.609E+00	9.126E-01
4.000E+00	3.100E-01	1.616E+00	1.426E+00	1.373E+00	5.192E-01
3.875E+00	3.200E-01	5.597E-01	5.462E-01	8.191E-01	3.334E-01
3.758E+00	3.300E-01	-4.108E-01	2.992E-01	2.207E-01	6.779E-01
3.647E+00	3.400E-01	-1.162E+00	2.403E-01	1.109E-01	1.084E+00
3.543E+00	3.500E-01	-1.791E+00	2.264E-01	8.443E-02	1.341E+00
3.444E+00	3.600E-01	-2.355E+00	2.255E-01	7.339E-02	1.536E+00
3.351E+00	3.699E-01	-2.881E+00	2.286E-01	6.727E-02	1.699E+00
3.263E+00	3.799E-01	-3.387E+00	2.329E-01	6.325E-02	1.841E+00
3.180E+00	3.899E-01	-3.880E+00	2.379E-01	6.035E-02	1.971E+00
3.100E+00	3.999E-01	-4.366E+00	2.432E-01	5.817E-02	2.090E+00
3.024E+00	4.099E-01	-4.850E+00	2.488E-01	5.647E-02	2.203E+00
2.952E+00	4.199E-01	-5.334E+00	2.548E-01	5.515E-02	2.310E+00
2.884E+00	4.299E-01	-5.821E+00	2.612E-01	5.411E-02	2.413E+00
2.818E+00	4.399E-01	-6.310E+00	2.679E-01	5.332E-02	2.513E+00
2.756E+00	4.499E-01	-6.805E+00	2.751E-01	5.271E-02	2.609E+00
2.696E+00	4.599E-01	-7.305E+00	2.826E-01	5.227E-02	2.703E+00
2.638E+00	4.699E-01	-7.811E+00	2.906E-01	5.198E-02	2.795E+00
2.583E+00	4.799E-01	-8.324E+00	2.990E-01	5.181E-02	2.886E+00
2.531E+00	4.899E-01	-8.844E+00	3.079E-01	5.175E-02	2.974E+00
2.480E+00	4.999E-01	-9.372E+00	3.172E-01	5.180E-02	3.062E+00
2.431E+00	5.099E-01	-9.908E+00	3.270E-01	5.193E-02	3.148E+00
2.385E+00	5.199E-01	-1.045E+01	3.373E-01	5.215E-02	3.233E+00
2.340E+00	5.299E-01	-1.100E+01	3.480E-01	5.245E-02	3.318E+00
2.296E+00	5.399E-01	-1.157E+01	3.593E-01	5.282E-02	3.401E+00
2.255E+00	5.499E-01	-1.213E+01	3.711E-01	5.326E-02	3.484E+00
2.214E+00	5.599E-01	-1.271E+01	3.834E-01	5.376E-02	3.566E+00
2.175E+00	5.699E-01	-1.330E+01	3.962E-01	5.431E-02	3.648E+00
2.138E+00	5.799E-01	-1.390E+01	4.096E-01	5.493E-02	3.728E+00
2.102E+00	5.899E-01	-1.450E+01	4.235E-01	5.560E-02	3.809E+00
2.067E+00	5.999E-01	-1.512E+01	4.380E-01	5.632E-02	3.889E+00
2.033E+00	6.099E-01	-1.574E+01	4.531E-01	5.709E-02	3.968E+00
2.000E+00	6.199E-01	-1.638E+01	4.687E-01	5.790E-02	4.048E+00
1.968E+00	6.299E-01	-1.702E+01	4.849E-01	5.876E-02	4.126E+00
1.938E+00	6.399E-01	-1.768E+01	5.017E-01	5.966E-02	4.205E+00
1.908E+00	6.499E-01	-1.834E+01	5.191E-01	6.061E-02	4.283E+00
1.879E+00	6.599E-01	-1.901E+01	5.372E-01	6.159E-02	4.361E+00
1.851E+00	6.699E-01	-1.969E+01	5.558E-01	6.262E-02	4.438E+00
1.824E+00	6.799E-01	-2.039E+01	5.751E-01	6.368E-02	4.516E+00
1.797E+00	6.899E-01	-2.109E+01	5.950E-01	6.478E-02	4.593E+00
1.771E+00	6.999E-01	-2.180E+01	6.156E-01	6.591E-02	4.669E+00
1.747E+00	7.099E-01	-2.252E+01	6.368E-01	6.708E-02	4.746E+00
1.722E+00	7.199E-01	-2.325E+01	6.586E-01	6.829E-02	4.823E+00
1.699E+00	7.299E-01	-2.399E+01	6.812E-01	6.953E-02	4.899E+00
1.676E+00	7.399E-01	-2.474E+01	7.044E-01	7.080E-02	4.975E+00
1.653E+00	7.499E-01	-2.550E+01	7.283E-01	7.210E-02	5.051E+00
1.632E+00	7.599E-01	-2.627E+01	7.529E-01	7.344E-02	5.126E+00

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.610E+00	7.699E-01	-2.706E+01	7.782E-01	7.480E-02	5.202E+00
1.590E+00	7.799E-01	-2.785E+01	8.043E-01	7.620E-02	5.278E+00
1.570E+00	7.899E-01	-2.865E+01	8.310E-01	7.762E-02	5.353E+00
1.550E+00	7.999E-01	-2.946E+01	8.585E-01	7.908E-02	5.428E+00
1.531E+00	8.099E-01	-3.028E+01	8.867E-01	8.057E-02	5.503E+00
1.512E+00	8.199E-01	-3.111E+01	9.157E-01	8.208E-02	5.578E+00
1.494E+00	8.299E-01	-3.195E+01	9.454E-01	8.362E-02	5.653E+00
1.476E+00	8.399E-01	-3.280E+01	9.759E-01	8.519E-02	5.728E+00
1.459E+00	8.499E-01	-3.366E+01	1.007E+00	8.679E-02	5.802E+00
1.442E+00	8.599E-01	-3.453E+01	1.039E+00	8.841E-02	5.877E+00
1.425E+00	8.699E-01	-3.541E+01	1.072E+00	9.007E-02	5.951E+00
1.409E+00	8.799E-01	-3.630E+01	1.106E+00	9.174E-02	6.026E+00
1.393E+00	8.899E-01	-3.720E+01	1.140E+00	9.345E-02	6.100E+00
1.378E+00	8.999E-01	-3.811E+01	1.175E+00	9.518E-02	6.174E+00
1.363E+00	9.099E-01	-3.903E+01	1.211E+00	9.694E-02	6.248E+00
1.348E+00	9.199E-01	-3.996E+01	1.248E+00	9.872E-02	6.322E+00
1.333E+00	9.299E-01	-4.090E+01	1.286E+00	1.005E-01	6.396E+00
1.319E+00	9.399E-01	-4.185E+01	1.325E+00	1.024E-01	6.470E+00
1.305E+00	9.499E-01	-4.281E+01	1.364E+00	1.042E-01	6.544E+00
1.292E+00	9.599E-01	-4.378E+01	1.404E+00	1.061E-01	6.618E+00
1.278E+00	9.698E-01	-4.476E+01	1.446E+00	1.080E-01	6.691E+00
1.265E+00	9.799E-01	-4.575E+01	1.488E+00	1.100E-01	6.765E+00
1.253E+00	9.899E-01	-4.675E+01	1.531E+00	1.119E-01	6.838E+00
1.240E+00	9.999E-01	-4.776E+01	1.575E+00	1.139E-01	6.912E+00
1.228E+00	1.010E+00	-4.878E+01	1.619E+00	1.159E-01	6.985E+00
1.216E+00	1.020E+00	-4.981E+01	1.665E+00	1.179E-01	7.059E+00
1.204E+00	1.030E+00	-5.085E+01	1.712E+00	1.200E-01	7.132E+00
1.192E+00	1.040E+00	-5.190E+01	1.759E+00	1.221E-01	7.206E+00
1.181E+00	1.050E+00	-5.297E+01	1.808E+00	1.242E-01	7.279E+00
1.170E+00	1.060E+00	-5.404E+01	1.857E+00	1.263E-01	7.352E+00
1.159E+00	1.070E+00	-5.512E+01	1.908E+00	1.285E-01	7.425E+00
1.148E+00	1.080E+00	-5.621E+01	1.959E+00	1.306E-01	7.498E+00
1.138E+00	1.090E+00	-5.731E+01	2.011E+00	1.328E-01	7.571E+00
1.127E+00	1.100E+00	-5.842E+01	2.065E+00	1.351E-01	7.645E+00
1.117E+00	1.110E+00	-5.954E+01	2.119E+00	1.373E-01	7.718E+00
1.107E+00	1.120E+00	-6.067E+01	2.174E+00	1.396E-01	7.791E+00
1.097E+00	1.130E+00	-6.181E+01	2.231E+00	1.419E-01	7.863E+00
1.088E+00	1.140E+00	-6.296E+01	2.288E+00	1.442E-01	7.936E+00
1.078E+00	1.150E+00	-6.413E+01	2.347E+00	1.465E-01	8.009E+00
1.069E+00	1.160E+00	-6.530E+01	2.406E+00	1.489E-01	8.082E+00
1.060E+00	1.170E+00	-6.648E+01	2.467E+00	1.513E-01	8.155E+00
1.051E+00	1.180E+00	-6.767E+01	2.528E+00	1.537E-01	8.228E+00
1.042E+00	1.190E+00	-6.887E+01	2.591E+00	1.561E-01	8.300E+00
1.033E+00	1.200E+00	-7.008E+01	2.655E+00	1.585E-01	8.373E+00
1.025E+00	1.210E+00	-7.130E+01	2.720E+00	1.610E-01	8.446E+00
1.016E+00	1.220E+00	-7.253E+01	2.785E+00	1.635E-01	8.518E+00
1.008E+00	1.230E+00	-7.378E+01	2.853E+00	1.660E-01	8.591E+00
1.000E+00	1.240E+00	-7.503E+01	2.921E+00	1.686E-01	8.664E+00
9.920E-01	1.250E+00	-7.629E+01	2.990E+00	1.711E-01	8.736E+00

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.841E-01	1.260E+00	-7.756E+01	3.060E+00	1.737E-01	8.809E+00
9.777E-01	1.268E+00	-7.863E+01	3.120E+00	1.759E-01	8.869E+00
9.764E-01	1.270E+00	-7.884E+01	3.132E+00	1.763E-01	8.881E+00
9.700E-01	1.278E+00	-7.992E+01	3.192E+00	1.785E-01	8.942E+00
9.688E-01	1.280E+00	-8.014E+01	3.205E+00	1.790E-01	8.954E+00
9.624E-01	1.288E+00	-8.124E+01	3.267E+00	1.812E-01	9.015E+00
9.612E-01	1.290E+00	-8.144E+01	3.278E+00	1.816E-01	9.026E+00
9.547E-01	1.299E+00	-8.260E+01	3.344E+00	1.840E-01	9.090E+00
9.539E-01	1.300E+00	-8.275E+01	3.353E+00	1.843E-01	9.099E+00
9.471E-01	1.309E+00	-8.398E+01	3.424E+00	1.868E-01	9.166E+00
9.466E-01	1.310E+00	-8.407E+01	3.429E+00	1.870E-01	9.171E+00
9.394E-01	1.320E+00	-8.540E+01	3.507E+00	1.897E-01	9.243E+00
9.394E-01	1.320E+00	-8.540E+01	3.507E+00	1.897E-01	9.243E+00
9.337E-01	1.328E+00	-8.649E+01	3.570E+00	1.919E-01	9.302E+00
9.323E-01	1.330E+00	-8.675E+01	3.585E+00	1.924E-01	9.316E+00
9.260E-01	1.339E+00	-8.797E+01	3.657E+00	1.949E-01	9.381E+00
9.254E-01	1.340E+00	-8.810E+01	3.665E+00	1.952E-01	9.388E+00
9.203E-01	1.347E+00	-8.911E+01	3.725E+00	1.973E-01	9.442E+00
9.185E-01	1.350E+00	-8.946E+01	3.746E+00	1.980E-01	9.460E+00
9.126E-01	1.359E+00	-9.066E+01	3.817E+00	2.004E-01	9.524E+00
9.069E-01	1.367E+00	-9.184E+01	3.889E+00	2.029E-01	9.586E+00
8.992E-01	1.379E+00	-9.346E+01	3.987E+00	2.062E-01	9.670E+00
8.935E-01	1.388E+00	-9.470E+01	4.063E+00	2.087E-01	9.734E+00
8.858E-01	1.400E+00	-9.640E+01	4.167E+00	2.122E-01	9.820E+00
8.801E-01	1.409E+00	-9.769E+01	4.248E+00	2.148E-01	9.886E+00
8.744E-01	1.418E+00	-9.902E+01	4.331E+00	2.176E-01	9.953E+00
8.686E-01	1.427E+00	-1.004E+02	4.416E+00	2.203E-01	1.002E+01
8.671E-01	1.430E+00	-1.007E+02	4.438E+00	2.210E-01	1.004E+01
8.629E-01	1.437E+00	-1.017E+02	4.503E+00	2.231E-01	1.009E+01
8.611E-01	1.440E+00	-1.022E+02	4.530E+00	2.240E-01	1.011E+01
8.552E-01	1.450E+00	-1.036E+02	4.623E+00	2.270E-01	1.018E+01
8.552E-01	1.450E+00	-1.036E+02	4.623E+00	2.270E-01	1.018E+01
8.495E-01	1.460E+00	-1.051E+02	4.716E+00	2.300E-01	1.025E+01
8.493E-01	1.460E+00	-1.051E+02	4.718E+00	2.301E-01	1.026E+01
8.437E-01	1.469E+00	-1.065E+02	4.811E+00	2.330E-01	1.032E+01
8.435E-01	1.470E+00	-1.066E+02	4.814E+00	2.331E-01	1.033E+01
8.380E-01	1.480E+00	-1.080E+02	4.909E+00	2.361E-01	1.040E+01
8.378E-01	1.480E+00	-1.081E+02	4.912E+00	2.362E-01	1.040E+01
8.323E-01	1.490E+00	-1.096E+02	5.009E+00	2.392E-01	1.047E+01
8.322E-01	1.490E+00	-1.096E+02	5.010E+00	2.393E-01	1.047E+01
8.284E-01	1.497E+00	-1.106E+02	5.078E+00	2.414E-01	1.052E+01
8.267E-01	1.500E+00	-1.111E+02	5.110E+00	2.424E-01	1.054E+01
8.227E-01	1.507E+00	-1.122E+02	5.184E+00	2.446E-01	1.060E+01
8.212E-01	1.510E+00	-1.126E+02	5.212E+00	2.455E-01	1.062E+01
8.170E-01	1.518E+00	-1.138E+02	5.292E+00	2.480E-01	1.067E+01
8.158E-01	1.520E+00	-1.142E+02	5.315E+00	2.487E-01	1.069E+01
8.112E-01	1.528E+00	-1.155E+02	5.404E+00	2.514E-01	1.075E+01
8.105E-01	1.530E+00	-1.157E+02	5.419E+00	2.518E-01	1.076E+01
8.055E-01	1.539E+00	-1.172E+02	5.519E+00	2.549E-01	1.083E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
8.052E-01	1.540E+00	-1.172E+02	5.524E+00	2.550E-01	1.083E+01
8.017E-01	1.547E+00	-1.183E+02	5.597E+00	2.572E-01	1.088E+01
8.000E-01	1.550E+00	-1.188E+02	5.631E+00	2.582E-01	1.090E+01
7.959E-01	1.558E+00	-1.201E+02	5.718E+00	2.608E-01	1.096E+01
7.949E-01	1.560E+00	-1.204E+02	5.739E+00	2.615E-01	1.098E+01
7.902E-01	1.569E+00	-1.219E+02	5.841E+00	2.645E-01	1.104E+01
7.898E-01	1.570E+00	-1.220E+02	5.849E+00	2.647E-01	1.105E+01
7.863E-01	1.577E+00	-1.231E+02	5.926E+00	2.670E-01	1.110E+01
7.848E-01	1.580E+00	-1.236E+02	5.960E+00	2.680E-01	1.112E+01
7.806E-01	1.588E+00	-1.249E+02	6.056E+00	2.708E-01	1.118E+01
7.799E-01	1.590E+00	-1.252E+02	6.073E+00	2.713E-01	1.119E+01
7.768E-01	1.596E+00	-1.262E+02	6.145E+00	2.734E-01	1.124E+01
7.750E-01	1.600E+00	-1.268E+02	6.187E+00	2.747E-01	1.126E+01
7.710E-01	1.608E+00	-1.281E+02	6.282E+00	2.774E-01	1.132E+01
7.702E-01	1.610E+00	-1.284E+02	6.302E+00	2.780E-01	1.134E+01
7.672E-01	1.616E+00	-1.294E+02	6.375E+00	2.801E-01	1.138E+01
7.654E-01	1.620E+00	-1.300E+02	6.419E+00	2.814E-01	1.141E+01
7.615E-01	1.628E+00	-1.314E+02	6.519E+00	2.842E-01	1.147E+01
7.607E-01	1.630E+00	-1.317E+02	6.538E+00	2.848E-01	1.148E+01
7.576E-01	1.636E+00	-1.328E+02	6.617E+00	2.870E-01	1.153E+01
7.561E-01	1.640E+00	-1.333E+02	6.657E+00	2.882E-01	1.155E+01
7.519E-01	1.649E+00	-1.348E+02	6.768E+00	2.913E-01	1.162E+01
7.515E-01	1.650E+00	-1.350E+02	6.778E+00	2.916E-01	1.162E+01
7.481E-01	1.657E+00	-1.363E+02	6.871E+00	2.942E-01	1.168E+01
7.470E-01	1.660E+00	-1.367E+02	6.901E+00	2.951E-01	1.169E+01
7.443E-01	1.666E+00	-1.377E+02	6.977E+00	2.972E-01	1.174E+01
7.425E-01	1.670E+00	-1.383E+02	7.025E+00	2.985E-01	1.177E+01
7.385E-01	1.679E+00	-1.399E+02	7.139E+00	3.017E-01	1.183E+01
7.381E-01	1.680E+00	-1.400E+02	7.151E+00	3.020E-01	1.184E+01
7.347E-01	1.688E+00	-1.414E+02	7.250E+00	3.048E-01	1.189E+01
7.337E-01	1.690E+00	-1.418E+02	7.278E+00	3.056E-01	1.191E+01
7.309E-01	1.696E+00	-1.429E+02	7.363E+00	3.079E-01	1.196E+01
7.294E-01	1.700E+00	-1.434E+02	7.406E+00	3.091E-01	1.198E+01
7.270E-01	1.705E+00	-1.444E+02	7.479E+00	3.111E-01	1.202E+01
7.252E-01	1.710E+00	-1.452E+02	7.537E+00	3.127E-01	1.205E+01
7.213E-01	1.719E+00	-1.468E+02	7.657E+00	3.159E-01	1.212E+01
7.209E-01	1.720E+00	-1.469E+02	7.669E+00	3.162E-01	1.213E+01
7.175E-01	1.728E+00	-1.483E+02	7.779E+00	3.192E-01	1.218E+01
7.168E-01	1.730E+00	-1.487E+02	7.802E+00	3.198E-01	1.220E+01
7.136E-01	1.737E+00	-1.500E+02	7.904E+00	3.226E-01	1.225E+01
7.126E-01	1.740E+00	-1.504E+02	7.936E+00	3.235E-01	1.227E+01
7.098E-01	1.747E+00	-1.516E+02	8.031E+00	3.260E-01	1.232E+01
7.086E-01	1.750E+00	-1.522E+02	8.073E+00	3.271E-01	1.234E+01
7.060E-01	1.756E+00	-1.533E+02	8.161E+00	3.295E-01	1.239E+01
7.046E-01	1.760E+00	-1.539E+02	8.211E+00	3.308E-01	1.241E+01
7.022E-01	1.766E+00	-1.550E+02	8.295E+00	3.330E-01	1.246E+01
7.006E-01	1.770E+00	-1.557E+02	8.351E+00	3.345E-01	1.248E+01
6.983E-01	1.775E+00	-1.567E+02	8.430E+00	3.366E-01	1.252E+01
6.966E-01	1.780E+00	-1.575E+02	8.491E+00	3.382E-01	1.256E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.945E-01	1.785E+00	-1.585E+02	8.569E+00	3.402E-01	1.259E+01
6.927E-01	1.790E+00	-1.593E+02	8.634E+00	3.419E-01	1.263E+01
6.907E-01	1.795E+00	-1.603E+02	8.711E+00	3.439E-01	1.267E+01
6.889E-01	1.800E+00	-1.611E+02	8.779E+00	3.457E-01	1.270E+01
6.869E-01	1.805E+00	-1.621E+02	8.856E+00	3.477E-01	1.274E+01
6.851E-01	1.810E+00	-1.630E+02	8.924E+00	3.494E-01	1.277E+01
6.830E-01	1.815E+00	-1.639E+02	9.004E+00	3.515E-01	1.281E+01
6.813E-01	1.820E+00	-1.648E+02	9.072E+00	3.532E-01	1.284E+01
6.792E-01	1.825E+00	-1.658E+02	9.157E+00	3.554E-01	1.288E+01
6.776E-01	1.830E+00	-1.666E+02	9.222E+00	3.570E-01	1.291E+01
6.754E-01	1.836E+00	-1.678E+02	9.312E+00	3.593E-01	1.296E+01
6.739E-01	1.840E+00	-1.685E+02	9.372E+00	3.609E-01	1.299E+01
6.716E-01	1.846E+00	-1.697E+02	9.471E+00	3.634E-01	1.303E+01
6.703E-01	1.850E+00	-1.704E+02	9.525E+00	3.647E-01	1.306E+01
6.677E-01	1.857E+00	-1.717E+02	9.633E+00	3.675E-01	1.311E+01
6.667E-01	1.860E+00	-1.722E+02	9.679E+00	3.686E-01	1.313E+01
6.639E-01	1.868E+00	-1.737E+02	9.799E+00	3.716E-01	1.318E+01
6.631E-01	1.870E+00	-1.741E+02	9.834E+00	3.725E-01	1.320E+01
6.601E-01	1.878E+00	-1.757E+02	9.970E+00	3.759E-01	1.326E+01
6.596E-01	1.880E+00	-1.760E+02	9.992E+00	3.764E-01	1.327E+01
6.562E-01	1.889E+00	-1.778E+02	1.014E+01	3.802E-01	1.334E+01
6.561E-01	1.890E+00	-1.779E+02	1.015E+01	3.804E-01	1.334E+01
6.543E-01	1.895E+00	-1.789E+02	1.023E+01	3.824E-01	1.338E+01
6.526E-01	1.900E+00	-1.798E+02	1.031E+01	3.843E-01	1.342E+01
6.505E-01	1.906E+00	-1.810E+02	1.041E+01	3.868E-01	1.346E+01
6.492E-01	1.910E+00	-1.817E+02	1.047E+01	3.883E-01	1.349E+01
6.467E-01	1.917E+00	-1.832E+02	1.060E+01	3.913E-01	1.354E+01
6.458E-01	1.920E+00	-1.837E+02	1.064E+01	3.923E-01	1.356E+01
6.429E-01	1.929E+00	-1.854E+02	1.079E+01	3.959E-01	1.362E+01
6.425E-01	1.930E+00	-1.856E+02	1.080E+01	3.964E-01	1.363E+01
6.409E-01	1.934E+00	-1.865E+02	1.088E+01	3.982E-01	1.366E+01
6.392E-01	1.940E+00	-1.876E+02	1.097E+01	4.004E-01	1.370E+01
6.371E-01	1.946E+00	-1.888E+02	1.108E+01	4.030E-01	1.375E+01
6.359E-01	1.950E+00	-1.895E+02	1.114E+01	4.045E-01	1.377E+01
6.333E-01	1.958E+00	-1.911E+02	1.128E+01	4.078E-01	1.383E+01
6.327E-01	1.960E+00	-1.915E+02	1.131E+01	4.086E-01	1.384E+01
6.295E-01	1.970E+00	-1.935E+02	1.148E+01	4.127E-01	1.392E+01
6.294E-01	1.970E+00	-1.935E+02	1.149E+01	4.127E-01	1.392E+01
6.275E-01	1.976E+00	-1.947E+02	1.159E+01	4.151E-01	1.396E+01
6.263E-01	1.980E+00	-1.955E+02	1.166E+01	4.168E-01	1.399E+01
6.237E-01	1.988E+00	-1.971E+02	1.180E+01	4.202E-01	1.405E+01
6.231E-01	1.990E+00	-1.975E+02	1.184E+01	4.210E-01	1.406E+01
6.218E-01	1.994E+00	-1.983E+02	1.191E+01	4.227E-01	1.409E+01
6.200E-01	2.000E+00	-1.995E+02	1.201E+01	4.251E-01	1.413E+01
6.180E-01	2.006E+00	-2.008E+02	1.213E+01	4.279E-01	1.418E+01
6.142E-01	2.019E+00	-2.034E+02	1.236E+01	4.331E-01	1.427E+01
6.122E-01	2.025E+00	-2.046E+02	1.247E+01	4.358E-01	1.431E+01
6.084E-01	2.038E+00	-2.073E+02	1.271E+01	4.412E-01	1.440E+01
6.065E-01	2.044E+00	-2.086E+02	1.283E+01	4.440E-01	1.445E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.027E-01	2.057E+00	-2.112E+02	1.307E+01	4.495E-01	1.454E+01
6.008E-01	2.064E+00	-2.126E+02	1.320E+01	4.524E-01	1.459E+01
5.969E-01	2.077E+00	-2.154E+02	1.345E+01	4.581E-01	1.468E+01
5.950E-01	2.084E+00	-2.168E+02	1.358E+01	4.610E-01	1.473E+01
5.912E-01	2.097E+00	-2.196E+02	1.385E+01	4.669E-01	1.483E+01
5.893E-01	2.104E+00	-2.210E+02	1.398E+01	4.699E-01	1.488E+01
5.855E-01	2.118E+00	-2.240E+02	1.425E+01	4.760E-01	1.497E+01
5.835E-01	2.125E+00	-2.255E+02	1.439E+01	4.791E-01	1.502E+01
5.797E-01	2.139E+00	-2.285E+02	1.468E+01	4.853E-01	1.512E+01
5.778E-01	2.146E+00	-2.300E+02	1.482E+01	4.885E-01	1.517E+01
5.759E-01	2.153E+00	-2.316E+02	1.497E+01	4.917E-01	1.523E+01
5.721E-01	2.167E+00	-2.347E+02	1.527E+01	4.982E-01	1.533E+01
5.702E-01	2.175E+00	-2.363E+02	1.543E+01	5.015E-01	1.538E+01
5.663E-01	2.189E+00	-2.395E+02	1.574E+01	5.082E-01	1.548E+01
5.644E-01	2.197E+00	-2.411E+02	1.590E+01	5.116E-01	1.554E+01
5.625E-01	2.204E+00	-2.428E+02	1.606E+01	5.151E-01	1.559E+01
5.587E-01	2.219E+00	-2.462E+02	1.639E+01	5.221E-01	1.570E+01
5.568E-01	2.227E+00	-2.479E+02	1.656E+01	5.256E-01	1.575E+01
5.548E-01	2.235E+00	-2.496E+02	1.673E+01	5.292E-01	1.581E+01
5.529E-01	2.242E+00	-2.514E+02	1.690E+01	5.328E-01	1.586E+01
5.491E-01	2.258E+00	-2.549E+02	1.726E+01	5.402E-01	1.597E+01
5.472E-01	2.266E+00	-2.567E+02	1.744E+01	5.439E-01	1.603E+01
5.453E-01	2.274E+00	-2.585E+02	1.762E+01	5.477E-01	1.609E+01
5.434E-01	2.282E+00	-2.603E+02	1.781E+01	5.515E-01	1.614E+01
5.395E-01	2.298E+00	-2.641E+02	1.819E+01	5.593E-01	1.626E+01
5.376E-01	2.306E+00	-2.660E+02	1.838E+01	5.632E-01	1.632E+01
5.357E-01	2.314E+00	-2.679E+02	1.858E+01	5.672E-01	1.638E+01
5.338E-01	2.323E+00	-2.698E+02	1.878E+01	5.712E-01	1.644E+01
5.300E-01	2.339E+00	-2.737E+02	1.918E+01	5.794E-01	1.656E+01
5.281E-01	2.348E+00	-2.758E+02	1.939E+01	5.835E-01	1.662E+01
5.261E-01	2.356E+00	-2.778E+02	1.960E+01	5.877E-01	1.668E+01
5.242E-01	2.365E+00	-2.798E+02	1.982E+01	5.920E-01	1.674E+01
5.223E-01	2.374E+00	-2.819E+02	2.004E+01	5.963E-01	1.680E+01
5.204E-01	2.382E+00	-2.840E+02	2.026E+01	6.006E-01	1.686E+01
5.185E-01	2.391E+00	-2.861E+02	2.048E+01	6.050E-01	1.692E+01
5.147E-01	2.409E+00	-2.904E+02	2.094E+01	6.139E-01	1.705E+01
5.128E-01	2.418E+00	-2.925E+02	2.117E+01	6.185E-01	1.712E+01
5.108E-01	2.427E+00	-2.947E+02	2.141E+01	6.231E-01	1.718E+01
5.089E-01	2.436E+00	-2.970E+02	2.165E+01	6.277E-01	1.724E+01
5.070E-01	2.445E+00	-2.992E+02	2.189E+01	6.324E-01	1.731E+01
5.051E-01	2.455E+00	-3.015E+02	2.214E+01	6.372E-01	1.738E+01
5.032E-01	2.464E+00	-3.038E+02	2.239E+01	6.420E-01	1.744E+01
5.013E-01	2.473E+00	-3.061E+02	2.265E+01	6.468E-01	1.751E+01
4.994E-01	2.483E+00	-3.085E+02	2.291E+01	6.517E-01	1.758E+01
4.974E-01	2.492E+00	-3.109E+02	2.317E+01	6.567E-01	1.765E+01
4.955E-01	2.502E+00	-3.133E+02	2.344E+01	6.617E-01	1.771E+01
4.936E-01	2.512E+00	-3.158E+02	2.371E+01	6.668E-01	1.778E+01
4.917E-01	2.522E+00	-3.182E+02	2.399E+01	6.720E-01	1.785E+01
4.898E-01	2.531E+00	-3.207E+02	2.427E+01	6.772E-01	1.792E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.879E-01	2.541E+00	-3.232E+02	2.456E+01	6.824E-01	1.799E+01
4.860E-01	2.551E+00	-3.258E+02	2.485E+01	6.878E-01	1.806E+01
4.841E-01	2.561E+00	-3.284E+02	2.514E+01	6.931E-01	1.814E+01
4.821E-01	2.572E+00	-3.310E+02	2.544E+01	6.986E-01	1.821E+01
4.802E-01	2.582E+00	-3.337E+02	2.574E+01	7.041E-01	1.828E+01
4.783E-01	2.592E+00	-3.364E+02	2.605E+01	7.097E-01	1.835E+01
4.764E-01	2.603E+00	-3.391E+02	2.637E+01	7.154E-01	1.843E+01
4.745E-01	2.613E+00	-3.418E+02	2.668E+01	7.211E-01	1.850E+01
4.726E-01	2.624E+00	-3.446E+02	2.701E+01	7.269E-01	1.858E+01
4.707E-01	2.634E+00	-3.474E+02	2.734E+01	7.327E-01	1.865E+01
4.687E-01	2.645E+00	-3.503E+02	2.767E+01	7.387E-01	1.873E+01
4.668E-01	2.656E+00	-3.531E+02	2.801E+01	7.447E-01	1.881E+01
4.649E-01	2.667E+00	-3.561E+02	2.836E+01	7.508E-01	1.889E+01
4.630E-01	2.678E+00	-3.590E+02	2.871E+01	7.569E-01	1.896E+01
4.611E-01	2.689E+00	-3.620E+02	2.906E+01	7.631E-01	1.904E+01
4.592E-01	2.700E+00	-3.650E+02	2.943E+01	7.695E-01	1.912E+01
4.573E-01	2.711E+00	-3.681E+02	2.980E+01	7.758E-01	1.920E+01
4.554E-01	2.723E+00	-3.712E+02	3.017E+01	7.823E-01	1.928E+01
4.534E-01	2.734E+00	-3.743E+02	3.055E+01	7.889E-01	1.936E+01
4.515E-01	2.746E+00	-3.775E+02	3.094E+01	7.955E-01	1.945E+01
4.496E-01	2.758E+00	-3.807E+02	3.133E+01	8.022E-01	1.953E+01
4.477E-01	2.769E+00	-3.840E+02	3.173E+01	8.090E-01	1.961E+01
4.458E-01	2.781E+00	-3.873E+02	3.214E+01	8.159E-01	1.970E+01
4.439E-01	2.793E+00	-3.907E+02	3.256E+01	8.229E-01	1.978E+01
4.420E-01	2.805E+00	-3.940E+02	3.298E+01	8.300E-01	1.987E+01
4.401E-01	2.817E+00	-3.975E+02	3.341E+01	8.371E-01	1.996E+01
4.381E-01	2.830E+00	-4.010E+02	3.385E+01	8.444E-01	2.004E+01
4.362E-01	2.842E+00	-4.045E+02	3.429E+01	8.517E-01	2.013E+01
4.343E-01	2.855E+00	-4.081E+02	3.474E+01	8.592E-01	2.022E+01
4.324E-01	2.867E+00	-4.117E+02	3.520E+01	8.667E-01	2.031E+01
4.305E-01	2.880E+00	-4.154E+02	3.567E+01	8.744E-01	2.040E+01
4.286E-01	2.893E+00	-4.191E+02	3.615E+01	8.821E-01	2.049E+01
4.267E-01	2.906E+00	-4.228E+02	3.664E+01	8.900E-01	2.058E+01
4.247E-01	2.919E+00	-4.266E+02	3.713E+01	8.979E-01	2.068E+01
4.228E-01	2.932E+00	-4.305E+02	3.763E+01	9.060E-01	2.077E+01
4.209E-01	2.946E+00	-4.344E+02	3.815E+01	9.142E-01	2.086E+01
4.190E-01	2.959E+00	-4.384E+02	3.867E+01	9.225E-01	2.096E+01
4.171E-01	2.973E+00	-4.424E+02	3.920E+01	9.309E-01	2.106E+01
4.152E-01	2.986E+00	-4.465E+02	3.974E+01	9.394E-01	2.115E+01
4.133E-01	3.000E+00	-4.507E+02	4.029E+01	9.480E-01	2.125E+01
4.114E-01	3.014E+00	-4.549E+02	4.085E+01	9.568E-01	2.135E+01
4.094E-01	3.028E+00	-4.591E+02	4.143E+01	9.657E-01	2.145E+01
4.075E-01	3.042E+00	-4.635E+02	4.201E+01	9.747E-01	2.155E+01
4.056E-01	3.057E+00	-4.678E+02	4.260E+01	9.838E-01	2.165E+01
4.037E-01	3.071E+00	-4.723E+02	4.321E+01	9.931E-01	2.175E+01
4.018E-01	3.086E+00	-4.767E+02	4.382E+01	1.003E+00	2.186E+01
3.999E-01	3.101E+00	-4.813E+02	4.445E+01	1.012E+00	2.196E+01
3.980E-01	3.116E+00	-4.860E+02	4.509E+01	1.022E+00	2.207E+01
3.960E-01	3.131E+00	-4.906E+02	4.574E+01	1.031E+00	2.217E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.941E-01	3.146E+00	-4.954E+02	4.641E+01	1.041E+00	2.228E+01
3.922E-01	3.161E+00	-5.002E+02	4.709E+01	1.052E+00	2.239E+01
3.903E-01	3.177E+00	-5.051E+02	4.778E+01	1.062E+00	2.250E+01
3.884E-01	3.192E+00	-5.101E+02	4.848E+01	1.072E+00	2.261E+01
3.865E-01	3.208E+00	-5.151E+02	4.920E+01	1.083E+00	2.272E+01
3.846E-01	3.224E+00	-5.202E+02	4.993E+01	1.093E+00	2.284E+01
3.827E-01	3.240E+00	-5.254E+02	5.068E+01	1.104E+00	2.295E+01
3.807E-01	3.256E+00	-5.308E+02	5.144E+01	1.115E+00	2.307E+01
3.788E-01	3.273E+00	-5.361E+02	5.222E+01	1.126E+00	2.318E+01
3.769E-01	3.289E+00	-5.415E+02	5.302E+01	1.138E+00	2.330E+01
3.750E-01	3.306E+00	-5.470E+02	5.383E+01	1.149E+00	2.342E+01
3.731E-01	3.323E+00	-5.526E+02	5.465E+01	1.161E+00	2.354E+01
3.712E-01	3.340E+00	-5.583E+02	5.550E+01	1.173E+00	2.366E+01
3.693E-01	3.358E+00	-5.641E+02	5.636E+01	1.185E+00	2.378E+01
3.673E-01	3.375E+00	-5.700E+02	5.724E+01	1.197E+00	2.390E+01
3.654E-01	3.393E+00	-5.759E+02	5.814E+01	1.210E+00	2.403E+01
3.635E-01	3.411E+00	-5.820E+02	5.905E+01	1.222E+00	2.416E+01
3.616E-01	3.429E+00	-5.881E+02	5.998E+01	1.235E+00	2.428E+01
3.597E-01	3.447E+00	-5.943E+02	6.094E+01	1.248E+00	2.441E+01
3.578E-01	3.465E+00	-6.007E+02	6.192E+01	1.262E+00	2.454E+01
3.559E-01	3.484E+00	-6.071E+02	6.291E+01	1.275E+00	2.467E+01
3.540E-01	3.503E+00	-6.137E+02	6.393E+01	1.289E+00	2.481E+01
3.520E-01	3.522E+00	-6.203E+02	6.497E+01	1.303E+00	2.494E+01
3.501E-01	3.541E+00	-6.271E+02	6.604E+01	1.317E+00	2.508E+01
3.482E-01	3.561E+00	-6.339E+02	6.712E+01	1.331E+00	2.521E+01
3.463E-01	3.580E+00	-6.409E+02	6.823E+01	1.346E+00	2.535E+01
3.444E-01	3.600E+00	-6.480E+02	6.936E+01	1.361E+00	2.549E+01
3.425E-01	3.620E+00	-6.552E+02	7.052E+01	1.376E+00	2.563E+01
3.406E-01	3.641E+00	-6.625E+02	7.171E+01	1.391E+00	2.578E+01
3.386E-01	3.661E+00	-6.700E+02	7.292E+01	1.407E+00	2.592E+01
3.367E-01	3.682E+00	-6.776E+02	7.416E+01	1.422E+00	2.607E+01
3.348E-01	3.703E+00	-6.853E+02	7.543E+01	1.439E+00	2.622E+01
3.329E-01	3.724E+00	-6.931E+02	7.672E+01	1.455E+00	2.637E+01
3.310E-01	3.746E+00	-7.011E+02	7.805E+01	1.472E+00	2.652E+01
3.291E-01	3.768E+00	-7.092E+02	7.941E+01	1.489E+00	2.667E+01
3.272E-01	3.790E+00	-7.174E+02	8.080E+01	1.506E+00	2.683E+01
3.253E-01	3.812E+00	-7.258E+02	8.222E+01	1.524E+00	2.698E+01
3.233E-01	3.834E+00	-7.344E+02	8.368E+01	1.541E+00	2.714E+01
3.214E-01	3.857E+00	-7.431E+02	8.517E+01	1.560E+00	2.730E+01
3.195E-01	3.880E+00	-7.519E+02	8.669E+01	1.578E+00	2.747E+01
3.176E-01	3.904E+00	-7.609E+02	8.825E+01	1.597E+00	2.763E+01
3.157E-01	3.927E+00	-7.701E+02	8.985E+01	1.616E+00	2.780E+01
3.138E-01	3.951E+00	-7.794E+02	9.149E+01	1.636E+00	2.797E+01
3.119E-01	3.976E+00	-7.889E+02	9.317E+01	1.656E+00	2.814E+01
3.100E-01	4.000E+00	-7.986E+02	9.489E+01	1.676E+00	2.831E+01
3.080E-01	4.025E+00	-8.084E+02	9.665E+01	1.697E+00	2.848E+01
3.061E-01	4.050E+00	-8.184E+02	9.845E+01	1.718E+00	2.866E+01
3.042E-01	4.076E+00	-8.287E+02	1.003E+02	1.739E+00	2.884E+01
3.023E-01	4.101E+00	-8.391E+02	1.022E+02	1.761E+00	2.902E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.004E-01	4.128E+00	-8.497E+02	1.042E+02	1.783E+00	2.920E+01
2.985E-01	4.154E+00	-8.605E+02	1.061E+02	1.806E+00	2.939E+01
2.966E-01	4.181E+00	-8.715E+02	1.082E+02	1.829E+00	2.958E+01
2.946E-01	4.208E+00	-8.827E+02	1.103E+02	1.853E+00	2.977E+01
2.927E-01	4.235E+00	-8.941E+02	1.124E+02	1.877E+00	2.996E+01
2.908E-01	4.263E+00	-9.058E+02	1.147E+02	1.901E+00	3.016E+01
2.889E-01	4.292E+00	-9.177E+02	1.169E+02	1.926E+00	3.035E+01
2.870E-01	4.320E+00	-9.298E+02	1.193E+02	1.951E+00	3.056E+01
2.851E-01	4.349E+00	-9.421E+02	1.216E+02	1.977E+00	3.076E+01
2.832E-01	4.379E+00	-9.548E+02	1.241E+02	2.004E+00	3.096E+01
2.813E-01	4.408E+00	-9.676E+02	1.266E+02	2.031E+00	3.117E+01
2.793E-01	4.439E+00	-9.807E+02	1.292E+02	2.059E+00	3.138E+01
2.774E-01	4.469E+00	-9.941E+02	1.319E+02	2.087E+00	3.160E+01
2.755E-01	4.500E+00	-1.008E+03	1.346E+02	2.115E+00	3.182E+01
2.736E-01	4.532E+00	-1.022E+03	1.374E+02	2.145E+00	3.204E+01
2.717E-01	4.564E+00	-1.036E+03	1.403E+02	2.175E+00	3.226E+01
2.698E-01	4.596E+00	-1.050E+03	1.433E+02	2.205E+00	3.249E+01
2.679E-01	4.629E+00	-1.065E+03	1.463E+02	2.236E+00	3.272E+01
2.659E-01	4.662E+00	-1.080E+03	1.495E+02	2.268E+00	3.295E+01
2.640E-01	4.696E+00	-1.096E+03	1.527E+02	2.301E+00	3.318E+01
2.621E-01	4.730E+00	-1.112E+03	1.560E+02	2.334E+00	3.342E+01
2.602E-01	4.765E+00	-1.128E+03	1.594E+02	2.368E+00	3.367E+01
2.583E-01	4.800E+00	-1.144E+03	1.630E+02	2.403E+00	3.391E+01
2.564E-01	4.836E+00	-1.161E+03	1.666E+02	2.438E+00	3.416E+01
2.545E-01	4.872E+00	-1.178E+03	1.703E+02	2.474E+00	3.442E+01
2.526E-01	4.909E+00	-1.196E+03	1.742E+02	2.512E+00	3.467E+01
2.506E-01	4.947E+00	-1.214E+03	1.781E+02	2.550E+00	3.493E+01
2.487E-01	4.985E+00	-1.232E+03	1.822E+02	2.588E+00	3.520E+01
2.468E-01	5.023E+00	-1.251E+03	1.864E+02	2.628E+00	3.547E+01
2.449E-01	5.063E+00	-1.270E+03	1.908E+02	2.669E+00	3.574E+01
2.430E-01	5.103E+00	-1.290E+03	1.952E+02	2.710E+00	3.602E+01
2.411E-01	5.143E+00	-1.310E+03	1.998E+02	2.753E+00	3.630E+01
2.392E-01	5.184E+00	-1.331E+03	2.046E+02	2.796E+00	3.659E+01
2.372E-01	5.226E+00	-1.352E+03	2.095E+02	2.841E+00	3.688E+01
2.353E-01	5.269E+00	-1.373E+03	2.146E+02	2.886E+00	3.717E+01
2.334E-01	5.312E+00	-1.396E+03	2.198E+02	2.933E+00	3.747E+01
2.315E-01	5.356E+00	-1.418E+03	2.252E+02	2.981E+00	3.778E+01
2.296E-01	5.400E+00	-1.441E+03	2.308E+02	3.030E+00	3.809E+01
2.277E-01	5.446E+00	-1.465E+03	2.366E+02	3.080E+00	3.840E+01
2.258E-01	5.492E+00	-1.489E+03	2.425E+02	3.132E+00	3.872E+01
2.239E-01	5.539E+00	-1.514E+03	2.487E+02	3.185E+00	3.905E+01
2.219E-01	5.586E+00	-1.540E+03	2.551E+02	3.239E+00	3.938E+01
2.200E-01	5.635E+00	-1.566E+03	2.617E+02	3.294E+00	3.971E+01
2.181E-01	5.684E+00	-1.593E+03	2.685E+02	3.351E+00	4.005E+01
2.162E-01	5.735E+00	-1.621E+03	2.755E+02	3.410E+00	4.040E+01
2.143E-01	5.786E+00	-1.649E+03	2.828E+02	3.470E+00	4.076E+01
2.124E-01	5.838E+00	-1.678E+03	2.904E+02	3.532E+00	4.112E+01
2.105E-01	5.891E+00	-1.708E+03	2.982E+02	3.595E+00	4.148E+01
2.085E-01	5.945E+00	-1.738E+03	3.063E+02	3.660E+00	4.185E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.066E-01	6.000E+00	-1.770E+03	3.148E+02	3.726E+00	4.223E+01
2.047E-01	6.056E+00	-1.802E+03	3.235E+02	3.795E+00	4.262E+01
2.028E-01	6.114E+00	-1.835E+03	3.325E+02	3.865E+00	4.301E+01
2.009E-01	6.172E+00	-1.869E+03	3.419E+02	3.938E+00	4.341E+01
1.990E-01	6.231E+00	-1.904E+03	3.516E+02	4.012E+00	4.382E+01
1.971E-01	6.292E+00	-1.940E+03	3.618E+02	4.089E+00	4.424E+01
1.952E-01	6.353E+00	-1.977E+03	3.723E+02	4.168E+00	4.466E+01
1.932E-01	6.416E+00	-2.015E+03	3.832E+02	4.249E+00	4.509E+01
1.913E-01	6.480E+00	-2.054E+03	3.945E+02	4.332E+00	4.553E+01
1.894E-01	6.546E+00	-2.095E+03	4.063E+02	4.418E+00	4.598E+01
1.875E-01	6.612E+00	-2.136E+03	4.185E+02	4.507E+00	4.644E+01
1.856E-01	6.681E+00	-2.179E+03	4.313E+02	4.598E+00	4.690E+01
1.837E-01	6.750E+00	-2.223E+03	4.445E+02	4.692E+00	4.738E+01
1.818E-01	6.821E+00	-2.268E+03	4.584E+02	4.788E+00	4.786E+01
1.798E-01	6.894E+00	-2.315E+03	4.728E+02	4.888E+00	4.836E+01
1.779E-01	6.968E+00	-2.363E+03	4.878E+02	4.991E+00	4.886E+01
1.760E-01	7.044E+00	-2.412E+03	5.034E+02	5.097E+00	4.938E+01
1.741E-01	7.121E+00	-2.463E+03	5.197E+02	5.207E+00	4.990E+01
1.722E-01	7.200E+00	-2.516E+03	5.367E+02	5.320E+00	5.044E+01
1.703E-01	7.281E+00	-2.570E+03	5.544E+02	5.437E+00	5.099E+01
1.684E-01	7.364E+00	-2.626E+03	5.730E+02	5.557E+00	5.155E+01
1.665E-01	7.449E+00	-2.684E+03	5.923E+02	5.682E+00	5.212E+01
1.645E-01	7.535E+00	-2.744E+03	6.126E+02	5.811E+00	5.271E+01
1.626E-01	7.624E+00	-2.806E+03	6.337E+02	5.944E+00	5.331E+01
1.607E-01	7.715E+00	-2.870E+03	6.559E+02	6.082E+00	5.392E+01
1.588E-01	7.808E+00	-2.936E+03	6.790E+02	6.225E+00	5.454E+01
1.569E-01	7.903E+00	-3.005E+03	7.033E+02	6.373E+00	5.518E+01
1.550E-01	8.001E+00	-3.075E+03	7.288E+02	6.526E+00	5.584E+01
1.531E-01	8.100E+00	-3.149E+03	7.554E+02	6.684E+00	5.651E+01
1.512E-01	8.203E+00	-3.224E+03	7.834E+02	6.848E+00	5.720E+01
1.492E-01	8.308E+00	-3.303E+03	8.127E+02	7.019E+00	5.790E+01
1.473E-01	8.416E+00	-3.384E+03	8.435E+02	7.195E+00	5.862E+01
1.454E-01	8.527E+00	-3.469E+03	8.759E+02	7.379E+00	5.936E+01
1.435E-01	8.641E+00	-3.556E+03	9.100E+02	7.569E+00	6.011E+01
1.416E-01	8.757E+00	-3.647E+03	9.458E+02	7.767E+00	6.089E+01
1.397E-01	8.877E+00	-3.741E+03	9.835E+02	7.972E+00	6.168E+01
1.378E-01	9.001E+00	-3.839E+03	1.023E+03	8.186E+00	6.250E+01
1.358E-01	9.127E+00	-3.940E+03	1.065E+03	8.408E+00	6.333E+01
1.339E-01	9.257E+00	-4.046E+03	1.109E+03	8.639E+00	6.419E+01
1.320E-01	9.392E+00	-4.156E+03	1.156E+03	8.880E+00	6.507E+01
1.301E-01	9.530E+00	-4.270E+03	1.205E+03	9.131E+00	6.598E+01
1.282E-01	9.672E+00	-4.389E+03	1.257E+03	9.393E+00	6.691E+01
1.263E-01	9.819E+00	-4.512E+03	1.312E+03	9.665E+00	6.787E+01
1.244E-01	9.970E+00	-4.641E+03	1.370E+03	9.950E+00	6.885E+01
1.225E-01	1.013E+01	-4.775E+03	1.432E+03	1.025E+01	6.986E+01
1.205E-01	1.029E+01	-4.915E+03	1.497E+03	1.056E+01	7.090E+01
1.186E-01	1.045E+01	-5.061E+03	1.566E+03	1.088E+01	7.197E+01
1.167E-01	1.062E+01	-5.213E+03	1.640E+03	1.122E+01	7.307E+01
1.148E-01	1.080E+01	-5.373E+03	1.718E+03	1.158E+01	7.421E+01

Corrected optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Ag sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.129E-01	1.098E+01	-5.539E+03	1.801E+03	1.195E+01	7.538E+01
1.110E-01	1.117E+01	-5.713E+03	1.890E+03	1.234E+01	7.658E+01
1.091E-01	1.137E+01	-5.894E+03	1.984E+03	1.275E+01	7.783E+01
1.071E-01	1.157E+01	-6.084E+03	2.084E+03	1.318E+01	7.911E+01
1.052E-01	1.178E+01	-6.284E+03	2.192E+03	1.363E+01	8.043E+01
1.033E-01	1.200E+01	-6.492E+03	2.306E+03	1.410E+01	8.180E+01
1.014E-01	1.223E+01	-6.711E+03	2.429E+03	1.460E+01	8.321E+01
9.949E-02	1.246E+01	-6.941E+03	2.560E+03	1.512E+01	8.467E+01
9.758E-02	1.271E+01	-7.182E+03	2.701E+03	1.567E+01	8.618E+01
9.566E-02	1.296E+01	-7.434E+03	2.852E+03	1.625E+01	8.774E+01
9.375E-02	1.323E+01	-7.701E+03	3.015E+03	1.687E+01	8.936E+01
9.184E-02	1.350E+01	-7.980E+03	3.189E+03	1.752E+01	9.103E+01
8.992E-02	1.379E+01	-8.274E+03	3.377E+03	1.820E+01	9.277E+01
8.801E-02	1.409E+01	-8.584E+03	3.580E+03	1.893E+01	9.457E+01
8.610E-02	1.440E+01	-8.911E+03	3.798E+03	1.970E+01	9.643E+01
8.418E-02	1.473E+01	-9.255E+03	4.035E+03	2.051E+01	9.837E+01
8.227E-02	1.507E+01	-9.619E+03	4.291E+03	2.137E+01	1.004E+02
8.036E-02	1.543E+01	-1.000E+04	4.568E+03	2.229E+01	1.025E+02
7.844E-02	1.581E+01	-1.041E+04	4.869E+03	2.327E+01	1.046E+02
7.653E-02	1.620E+01	-1.084E+04	5.196E+03	2.431E+01	1.069E+02
7.462E-02	1.662E+01	-1.129E+04	5.552E+03	2.541E+01	1.093E+02
7.270E-02	1.705E+01	-1.177E+04	5.941E+03	2.659E+01	1.117E+02
7.079E-02	1.751E+01	-1.228E+04	6.364E+03	2.785E+01	1.143E+02
6.888E-02	1.800E+01	-1.282E+04	6.829E+03	2.920E+01	1.169E+02
6.696E-02	1.852E+01	-1.339E+04	7.337E+03	3.065E+01	1.197E+02
6.505E-02	1.906E+01	-1.399E+04	7.894E+03	3.220E+01	1.226E+02
6.314E-02	1.964E+01	-1.464E+04	8.508E+03	3.386E+01	1.256E+02
6.122E-02	2.025E+01	-1.532E+04	9.183E+03	3.565E+01	1.288E+02
5.931E-02	2.090E+01	-1.605E+04	9.930E+03	3.757E+01	1.321E+02
5.740E-02	2.160E+01	-1.682E+04	1.075E+04	3.965E+01	1.356E+02
5.548E-02	2.235E+01	-1.764E+04	1.167E+04	4.189E+01	1.393E+02
5.357E-02	2.314E+01	-1.852E+04	1.268E+04	4.431E+01	1.431E+02
5.166E-02	2.400E+01	-1.944E+04	1.381E+04	4.694E+01	1.471E+02
4.974E-02	2.492E+01	-2.043E+04	1.507E+04	4.979E+01	1.514E+02