

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.133E+00	3.000E-01	-1.022E+00	6.315E+00	1.639E+00	1.926E+00
3.999E+00	3.100E-01	-8.853E-01	6.494E+00	1.684E+00	1.929E+00
3.875E+00	3.200E-01	-7.193E-01	6.565E+00	1.715E+00	1.914E+00
3.757E+00	3.300E-01	-5.533E-01	6.571E+00	1.738E+00	1.891E+00
3.647E+00	3.400E-01	-4.480E-01	6.487E+00	1.740E+00	1.864E+00
3.542E+00	3.500E-01	-4.942E-01	6.265E+00	1.702E+00	1.841E+00
3.444E+00	3.600E-01	-7.148E-01	6.148E+00	1.655E+00	1.858E+00
3.351E+00	3.700E-01	-9.040E-01	6.178E+00	1.634E+00	1.891E+00
3.263E+00	3.800E-01	-1.019E+00	6.238E+00	1.628E+00	1.916E+00
3.179E+00	3.900E-01	-1.105E+00	6.276E+00	1.623E+00	1.934E+00
3.100E+00	4.000E-01	-1.156E+00	6.280E+00	1.617E+00	1.942E+00
3.024E+00	4.100E-01	-1.198E+00	6.250E+00	1.607E+00	1.945E+00
2.952E+00	4.200E-01	-1.223E+00	6.157E+00	1.590E+00	1.937E+00
2.883E+00	4.300E-01	-1.255E+00	6.040E+00	1.567E+00	1.927E+00
2.818E+00	4.400E-01	-1.281E+00	5.868E+00	1.537E+00	1.909E+00
2.755E+00	4.500E-01	-1.299E+00	5.610E+00	1.493E+00	1.879E+00
2.695E+00	4.600E-01	-1.348E+00	5.273E+00	1.431E+00	1.843E+00
2.638E+00	4.700E-01	-1.440E+00	4.833E+00	1.342E+00	1.800E+00
2.583E+00	4.800E-01	-1.633E+00	4.243E+00	1.207E+00	1.758E+00
2.530E+00	4.900E-01	-2.027E+00	3.580E+00	1.022E+00	1.752E+00
2.480E+00	5.000E-01	-2.642E+00	2.972E+00	8.168E-01	1.819E+00
2.431E+00	5.100E-01	-3.413E+00	2.522E+00	6.445E-01	1.957E+00
2.384E+00	5.200E-01	-4.191E+00	2.216E+00	5.243E-01	2.113E+00
2.339E+00	5.300E-01	-4.965E+00	1.998E+00	4.398E-01	2.271E+00
2.296E+00	5.400E-01	-5.724E+00	1.835E+00	3.789E-01	2.422E+00
2.254E+00	5.500E-01	-6.454E+00	1.704E+00	3.325E-01	2.562E+00
2.214E+00	5.600E-01	-7.188E+00	1.601E+00	2.967E-01	2.697E+00
2.175E+00	5.700E-01	-7.920E+00	1.514E+00	2.677E-01	2.827E+00
2.138E+00	5.800E-01	-8.639E+00	1.436E+00	2.435E-01	2.949E+00
2.101E+00	5.900E-01	-9.379E+00	1.374E+00	2.237E-01	3.071E+00
2.066E+00	6.000E-01	-1.010E+01	1.315E+00	2.064E-01	3.184E+00
2.033E+00	6.100E-01	-1.082E+01	1.265E+00	1.920E-01	3.295E+00
2.000E+00	6.200E-01	-1.157E+01	1.216E+00	1.785E-01	3.406E+00
1.968E+00	6.300E-01	-1.229E+01	1.172E+00	1.670E-01	3.509E+00
1.937E+00	6.400E-01	-1.305E+01	1.137E+00	1.573E-01	3.615E+00
1.907E+00	6.500E-01	-1.380E+01	1.096E+00	1.474E-01	3.718E+00
1.879E+00	6.600E-01	-1.458E+01	1.064E+00	1.393E-01	3.821E+00
1.851E+00	6.700E-01	-1.538E+01	1.044E+00	1.330E-01	3.924E+00
1.823E+00	6.800E-01	-1.618E+01	1.033E+00	1.284E-01	4.024E+00
1.797E+00	6.900E-01	-1.696E+01	1.028E+00	1.248E-01	4.120E+00
1.771E+00	7.000E-01	-1.778E+01	1.035E+00	1.227E-01	4.218E+00
1.746E+00	7.100E-01	-1.859E+01	1.054E+00	1.222E-01	4.314E+00
1.722E+00	7.200E-01	-1.940E+01	1.077E+00	1.222E-01	4.406E+00
1.698E+00	7.300E-01	-2.022E+01	1.098E+00	1.220E-01	4.498E+00
1.675E+00	7.400E-01	-2.106E+01	1.121E+00	1.221E-01	4.591E+00
1.653E+00	7.500E-01	-2.188E+01	1.148E+00	1.226E-01	4.680E+00
1.631E+00	7.600E-01	-2.273E+01	1.179E+00	1.236E-01	4.769E+00
1.610E+00	7.700E-01	-2.355E+01	1.206E+00	1.242E-01	4.855E+00
1.590E+00	7.800E-01	-2.443E+01	1.234E+00	1.248E-01	4.945E+00
1.569E+00	7.900E-01	-2.525E+01	1.274E+00	1.267E-01	5.026E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.550E+00	8.000E-01	-2.613E+01	1.299E+00	1.270E-01	5.113E+00
1.531E+00	8.100E-01	-2.701E+01	1.342E+00	1.291E-01	5.199E+00
1.512E+00	8.200E-01	-2.799E+01	1.383E+00	1.307E-01	5.292E+00
1.494E+00	8.300E-01	-2.877E+01	1.412E+00	1.316E-01	5.366E+00
1.476E+00	8.400E-01	-2.971E+01	1.450E+00	1.330E-01	5.452E+00
1.459E+00	8.500E-01	-3.086E+01	1.496E+00	1.346E-01	5.556E+00
1.442E+00	8.600E-01	-3.185E+01	1.538E+00	1.362E-01	5.645E+00
1.425E+00	8.700E-01	-3.277E+01	1.578E+00	1.378E-01	5.727E+00
1.409E+00	8.800E-01	-3.365E+01	1.613E+00	1.389E-01	5.803E+00
1.393E+00	8.900E-01	-3.473E+01	1.659E+00	1.408E-01	5.895E+00
1.378E+00	9.000E-01	-3.572E+01	1.698E+00	1.421E-01	5.979E+00
1.362E+00	9.100E-01	-3.673E+01	1.751E+00	1.444E-01	6.062E+00
1.348E+00	9.200E-01	-3.748E+01	1.785E+00	1.457E-01	6.124E+00
1.333E+00	9.300E-01	-3.855E+01	1.839E+00	1.480E-01	6.211E+00
1.319E+00	9.400E-01	-3.951E+01	1.876E+00	1.492E-01	6.287E+00
1.305E+00	9.500E-01	-4.051E+01	1.928E+00	1.514E-01	6.367E+00
1.292E+00	9.600E-01	-4.156E+01	1.992E+00	1.544E-01	6.449E+00
1.278E+00	9.700E-01	-4.265E+01	2.044E+00	1.565E-01	6.532E+00
1.265E+00	9.800E-01	-4.356E+01	2.093E+00	1.585E-01	6.602E+00
1.252E+00	9.900E-01	-4.471E+01	2.162E+00	1.616E-01	6.689E+00
1.240E+00	1.000E+00	-4.573E+01	2.223E+00	1.643E-01	6.764E+00
1.228E+00	1.010E+00	-4.687E+01	2.285E+00	1.669E-01	6.848E+00
1.216E+00	1.020E+00	-4.784E+01	2.341E+00	1.692E-01	6.919E+00
1.204E+00	1.030E+00	-4.900E+01	2.411E+00	1.722E-01	7.002E+00
1.192E+00	1.040E+00	-5.010E+01	2.473E+00	1.746E-01	7.080E+00
1.181E+00	1.050E+00	-5.119E+01	2.547E+00	1.780E-01	7.157E+00
1.170E+00	1.060E+00	-5.227E+01	2.595E+00	1.794E-01	7.232E+00
1.159E+00	1.070E+00	-5.349E+01	2.679E+00	1.831E-01	7.316E+00
1.148E+00	1.080E+00	-5.466E+01	2.745E+00	1.856E-01	7.396E+00
1.137E+00	1.090E+00	-5.561E+01	2.807E+00	1.881E-01	7.459E+00
1.127E+00	1.100E+00	-5.693E+01	2.888E+00	1.913E-01	7.548E+00
1.117E+00	1.110E+00	-5.803E+01	2.965E+00	1.945E-01	7.621E+00
1.107E+00	1.120E+00	-5.915E+01	3.022E+00	1.964E-01	7.694E+00
1.097E+00	1.130E+00	-6.039E+01	3.120E+00	2.007E-01	7.773E+00
1.088E+00	1.140E+00	-6.163E+01	3.183E+00	2.027E-01	7.853E+00
1.078E+00	1.150E+00	-6.283E+01	3.282E+00	2.069E-01	7.929E+00
1.069E+00	1.160E+00	-6.408E+01	3.364E+00	2.100E-01	8.008E+00
1.060E+00	1.170E+00	-6.547E+01	3.456E+00	2.135E-01	8.094E+00
1.051E+00	1.180E+00	-6.646E+01	3.523E+00	2.160E-01	8.155E+00
1.042E+00	1.190E+00	-6.770E+01	3.602E+00	2.188E-01	8.231E+00
1.033E+00	1.200E+00	-6.905E+01	3.681E+00	2.214E-01	8.313E+00
1.025E+00	1.210E+00	-7.027E+01	3.775E+00	2.251E-01	8.386E+00
1.016E+00	1.220E+00	-7.161E+01	3.841E+00	2.269E-01	8.466E+00
1.008E+00	1.230E+00	-7.282E+01	3.946E+00	2.311E-01	8.537E+00
9.999E-01	1.240E+00	-7.419E+01	4.019E+00	2.332E-01	8.617E+00
9.919E-01	1.250E+00	-7.555E+01	4.119E+00	2.369E-01	8.695E+00
9.840E-01	1.260E+00	-7.703E+01	4.242E+00	2.416E-01	8.780E+00
9.763E-01	1.270E+00	-7.798E+01	4.303E+00	2.436E-01	8.834E+00
9.686E-01	1.280E+00	-7.948E+01	4.414E+00	2.475E-01	8.918E+00

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
9.611E-01	1.290E+00	-8.084E+01	4.508E+00	2.506E-01	8.995E+00
9.537E-01	1.300E+00	-8.222E+01	4.575E+00	2.522E-01	9.071E+00
9.464E-01	1.310E+00	-8.360E+01	4.690E+00	2.564E-01	9.147E+00
9.393E-01	1.320E+00	-8.500E+01	4.756E+00	2.578E-01	9.223E+00
9.322E-01	1.330E+00	-8.636E+01	4.914E+00	2.643E-01	9.297E+00
9.253E-01	1.340E+00	-8.782E+01	4.974E+00	2.653E-01	9.375E+00
9.184E-01	1.350E+00	-8.914E+01	5.088E+00	2.693E-01	9.446E+00
8.670E-01	1.430E+00	-1.009E+02	5.969E+00	2.970E-01	1.005E+01
8.610E-01	1.440E+00	-1.023E+02	6.099E+00	3.014E-01	1.012E+01
8.551E-01	1.450E+00	-1.038E+02	6.154E+00	3.018E-01	1.020E+01
8.492E-01	1.460E+00	-1.054E+02	6.360E+00	3.096E-01	1.027E+01
8.434E-01	1.470E+00	-1.073E+02	6.563E+00	3.166E-01	1.036E+01
8.377E-01	1.480E+00	-1.083E+02	6.660E+00	3.198E-01	1.041E+01
8.321E-01	1.490E+00	-1.099E+02	6.740E+00	3.213E-01	1.049E+01
8.266E-01	1.500E+00	-1.116E+02	6.952E+00	3.288E-01	1.057E+01
8.211E-01	1.510E+00	-1.132E+02	7.004E+00	3.289E-01	1.065E+01
8.157E-01	1.520E+00	-1.149E+02	7.111E+00	3.316E-01	1.072E+01
8.104E-01	1.530E+00	-1.165E+02	7.218E+00	3.343E-01	1.080E+01
8.051E-01	1.540E+00	-1.182E+02	7.432E+00	3.417E-01	1.088E+01
7.999E-01	1.550E+00	-1.196E+02	7.596E+00	3.472E-01	1.094E+01
7.948E-01	1.560E+00	-1.212E+02	7.593E+00	3.447E-01	1.102E+01
7.897E-01	1.570E+00	-1.229E+02	7.814E+00	3.522E-01	1.109E+01
7.847E-01	1.580E+00	-1.246E+02	7.828E+00	3.505E-01	1.117E+01
7.798E-01	1.590E+00	-1.263E+02	8.085E+00	3.594E-01	1.125E+01
7.749E-01	1.600E+00	-1.282E+02	8.107E+00	3.579E-01	1.133E+01
7.701E-01	1.610E+00	-1.296E+02	8.304E+00	3.646E-01	1.139E+01
7.653E-01	1.620E+00	-1.312E+02	8.362E+00	3.648E-01	1.146E+01
7.606E-01	1.630E+00	-1.329E+02	8.547E+00	3.705E-01	1.154E+01
7.560E-01	1.640E+00	-1.347E+02	8.702E+00	3.747E-01	1.161E+01
7.514E-01	1.650E+00	-1.364E+02	8.879E+00	3.799E-01	1.169E+01
7.469E-01	1.660E+00	-1.381E+02	9.005E+00	3.829E-01	1.176E+01
7.424E-01	1.670E+00	-1.401E+02	9.241E+00	3.902E-01	1.184E+01
7.380E-01	1.680E+00	-1.416E+02	9.374E+00	3.937E-01	1.190E+01
7.336E-01	1.690E+00	-1.434E+02	9.524E+00	3.975E-01	1.198E+01
7.293E-01	1.700E+00	-1.452E+02	9.558E+00	3.964E-01	1.206E+01
7.251E-01	1.710E+00	-1.471E+02	9.858E+00	4.062E-01	1.213E+01
7.208E-01	1.720E+00	-1.488E+02	9.854E+00	4.037E-01	1.221E+01
7.167E-01	1.730E+00	-1.505E+02	1.009E+01	4.111E-01	1.227E+01
7.126E-01	1.740E+00	-1.525E+02	1.027E+01	4.158E-01	1.236E+01
7.085E-01	1.750E+00	-1.544E+02	1.043E+01	4.194E-01	1.243E+01
7.045E-01	1.760E+00	-1.559E+02	1.051E+01	4.204E-01	1.250E+01
7.005E-01	1.770E+00	-1.580E+02	1.061E+01	4.219E-01	1.258E+01
6.965E-01	1.780E+00	-1.598E+02	1.073E+01	4.240E-01	1.265E+01
6.926E-01	1.790E+00	-1.612E+02	1.088E+01	4.281E-01	1.270E+01
6.888E-01	1.800E+00	-1.635E+02	1.117E+01	4.365E-01	1.279E+01
6.850E-01	1.810E+00	-1.656E+02	1.110E+01	4.311E-01	1.287E+01
6.812E-01	1.820E+00	-1.676E+02	1.145E+01	4.418E-01	1.296E+01
6.775E-01	1.830E+00	-1.695E+02	1.134E+01	4.355E-01	1.303E+01
6.738E-01	1.840E+00	-1.712E+02	1.172E+01	4.475E-01	1.309E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.702E-01	1.850E+00	-1.736E+02	1.208E+01	4.580E-01	1.318E+01
6.666E-01	1.860E+00	-1.752E+02	1.191E+01	4.497E-01	1.324E+01
6.630E-01	1.870E+00	-1.775E+02	1.243E+01	4.662E-01	1.333E+01
6.595E-01	1.880E+00	-1.793E+02	1.260E+01	4.703E-01	1.340E+01
6.560E-01	1.890E+00	-1.813E+02	1.258E+01	4.669E-01	1.347E+01
6.525E-01	1.900E+00	-1.833E+02	1.287E+01	4.751E-01	1.355E+01
6.491E-01	1.910E+00	-1.854E+02	1.272E+01	4.669E-01	1.363E+01
6.458E-01	1.920E+00	-1.869E+02	1.327E+01	4.849E-01	1.368E+01
6.424E-01	1.930E+00	-1.893E+02	1.347E+01	4.893E-01	1.377E+01
6.391E-01	1.940E+00	-1.911E+02	1.336E+01	4.828E-01	1.383E+01
6.358E-01	1.950E+00	-1.934E+02	1.375E+01	4.940E-01	1.392E+01
6.326E-01	1.960E+00	-1.956E+02	1.393E+01	4.976E-01	1.400E+01
6.294E-01	1.970E+00	-1.973E+02	1.433E+01	5.097E-01	1.406E+01
6.262E-01	1.980E+00	-1.998E+02	1.439E+01	5.088E-01	1.414E+01
6.230E-01	1.990E+00	-2.019E+02	1.449E+01	5.096E-01	1.422E+01
6.199E-01	2.000E+00	-2.041E+02	1.455E+01	5.088E-01	1.429E+01
—	—	—	—	—	—
7.269E-01	1.706E+00	-1.320E+02	8.083E+00	3.517E-01	1.149E+01
7.212E-01	1.719E+00	-1.336E+02	8.358E+00	3.613E-01	1.157E+01
7.174E-01	1.728E+00	-1.348E+02	8.343E+00	3.591E-01	1.162E+01
7.135E-01	1.738E+00	-1.361E+02	8.156E+00	3.494E-01	1.167E+01
7.097E-01	1.747E+00	-1.378E+02	8.291E+00	3.530E-01	1.174E+01
7.059E-01	1.756E+00	-1.396E+02	8.639E+00	3.655E-01	1.182E+01
7.021E-01	1.766E+00	-1.414E+02	8.709E+00	3.660E-01	1.190E+01
6.982E-01	1.776E+00	-1.428E+02	8.525E+00	3.566E-01	1.196E+01
6.944E-01	1.785E+00	-1.444E+02	8.527E+00	3.546E-01	1.202E+01
6.906E-01	1.795E+00	-1.460E+02	8.799E+00	3.640E-01	1.209E+01
6.868E-01	1.805E+00	-1.475E+02	9.286E+00	3.821E-01	1.215E+01
6.830E-01	1.815E+00	-1.491E+02	9.712E+00	3.974E-01	1.222E+01
6.791E-01	1.826E+00	-1.515E+02	9.789E+00	3.975E-01	1.231E+01
6.753E-01	1.836E+00	-1.537E+02	9.784E+00	3.944E-01	1.240E+01
6.715E-01	1.847E+00	-1.550E+02	1.006E+01	4.036E-01	1.246E+01
6.676E-01	1.857E+00	-1.563E+02	1.033E+01	4.128E-01	1.251E+01
6.638E-01	1.868E+00	-1.579E+02	1.041E+01	4.139E-01	1.257E+01
6.600E-01	1.879E+00	-1.597E+02	1.042E+01	4.118E-01	1.265E+01
6.562E-01	1.890E+00	-1.617E+02	1.042E+01	4.093E-01	1.272E+01
6.524E-01	1.895E+00	-1.629E+02	1.042E+01	4.081E-01	1.277E+01
6.504E-01	1.906E+00	-1.656E+02	1.046E+01	4.064E-01	1.287E+01
6.466E-01	1.918E+00	-1.679E+02	1.087E+01	4.191E-01	1.296E+01
6.428E-01	1.929E+00	-1.695E+02	1.156E+01	4.437E-01	1.303E+01
6.408E-01	1.935E+00	-1.704E+02	1.176E+01	4.501E-01	1.306E+01
6.370E-01	1.946E+00	-1.730E+02	1.163E+01	4.419E-01	1.316E+01
6.332E-01	1.958E+00	-1.749E+02	1.134E+01	4.285E-01	1.323E+01
6.294E-01	1.970E+00	-1.767E+02	1.161E+01	4.366E-01	1.330E+01
6.274E-01	1.976E+00	-1.775E+02	1.178E+01	4.420E-01	1.333E+01
6.236E-01	1.988E+00	-1.799E+02	1.202E+01	4.477E-01	1.342E+01
6.217E-01	1.994E+00	-1.810E+02	1.213E+01	4.504E-01	1.346E+01
6.179E-01	2.007E+00	-1.834E+02	1.245E+01	4.594E-01	1.355E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
6.141E-01	2.019E+00	-1.861E+02	1.271E+01	4.658E-01	1.365E+01
6.121E-01	2.025E+00	-1.874E+02	1.276E+01	4.658E-01	1.370E+01
6.083E-01	2.038E+00	-1.896E+02	1.261E+01	4.577E-01	1.378E+01
6.064E-01	2.045E+00	-1.907E+02	1.266E+01	4.581E-01	1.382E+01
6.026E-01	2.058E+00	-1.934E+02	1.318E+01	4.736E-01	1.392E+01
6.007E-01	2.064E+00	-1.948E+02	1.336E+01	4.784E-01	1.397E+01
5.969E-01	2.077E+00	-1.973E+02	1.358E+01	4.830E-01	1.405E+01
5.949E-01	2.084E+00	-1.985E+02	1.372E+01	4.868E-01	1.410E+01
5.911E-01	2.098E+00	-2.013E+02	1.392E+01	4.903E-01	1.420E+01
5.892E-01	2.104E+00	-2.031E+02	1.407E+01	4.935E-01	1.426E+01
5.854E-01	2.118E+00	-2.057E+02	1.448E+01	5.046E-01	1.435E+01
5.835E-01	2.125E+00	-2.070E+02	1.454E+01	5.049E-01	1.440E+01
5.796E-01	2.139E+00	-2.098E+02	1.478E+01	5.098E-01	1.449E+01
5.777E-01	2.146E+00	-2.110E+02	1.508E+01	5.189E-01	1.453E+01
5.758E-01	2.153E+00	-2.124E+02	1.542E+01	5.288E-01	1.458E+01
5.720E-01	2.168E+00	-2.153E+02	1.607E+01	5.470E-01	1.468E+01
5.701E-01	2.175E+00	-2.168E+02	1.633E+01	5.542E-01	1.473E+01
5.662E-01	2.190E+00	-2.196E+02	1.667E+01	5.622E-01	1.483E+01
5.643E-01	2.197E+00	-2.213E+02	1.684E+01	5.655E-01	1.489E+01
5.624E-01	2.205E+00	-2.230E+02	1.693E+01	5.663E-01	1.495E+01
5.586E-01	2.220E+00	-2.261E+02	1.701E+01	5.651E-01	1.505E+01
5.567E-01	2.227E+00	-2.278E+02	1.722E+01	5.700E-01	1.510E+01
5.548E-01	2.235E+00	-2.293E+02	1.749E+01	5.772E-01	1.516E+01
5.529E-01	2.243E+00	-2.309E+02	1.777E+01	5.844E-01	1.521E+01
5.490E-01	2.258E+00	-2.331E+02	1.808E+01	5.917E-01	1.528E+01
5.471E-01	2.266E+00	-2.349E+02	1.824E+01	5.945E-01	1.534E+01
5.452E-01	2.274E+00	-2.371E+02	1.852E+01	6.009E-01	1.541E+01
5.433E-01	2.282E+00	-2.391E+02	1.887E+01	6.097E-01	1.547E+01
5.395E-01	2.298E+00	-2.429E+02	1.968E+01	6.310E-01	1.560E+01
5.375E-01	2.307E+00	-2.446E+02	1.992E+01	6.364E-01	1.565E+01
5.356E-01	2.315E+00	-2.464E+02	2.001E+01	6.370E-01	1.571E+01
5.337E-01	2.323E+00	-2.485E+02	2.009E+01	6.366E-01	1.578E+01
5.299E-01	2.340E+00	-2.522E+02	1.995E+01	6.277E-01	1.589E+01
5.280E-01	2.348E+00	-2.541E+02	2.001E+01	6.270E-01	1.595E+01
5.261E-01	2.357E+00	-2.563E+02	2.034E+01	6.347E-01	1.602E+01
5.242E-01	2.365E+00	-2.581E+02	2.066E+01	6.424E-01	1.608E+01
5.223E-01	2.374E+00	-2.598E+02	2.074E+01	6.428E-01	1.613E+01
5.203E-01	2.383E+00	-2.616E+02	2.068E+01	6.388E-01	1.619E+01
5.184E-01	2.392E+00	-2.636E+02	2.061E+01	6.343E-01	1.625E+01
5.146E-01	2.409E+00	-2.680E+02	2.101E+01	6.411E-01	1.638E+01
5.127E-01	2.418E+00	-2.702E+02	2.159E+01	6.561E-01	1.645E+01
5.108E-01	2.427E+00	-2.722E+02	2.208E+01	6.686E-01	1.651E+01
5.089E-01	2.437E+00	-2.742E+02	2.235E+01	6.742E-01	1.657E+01
5.069E-01	2.446E+00	-2.764E+02	2.259E+01	6.788E-01	1.664E+01
5.050E-01	2.455E+00	-2.783E+02	2.292E+01	6.864E-01	1.670E+01
5.031E-01	2.464E+00	-2.806E+02	2.328E+01	6.943E-01	1.677E+01
5.012E-01	2.474E+00	-2.833E+02	2.363E+01	7.014E-01	1.685E+01
4.993E-01	2.483E+00	-2.859E+02	2.394E+01	7.072E-01	1.692E+01
4.974E-01	2.493E+00	-2.881E+02	2.420E+01	7.122E-01	1.699E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.955E-01	2.502E+00	-2.900E+02	2.447E+01	7.179E-01	1.705E+01
4.935E-01	2.512E+00	-2.921E+02	2.477E+01	7.241E-01	1.711E+01
4.916E-01	2.522E+00	-2.945E+02	2.511E+01	7.310E-01	1.718E+01
4.897E-01	2.532E+00	-2.970E+02	2.552E+01	7.397E-01	1.725E+01
4.878E-01	2.542E+00	-2.995E+02	2.597E+01	7.497E-01	1.732E+01
4.859E-01	2.552E+00	-3.020E+02	2.644E+01	7.600E-01	1.739E+01
4.840E-01	2.562E+00	-3.046E+02	2.686E+01	7.689E-01	1.747E+01
4.821E-01	2.572E+00	-3.070E+02	2.718E+01	7.748E-01	1.754E+01
4.802E-01	2.582E+00	-3.095E+02	2.745E+01	7.793E-01	1.761E+01
4.782E-01	2.593E+00	-3.121E+02	2.778E+01	7.853E-01	1.768E+01
4.763E-01	2.603E+00	-3.146E+02	2.808E+01	7.907E-01	1.775E+01
4.744E-01	2.613E+00	-3.172E+02	2.838E+01	7.959E-01	1.783E+01
4.725E-01	2.624E+00	-3.203E+02	2.880E+01	8.037E-01	1.791E+01
4.706E-01	2.635E+00	-3.232E+02	2.917E+01	8.106E-01	1.800E+01
4.687E-01	2.645E+00	-3.257E+02	2.943E+01	8.146E-01	1.807E+01
4.668E-01	2.656E+00	-3.284E+02	2.969E+01	8.184E-01	1.814E+01
4.649E-01	2.667E+00	-3.314E+02	3.009E+01	8.257E-01	1.822E+01
4.629E-01	2.678E+00	-3.343E+02	3.061E+01	8.362E-01	1.830E+01
4.610E-01	2.689E+00	-3.368E+02	3.101E+01	8.439E-01	1.837E+01
4.591E-01	2.701E+00	-3.397E+02	3.117E+01	8.448E-01	1.845E+01
4.572E-01	2.712E+00	-3.427E+02	3.123E+01	8.426E-01	1.853E+01
4.553E-01	2.723E+00	-3.457E+02	3.138E+01	8.430E-01	1.861E+01
4.534E-01	2.735E+00	-3.485E+02	3.178E+01	8.502E-01	1.869E+01
4.515E-01	2.746E+00	-3.511E+02	3.252E+01	8.668E-01	1.876E+01
4.496E-01	2.758E+00	-3.537E+02	3.337E+01	8.862E-01	1.883E+01
4.476E-01	2.770E+00	-3.569E+02	3.405E+01	9.001E-01	1.891E+01
4.457E-01	2.782E+00	-3.608E+02	3.454E+01	9.081E-01	1.902E+01
4.438E-01	2.794E+00	-3.645E+02	3.501E+01	9.160E-01	1.911E+01
4.419E-01	2.806E+00	-3.676E+02	3.559E+01	9.269E-01	1.920E+01
4.400E-01	2.818E+00	-3.706E+02	3.621E+01	9.394E-01	1.928E+01
4.381E-01	2.830E+00	-3.736E+02	3.679E+01	9.507E-01	1.935E+01
4.362E-01	2.843E+00	-3.766E+02	3.716E+01	9.563E-01	1.943E+01
4.343E-01	2.855E+00	-3.799E+02	3.731E+01	9.560E-01	1.952E+01
4.323E-01	2.868E+00	-3.836E+02	3.757E+01	9.579E-01	1.961E+01
4.304E-01	2.881E+00	-3.872E+02	3.805E+01	9.655E-01	1.970E+01
4.285E-01	2.893E+00	-3.908E+02	3.866E+01	9.767E-01	1.979E+01
4.266E-01	2.906E+00	-3.943E+02	3.951E+01	9.938E-01	1.988E+01
4.247E-01	2.919E+00	-3.977E+02	4.060E+01	1.017E+00	1.997E+01
4.228E-01	2.933E+00	-4.010E+02	4.152E+01	1.035E+00	2.005E+01
4.209E-01	2.946E+00	-4.045E+02	4.185E+01	1.039E+00	2.014E+01
4.189E-01	2.959E+00	-4.083E+02	4.206E+01	1.040E+00	2.023E+01
4.170E-01	2.973E+00	-4.123E+02	4.269E+01	1.050E+00	2.033E+01
4.151E-01	2.987E+00	-4.161E+02	4.329E+01	1.060E+00	2.043E+01
4.132E-01	3.001E+00	-4.199E+02	4.353E+01	1.061E+00	2.052E+01
4.113E-01	3.015E+00	-4.240E+02	4.369E+01	1.060E+00	2.062E+01
4.094E-01	3.029E+00	-4.281E+02	4.401E+01	1.062E+00	2.072E+01
4.075E-01	3.043E+00	-4.322E+02	4.463E+01	1.072E+00	2.082E+01
4.056E-01	3.057E+00	-4.360E+02	4.554E+01	1.089E+00	2.091E+01
4.036E-01	3.072E+00	-4.399E+02	4.675E+01	1.113E+00	2.100E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
4.017E-01	3.086E+00	-4.438E+02	4.803E+01	1.138E+00	2.110E+01
3.998E-01	3.101E+00	-4.482E+02	4.883E+01	1.152E+00	2.120E+01
3.979E-01	3.116E+00	-4.530E+02	4.920E+01	1.154E+00	2.131E+01
3.960E-01	3.131E+00	-4.579E+02	4.960E+01	1.157E+00	2.143E+01
3.941E-01	3.146E+00	-4.627E+02	5.001E+01	1.161E+00	2.154E+01
3.922E-01	3.162E+00	-4.672E+02	5.052E+01	1.167E+00	2.165E+01
3.903E-01	3.177E+00	-4.717E+02	5.126E+01	1.178E+00	2.175E+01
3.883E-01	3.193E+00	-4.763E+02	5.193E+01	1.188E+00	2.186E+01
3.864E-01	3.209E+00	-4.811E+02	5.253E+01	1.196E+00	2.197E+01
3.845E-01	3.224E+00	-4.862E+02	5.341E+01	1.209E+00	2.208E+01
3.826E-01	3.241E+00	-4.912E+02	5.444E+01	1.226E+00	2.220E+01
3.807E-01	3.257E+00	-4.961E+02	5.531E+01	1.240E+00	2.231E+01
3.788E-01	3.273E+00	-5.011E+02	5.614E+01	1.252E+00	2.242E+01
3.769E-01	3.290E+00	-5.062E+02	5.707E+01	1.266E+00	2.254E+01
3.749E-01	3.307E+00	-5.115E+02	5.774E+01	1.274E+00	2.265E+01
3.730E-01	3.324E+00	-5.171E+02	5.807E+01	1.275E+00	2.278E+01
3.711E-01	3.341E+00	-5.232E+02	5.891E+01	1.286E+00	2.291E+01
3.692E-01	3.358E+00	-5.287E+02	6.042E+01	1.312E+00	2.303E+01
3.673E-01	3.376E+00	-5.336E+02	6.176E+01	1.335E+00	2.314E+01
3.654E-01	3.393E+00	-5.389E+02	6.274E+01	1.349E+00	2.325E+01
3.635E-01	3.411E+00	-5.442E+02	6.353E+01	1.359E+00	2.337E+01
3.616E-01	3.429E+00	-5.496E+02	6.426E+01	1.368E+00	2.348E+01
3.596E-01	3.447E+00	-5.558E+02	6.499E+01	1.376E+00	2.362E+01
3.577E-01	3.466E+00	-5.620E+02	6.579E+01	1.385E+00	2.375E+01
3.558E-01	3.485E+00	-5.683E+02	6.677E+01	1.398E+00	2.388E+01
3.539E-01	3.503E+00	-5.747E+02	6.786E+01	1.413E+00	2.402E+01
3.520E-01	3.522E+00	-5.810E+02	6.895E+01	1.428E+00	2.415E+01
3.501E-01	3.542E+00	-5.873E+02	6.996E+01	1.441E+00	2.428E+01
3.482E-01	3.561E+00	-5.940E+02	7.079E+01	1.450E+00	2.442E+01
3.463E-01	3.581E+00	-6.010E+02	7.157E+01	1.457E+00	2.456E+01
3.443E-01	3.601E+00	-6.075E+02	7.292E+01	1.477E+00	2.469E+01
3.424E-01	3.621E+00	-6.142E+02	7.417E+01	1.494E+00	2.483E+01
3.405E-01	3.641E+00	-6.213E+02	7.490E+01	1.500E+00	2.497E+01
3.386E-01	3.662E+00	-6.284E+02	7.593E+01	1.512E+00	2.511E+01
3.367E-01	3.683E+00	-6.356E+02	7.722E+01	1.529E+00	2.526E+01
3.348E-01	3.704E+00	-6.433E+02	7.835E+01	1.542E+00	2.541E+01
3.329E-01	3.725E+00	-6.513E+02	7.947E+01	1.554E+00	2.557E+01
3.310E-01	3.746E+00	-6.589E+02	8.119E+01	1.579E+00	2.572E+01
3.290E-01	3.768E+00	-6.664E+02	8.299E+01	1.604E+00	2.587E+01
3.271E-01	3.790E+00	-6.744E+02	8.429E+01	1.620E+00	2.602E+01
3.252E-01	3.812E+00	-6.826E+02	8.610E+01	1.644E+00	2.618E+01
3.233E-01	3.835E+00	-6.910E+02	8.795E+01	1.670E+00	2.634E+01
3.214E-01	3.858E+00	-6.995E+02	8.921E+01	1.683E+00	2.650E+01
3.195E-01	3.881E+00	-7.080E+02	9.037E+01	1.695E+00	2.666E+01
3.176E-01	3.904E+00	-7.164E+02	9.181E+01	1.712E+00	2.682E+01
3.156E-01	3.928E+00	-7.254E+02	9.349E+01	1.732E+00	2.699E+01
3.137E-01	3.952E+00	-7.343E+02	9.522E+01	1.753E+00	2.715E+01
3.118E-01	3.976E+00	-7.429E+02	9.731E+01	1.781E+00	2.732E+01
3.099E-01	4.001E+00	-7.521E+02	9.921E+01	1.805E+00	2.748E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
3.080E-01	4.026E+00	-7.616E+02	1.007E+02	1.820E+00	2.766E+01
3.061E-01	4.051E+00	-7.711E+02	1.024E+02	1.840E+00	2.783E+01
3.042E-01	4.076E+00	-7.809E+02	1.046E+02	1.867E+00	2.801E+01
3.023E-01	4.102E+00	-7.907E+02	1.068E+02	1.894E+00	2.818E+01
3.003E-01	4.128E+00	-8.009E+02	1.088E+02	1.919E+00	2.837E+01
2.984E-01	4.155E+00	-8.118E+02	1.110E+02	1.944E+00	2.856E+01
2.965E-01	4.181E+00	-8.215E+02	1.130E+02	1.967E+00	2.873E+01
2.946E-01	4.209E+00	-8.288E+02	1.148E+02	1.989E+00	2.886E+01
2.927E-01	4.236E+00	-8.381E+02	1.167E+02	2.011E+00	2.902E+01
2.908E-01	4.264E+00	-8.497E+02	1.188E+02	2.033E+00	2.922E+01
2.889E-01	4.292E+00	-8.627E+02	1.214E+02	2.061E+00	2.944E+01
2.869E-01	4.321E+00	-8.762E+02	1.241E+02	2.091E+00	2.967E+01
2.850E-01	4.350E+00	-8.893E+02	1.267E+02	2.119E+00	2.990E+01
2.831E-01	4.379E+00	-9.021E+02	1.291E+02	2.143E+00	3.011E+01
2.812E-01	4.409E+00	-9.143E+02	1.312E+02	2.163E+00	3.032E+01
2.793E-01	4.439E+00	-9.268E+02	1.333E+02	2.184E+00	3.052E+01
2.774E-01	4.470E+00	-9.396E+02	1.359E+02	2.211E+00	3.073E+01
2.755E-01	4.501E+00	-9.526E+02	1.389E+02	2.245E+00	3.095E+01
2.736E-01	4.532E+00	-9.658E+02	1.422E+02	2.282E+00	3.116E+01
2.716E-01	4.564E+00	-9.789E+02	1.450E+02	2.310E+00	3.137E+01
2.697E-01	4.597E+00	-9.927E+02	1.470E+02	2.327E+00	3.159E+01
2.678E-01	4.629E+00	-1.006E+03	1.498E+02	2.355E+00	3.180E+01
2.659E-01	4.663E+00	-1.019E+03	1.536E+02	2.398E+00	3.202E+01
2.640E-01	4.697E+00	-1.035E+03	1.570E+02	2.433E+00	3.227E+01
2.621E-01	4.731E+00	-1.051E+03	1.602E+02	2.464E+00	3.252E+01
2.602E-01	4.766E+00	-1.067E+03	1.640E+02	2.503E+00	3.276E+01
2.583E-01	4.801E+00	-1.082E+03	1.676E+02	2.540E+00	3.299E+01
2.563E-01	4.837E+00	-1.098E+03	1.713E+02	2.577E+00	3.324E+01
2.544E-01	4.873E+00	-1.115E+03	1.753E+02	2.617E+00	3.349E+01
2.525E-01	4.910E+00	-1.132E+03	1.787E+02	2.648E+00	3.375E+01
2.506E-01	4.947E+00	-1.149E+03	1.819E+02	2.674E+00	3.401E+01
2.487E-01	4.986E+00	-1.167E+03	1.856E+02	2.709E+00	3.426E+01
2.468E-01	5.024E+00	-1.184E+03	1.894E+02	2.744E+00	3.452E+01
2.449E-01	5.063E+00	-1.202E+03	1.935E+02	2.782E+00	3.478E+01
2.429E-01	5.103E+00	-1.220E+03	1.978E+02	2.822E+00	3.504E+01
2.410E-01	5.144E+00	-1.238E+03	2.019E+02	2.859E+00	3.531E+01
2.391E-01	5.185E+00	-1.257E+03	2.067E+02	2.905E+00	3.557E+01
2.372E-01	5.227E+00	-1.276E+03	2.118E+02	2.955E+00	3.585E+01
2.353E-01	5.269E+00	-1.297E+03	2.166E+02	2.997E+00	3.614E+01
2.334E-01	5.312E+00	-1.318E+03	2.218E+02	3.043E+00	3.643E+01
2.315E-01	5.356E+00	-1.340E+03	2.271E+02	3.091E+00	3.673E+01
2.296E-01	5.401E+00	-1.361E+03	2.322E+02	3.136E+00	3.702E+01
2.276E-01	5.446E+00	-1.383E+03	2.379E+02	3.187E+00	3.733E+01
2.257E-01	5.493E+00	-1.407E+03	2.444E+02	3.246E+00	3.765E+01
2.238E-01	5.539E+00	-1.430E+03	2.508E+02	3.303E+00	3.796E+01
2.219E-01	5.587E+00	-1.452E+03	2.576E+02	3.366E+00	3.826E+01
2.200E-01	5.636E+00	-1.475E+03	2.645E+02	3.429E+00	3.856E+01
2.181E-01	5.685E+00	-1.498E+03	2.716E+02	3.495E+00	3.886E+01
2.162E-01	5.736E+00	-1.521E+03	2.788E+02	3.560E+00	3.916E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
2.143E-01	5.787E+00	-1.545E+03	2.853E+02	3.613E+00	3.948E+01
2.123E-01	5.839E+00	-1.570E+03	2.895E+02	3.637E+00	3.979E+01
2.104E-01	5.892E+00	-1.597E+03	2.949E+02	3.674E+00	4.013E+01
2.085E-01	5.946E+00	-1.628E+03	3.030E+02	3.739E+00	4.052E+01
2.066E-01	6.001E+00	-1.658E+03	3.106E+02	3.798E+00	4.089E+01
2.047E-01	6.057E+00	-1.689E+03	3.194E+02	3.869E+00	4.129E+01
2.028E-01	6.114E+00	-1.725E+03	3.296E+02	3.950E+00	4.173E+01
2.009E-01	6.173E+00	-1.759E+03	3.383E+02	4.016E+00	4.213E+01
1.990E-01	6.232E+00	-1.792E+03	3.472E+02	4.082E+00	4.253E+01
1.970E-01	6.292E+00	-1.825E+03	3.561E+02	4.148E+00	4.293E+01
1.951E-01	6.354E+00	-1.854E+03	3.637E+02	4.204E+00	4.326E+01
1.932E-01	6.417E+00	-1.885E+03	3.737E+02	4.284E+00	4.362E+01
1.913E-01	6.481E+00	-1.922E+03	3.878E+02	4.401E+00	4.406E+01
1.894E-01	6.547E+00	-1.958E+03	4.009E+02	4.507E+00	4.448E+01
1.875E-01	6.613E+00	-1.996E+03	4.124E+02	4.592E+00	4.491E+01
1.856E-01	6.682E+00	-2.042E+03	4.274E+02	4.703E+00	4.544E+01
1.836E-01	6.751E+00	-2.084E+03	4.424E+02	4.818E+00	4.591E+01
1.817E-01	6.822E+00	-2.124E+03	4.558E+02	4.917E+00	4.635E+01
1.798E-01	6.895E+00	-2.171E+03	4.708E+02	5.024E+00	4.686E+01
1.779E-01	6.969E+00	-2.214E+03	4.842E+02	5.115E+00	4.733E+01
1.760E-01	7.045E+00	-2.256E+03	4.991E+02	5.223E+00	4.778E+01
1.741E-01	7.122E+00	-2.315E+03	5.241E+02	5.413E+00	4.841E+01
1.722E-01	7.201E+00	-2.373E+03	5.458E+02	5.565E+00	4.903E+01
1.703E-01	7.282E+00	-2.421E+03	5.538E+02	5.592E+00	4.952E+01
1.683E-01	7.365E+00	-2.490E+03	5.751E+02	5.726E+00	5.023E+01
1.664E-01	7.450E+00	-2.543E+03	6.044E+02	5.951E+00	5.078E+01
1.645E-01	7.536E+00	-2.590E+03	6.205E+02	6.054E+00	5.125E+01
1.626E-01	7.625E+00	-2.649E+03	6.336E+02	6.112E+00	5.183E+01
1.607E-01	7.716E+00	-2.711E+03	6.572E+02	6.265E+00	5.245E+01
1.588E-01	7.809E+00	-2.772E+03	6.890E+02	6.495E+00	5.305E+01
1.569E-01	7.904E+00	-2.831E+03	7.234E+02	6.745E+00	5.363E+01
1.550E-01	8.001E+00	-2.893E+03	7.549E+02	6.959E+00	5.424E+01
1.530E-01	8.101E+00	-2.970E+03	7.761E+02	7.062E+00	5.495E+01
1.511E-01	8.204E+00	-3.051E+03	8.007E+02	7.188E+00	5.570E+01
1.492E-01	8.309E+00	-3.123E+03	8.418E+02	7.465E+00	5.638E+01
1.473E-01	8.417E+00	-3.194E+03	8.949E+02	7.843E+00	5.706E+01
1.454E-01	8.528E+00	-3.265E+03	9.392E+02	8.136E+00	5.772E+01
1.435E-01	8.642E+00	-3.334E+03	9.816E+02	8.411E+00	5.835E+01
1.416E-01	8.758E+00	-3.405E+03	1.036E+03	8.782E+00	5.901E+01
1.396E-01	8.878E+00	-3.474E+03	1.078E+03	9.041E+00	5.963E+01
1.377E-01	9.002E+00	-3.539E+03	1.104E+03	9.169E+00	6.019E+01
1.358E-01	9.128E+00	-3.620E+03	1.121E+03	9.212E+00	6.087E+01
1.339E-01	9.259E+00	-3.716E+03	1.137E+03	9.221E+00	6.165E+01
1.320E-01	9.393E+00	-3.825E+03	1.163E+03	9.300E+00	6.254E+01
1.301E-01	9.531E+00	-3.950E+03	1.192E+03	9.380E+00	6.354E+01
1.282E-01	9.673E+00	-4.076E+03	1.226E+03	9.499E+00	6.454E+01
1.263E-01	9.820E+00	-4.202E+03	1.275E+03	9.727E+00	6.555E+01
1.243E-01	9.971E+00	-4.328E+03	1.327E+03	9.975E+00	6.654E+01
1.224E-01	1.013E+01	-4.452E+03	1.382E+03	1.024E+01	6.750E+01

Raw data for optical dielectric function $\epsilon_r = \epsilon_1 + i\epsilon_2$ and $\tilde{N} = n + ik$ of template stripped Au sample C
 Data supplement to Yang et al., *Physical Review B* 91, 235137 (2015) (continued).

E (eV)	λ (μm)	ϵ_1	ϵ_2	n	k
1.205E-01	1.029E+01	-4.581E+03	1.442E+03	1.053E+01	6.850E+01
1.186E-01	1.045E+01	-4.714E+03	1.519E+03	1.092E+01	6.952E+01
1.167E-01	1.063E+01	-4.850E+03	1.616E+03	1.145E+01	7.058E+01
1.148E-01	1.080E+01	-4.999E+03	1.690E+03	1.179E+01	7.168E+01
1.129E-01	1.099E+01	-5.147E+03	1.746E+03	1.200E+01	7.274E+01
1.110E-01	1.117E+01	-5.294E+03	1.825E+03	1.237E+01	7.380E+01
1.090E-01	1.137E+01	-5.454E+03	1.936E+03	1.291E+01	7.497E+01
1.071E-01	1.157E+01	-5.618E+03	2.041E+03	1.340E+01	7.614E+01
1.052E-01	1.178E+01	-5.791E+03	2.119E+03	1.370E+01	7.732E+01
1.033E-01	1.200E+01	-5.970E+03	2.213E+03	1.409E+01	7.854E+01
1.014E-01	1.223E+01	-6.176E+03	2.324E+03	1.454E+01	7.992E+01
9.947E-02	1.246E+01	-6.441E+03	2.460E+03	1.506E+01	8.166E+01
9.756E-02	1.271E+01	-6.693E+03	2.619E+03	1.572E+01	8.331E+01
9.565E-02	1.296E+01	-6.921E+03	2.768E+03	1.633E+01	8.478E+01
9.374E-02	1.323E+01	-7.153E+03	2.959E+03	1.714E+01	8.630E+01
9.183E-02	1.350E+01	-7.390E+03	3.146E+03	1.792E+01	8.781E+01
8.991E-02	1.379E+01	-7.615E+03	3.283E+03	1.840E+01	8.918E+01
8.800E-02	1.409E+01	-7.855E+03	3.481E+03	1.920E+01	9.068E+01
8.608E-02	1.440E+01	-8.132E+03	3.697E+03	2.001E+01	9.237E+01
8.417E-02	1.473E+01	-8.421E+03	3.843E+03	2.044E+01	9.401E+01
8.226E-02	1.507E+01	-8.785E+03	4.020E+03	2.093E+01	9.604E+01
8.035E-02	1.543E+01	-9.167E+03	4.221E+03	2.151E+01	9.813E+01
7.843E-02	1.581E+01	-9.584E+03	4.415E+03	2.200E+01	1.003E+02
7.652E-02	1.620E+01	-9.937E+03	4.816E+03	2.351E+01	1.024E+02
7.461E-02	1.662E+01	-1.030E+04	5.186E+03	2.482E+01	1.045E+02
7.269E-02	1.706E+01	-1.088E+04	5.298E+03	2.472E+01	1.072E+02
7.078E-02	1.752E+01	-1.140E+04	5.432E+03	2.478E+01	1.096E+02
6.887E-02	1.800E+01	-1.192E+04	5.702E+03	2.543E+01	1.121E+02
6.696E-02	1.852E+01	-1.263E+04	5.963E+03	2.585E+01	1.153E+02
6.504E-02	1.906E+01	-1.329E+04	6.403E+03	2.704E+01	1.184E+02
6.313E-02	1.964E+01	-1.376E+04	6.906E+03	2.860E+01	1.207E+02
6.121E-02	2.025E+01	-1.402E+04	7.493E+03	3.063E+01	1.223E+02
5.930E-02	2.091E+01	-1.468E+04	8.413E+03	3.347E+01	1.257E+02
5.739E-02	2.160E+01	-1.581E+04	9.155E+03	3.507E+01	1.305E+02
5.548E-02	2.235E+01	-1.718E+04	9.595E+03	3.534E+01	1.358E+02
5.356E-02	2.315E+01	-1.827E+04	1.058E+04	3.771E+01	1.403E+02
5.165E-02	2.400E+01	-1.847E+04	1.210E+04	4.248E+01	1.424E+02
4.974E-02	2.493E+01	-1.931E+04	1.347E+04	4.602E+01	1.464E+02